



INTERNATIONAL STANDARD ISO 12947-2:1998
TECHNICAL CORRIGENDUM 1

Published 2002-11-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textiles — Determination of the abrasion resistance of fabrics by the Martindale method —

Part 2: Determination of specimen breakdown

TECHNICAL CORRIGENDUM 1

Textiles — Détermination de la résistance à l'abrasion des étoffes par la méthode Martindale —

Partie 2: Détermination de la détérioration de l'éprouvette

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 12947-2:1998 was prepared by Technical Committee ISO/TC 38, *Textiles*.

Page 2

6 Conditioning and testing atmosphere, new text to read:

A standard temperate atmosphere for conditioning and testing textiles shall be used, i.e. a temperature of $(20 \pm 2) ^\circ\text{C}$ and a relative humidity of $(65 \pm 2) \%$ as defined in ISO 139.

Page 3

7.4.1: change dimension $38^{+0,5}_0$ to $38,0^{+0,5}_0$

7.4.3: change dimension $140^{+0,5}_0$ to 140^{+5}_0

7.4.4: change dimension $38^{+0,5}_0$ to $38,0^{+0,5}_0$