



INTERNATIONAL STANDARD ISO 17190-9:2001
TECHNICAL CORRIGENDUM 1

Published 2002-10-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Urine-absorbing aids for incontinence — Test methods for characterizing polymer-based absorbent materials —

**Part 9:
Gravimetric determination of density**

TECHNICAL CORRIGENDUM 1

Aides pour absorption d'urine — Méthodes d'essai pour caractériser les matériaux absorbants à base de polymères —

Partie 9: Détermination gravimétrique de la masse volumique

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 17190-9:2001 was prepared by Technical Committee ISO/TC 173, *Technical systems and aids for disabled or handicapped persons*, Subcommittee SC 3, *Aids for ostomy and incontinence*.

Annex A (informative)**Statistical results of interlaboratory tests**

Replace the existing table with the following table of results:

| Sample identification | A | B | C |
|---|--------|--------|--------|
| Number of participating laboratories | 10 | 10 | 10 |
| Number of laboratories whose results were accepted (excluding those whose results were discarded as outliers) | 10 | 9 | 10 |
| Number of accepted test results | 40 | 36 | 40 |
| Mean value (g/ml) | 0,67 | 0,69 | 0,72 |
| Repeatability standard deviation (s_r) | 0,00 | 0,01 | 0,00 |
| Repeatability coefficient of variation | 0,70 % | 0,85 % | 0,56 % |
| Repeatability limit (r) ($2,8 \times s_r$) | 0,01 | 0,02 | 0,01 |
| Reproducibility standard deviation of reproducibility (s_R) | 0,02 | 0,01 | 0,03 |
| Reproducibility coefficient of variation | 2,38 % | 2,17 % | 3,89 % |
| Reproducibility limit (R) ($2,8 \times s_R$) | 0,04 | 0,04 | 0,08 |