

English version
Version Française
Deutsche Fassung

Grouts for tiles - Part 4: Determination of shrinkage

Mortiers de joints pour carrelages - Partie
4: Détermination du retrait

Klebstoffe und Fugenmörtel für Fliesen und
Platten - Teil 4: Bestimmung der
Schwindung

This corrigendum becomes effective on 6 April 2011 for incorporation in the three official language versions of the EN.

Ce corrigendum prendra effet le 6 avril 2011 pour incorporation dans les trois versions linguistiques officielles de la EN.

Die Berichtigung tritt am 6. April 2011 zur Einarbeitung in die drei offiziellen Sprachfassungen der EN in Kraft.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

1 Modification to 6.1

Replace entry 6.1 with the following: "

6.1 Moulds, used to prepare prismatic specimens $10\text{ mm} \times 40\text{ mm} \times 160\text{ mm}$ (three-gang mould), with ground surfaces, made of steel, in accordance with EN 196-1. Holes for fitting suitable pins shall be drilled into the ends of the sides of the moulds corresponding to the ends of test specimen (see Figure 1):

- a) moulds with horizontal compartments $10\text{ mm} \times 40\text{ mm} \times 160\text{ mm}$, or
- b) moulds with horizontal compartments $40\text{ mm} \times 40\text{ mm} \times 160\text{ mm}$ and width reducing plastic or metal inserts (6.2), two for each mould."