

EUROPEAN STANDARD

EN 1993-1-9:2005/AC

NORME EUROPÉENNE

April 2009

EUROPÄISCHE NORM

Avril 2009

April 2009

ICS 91.010.30

English version
Version Française
Deutsche Fassung

Eurocode 3: Design of steel structures - Part 1-9: Fatigue

Eurocode 3: Calcul des structures en acier
- Partie 1-9: Fatigue

Eurocode 3: Bemessung und Konstruktion
von Stahlbauten - Teil 1-9: Ermüdung

This corrigendum becomes effective on 1 April 2009 for incorporation in the three official language versions of the EN.

Ce corrigendum prendra effet le 1 avril 2009 pour incorporation dans les trois versions linguistiques officielles de la EN.

Die Berichtigung tritt am 1. April 2009 zur Einarbeitung in die drei offiziellen Sprachfassungen der EN in Kraft.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2009 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.
Tous droits d'exploitation sous quelque forme et de quelque manière que ce soit réservés dans le monde entier aux membres nationaux du CEN.
Alle Rechte der Verwertung, gleich in welcher Form und in welchem Verfahren, sind weltweit den nationalen Mitgliedern von CEN vorbehalten.

Ref. No.:EN 1993-1-9:2005/AC:2009 D/E/F

Modifications due to EN 1993-1-9:2005/AC:2009

1) Modification to Clause 2

The corrections are to add a "P" after the clause number and replace "should" with "shall" where appropriate. The corrections are underlined as shown.

"

(1)P Structural members shall be designed for fatigue such that there is an acceptable level of probability that their performance will be satisfactory throughout their design life.

"

Modifications due to EN 1993-1-9:2005/AC:2009

2) Modification to Clause 3

Paragraph '(7)', list entry 'b)', change "the β – values equal to those for ultimate limit state verifications" into: "the β -values to be at least equal to those required for ultimate limit state verifications".

3) Modifications to Clause 4

Paragraph '(2)', change the text in the last sentence between the brackets "(see Table 4.1 for circular sections, Table 4.2 for rectangular sections)" into: "(see Table 4.1 for circular hollow sections, Table 4.2 for rectangular hollow sections; these sections are subject to the geometrical restrictions according to Table 8.7)".

Paragraph '(2)', 'Table 4.1' and 'Table 4.2', in the columns 'Verticals' for 'K-type joints', change "1,0" into: "-".

Paragraph '(2)', 'NOTE', change "NOTE" into: "NOTE 1".

Paragraph '(2)', add:

"

NOTE 2 Ranges of geometric validity:

For CHS planar joints (K-, N-, KT-joints):

$$0,30 \leq \beta \leq 0,60$$

$$12,0 \leq \gamma \leq 30,0$$

$$0,25 \leq \tau \leq 1,00$$

$$30^\circ \leq \theta \leq 60^\circ$$

For SHS joints (K-, N-, KT-joints):

$$0,40 \leq \beta \leq 0,60$$

$$6,25 \leq \gamma \leq 12,5$$

$$0,25 \leq \tau \leq 1,00$$

$$30^\circ \leq \theta \leq 60^\circ$$

"

4) Modification to Clause 5

Paragraph '(5)', 'NOTE', change reference to "8(2)" into: "8(3)".

5) Modification to 7.1

Paragraph '(2)', change "For constant amplitude nominal stresses fatigue strengths can" into: "For constant amplitude nominal stress ranges the fatigue strength can".

6) Modifications to Clause 8

Paragraph '(4)', 'NOTE 1', change "adopted for shear stress ranges" into: "adopted also for shear stress ranges".

'Table 8.1', second row [Detail category] 160', third column, change in this cell:

- the description "Rolled and extruded products:" into: "Rolled or extruded products:";
- the description "Plates and flats" into: "Plates and flats with as rolled edges";
- the description: "Rolled sections" into: "Rolled sections with as rolled edges".

'Table 8.1', fifth row [Detail category] 100 (m=5)', third column, change in this cell "Rolled and extruded products" into: "Rolled or extruded products".


'Table 8.2', third column 'Description', 2nd, 3rd, 4th, 5th, 11th and 12th rows [Detail categories] 125, 112, 100 and 140', change in the cells the description "Automatic" into: "Automatic or fully mechanized".

'Table 8.2', fourth column 'Requirements', 9th row, delete from the cell: "Free from defects outside the tolerances of EN 1090".

'Table 8.3', 2nd row, right-hand column, change in the cell "rewelded" into: "welded".

'Table 8.3 (continued)', last row, 1st column, change the text "As detail 1 in Table 8.5" into: "40".

'Table 8.3 (continued)', last row, 2nd column, delete the indication of the plate thickness: "t" from the following figure:



'Table 8.4', 8th, 9th and 10th rows, 3rd column in these rows, delete:

"

L: attachment length as in detail 1, 2 or 3

"

from the following figure:

90	$\frac{r}{L} \geq \frac{1}{3}$ or $r=150\text{mm}$	<p>L: attachment length as in detail 1, 2 or 3</p>
71	$\frac{1}{6} \leq \frac{r}{L} \leq \frac{1}{3}$	
50	$\frac{r}{L} < \frac{1}{6}$	

'Table 8.4', 8th, 9th and 10th rows, 2nd column in these rows (see just above), change in the second column " $\frac{r}{L}$ " into:

$$\frac{r}{\ell}$$

'Table 8.5', 11th row '36*', 3rd column, change:

3) Root failure in partial penetration Tee-butt joints or fillet welded joint and effective full penetration in Tee-butt joint.

into:

3) Root failure in partial penetration Tee-butt joints or fillet welded joint and in Tee-butt weld, according to Figure 4.6 in EN 1993-1-8:2005.







'Table 8.5', 2nd column, 2nd and 3rd rows:

Table 8.5: Load carrying welded joints

Detail category	Constructional detail		Description	Requirements
80	$\ell < 50\text{ mm}$	all t [mm]		Cruciform and Tee joints: 1) Toe failure in full penetration butt welds and all partial penetration joints.
71	$50 \leq \ell < 80$	all t		1) Inspected and found free from discontinuities and misalignments outside the tolerances of EN 1090. 2) For computing $\Delta\sigma$, use modified nominal stress.
63	$80 \leq \ell < 100$	all t		3) In partial penetration joints two fatigue assessments are required. Firstly, root cracking evaluated according to stresses defined in section 5, using category 36* for $\Delta\sigma_w$ and category 80 for $\Delta\sigma_u$. Secondly, toe cracking is evaluated by determining $\Delta\sigma$ in the load-carrying plate.
56	$100 \leq \ell < 120$	all t		
56	$\ell \geq 120$	$t \geq 20$		
50	$120 \leq \ell < 200$	$t \geq 20$		
45	$200 \leq \ell \leq 300$	$t \geq 30$		
40	$\ell > 300$	$t \geq 50$		
As detail 1 in Table 8.5	flexible panel			2) Toe failure from edge of attachment to plate, with stress peaks at weld ends due to local plate deformations. Details 1) to 3): The misalignment of the load-

as the figures in Table 8.5 as shown below should be made more clear as done in the German version, insert the same figures from the German version (see below):

"Tabelle 8.5: Geschweißte Stöße"

Kerfall	Konstruktionsdetail		Beschreibung	Anforderungen
80	$l \leq 50$	all t	  1)	Kreuz- und T-Stöße: 1) Riß am Schweißnahtübergang in voll durchgeschweißten Stumpfrahmen und allen nicht durchgeschweißten Nähten.
71	$50 < l \leq 80$	all t		
63	$80 < l \leq 100$	all t	  2)	2) ΔG ist mit korrigierten Nennspannungsschwingbreiten zu ermitteln. 3) Es sind 2 Ermüdungsnachweise erforderlich: zum einen der Nachweis gegen Riß der Schweißnahtwurzel mit Spannungen nach Kapitel 5 mit Kerbgruppe 36° für σ_{v} und Kerbgruppe 80 für τ_{w} , zum anderen der Nachweis des Nahtüberganges mit Bestimmung von ΔG in den belasteten Blechen.
56	$100 < l \leq 120$	all t		
56	$l > 120$	$t \geq 20$	  3)	3) Winkelstreif Riß hat nicht voll
50	$120 < l \leq 200$	$t > 20$		
	$l > 200$	$20 < t \leq 30$		
45	$200 < l \leq 300$	$t > 30$	  4)	4) Winkelstreif Riß hat nicht voll
40	$l > 300$	$t > 50$		
wie Kerfall 1 in Tabelle 8.5	 5)		  6)	6) Winkelstreif Riß hat nicht voll