

KIVISÜSI, KOKS JA PÕLEVKIVI
Lenduvate ainete määramine

Hard coal, coke and oil shale
Determination of volatile matter
(ISO 562:2010, modified)

EESTI STANDARDI EESSÕNA**NATIONAL FOREWORD**

See Eesti standard EVS-ISO 562:2018 „Kivisüsi, koks ja põlevkivi. Lenduvate ainete määramine“ sisaldab endast rahvusvahelise standardi ISO 562:2010 „Hard coal, coke and oil shale. Determination of volatile matter“ modifitseeritud ingliskeelset teksti.	This Estonian Standard EVS-ISO 562:2018 consists of the modified English text of the International Standard ISO 562:2010 „Hard coal, coke and oil shale. Determination of volatile matter“.
Ettepaneku rahvusvahelise standardi ümbertrüki meetodil ülevõtuks on esitanud EVS/TK 57, standardi avaldamist on korraldanud Eesti Standardikeskus.	Proposal to adopt the International Standard by reprint method has been presented by EVS/TK 57, the Estonian Standard has been published by the Estonian Centre for Standardisation.
Standard EVS-ISO 562:2018 on jõustunud sellekohase teate avaldamisega EVS Teataja 2018. aasta augustikuu numbris.	Standard EVS-ISO 562:2018 has been endorsed with a notification published in the August 2018 issue of the official bulletin of the Estonian Centre for Standardisation.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Käsitlusala

See rahvusvaheline standard käsitleb lenduvate ainete määramist kivisöes **[MOD]**, kooksis ja põlevkivis**[MOD]**. Seda ei kohaldata pruunsöele ja ligniitidele.

Selles standardis on tehtud järgmised muudatused:

Sellesse standardisse on sisse viidud täiendused, mis võimaldavad standardi alusel määrata lenduvate ainete sisaldust põlevkivis. Täiendused, mille algus ja lõpp on tähistatud märgisega **[MOD]** on sisse viidud järgmistesse jaotistesse:

- peatükk 1;
- peatükk 2;
- peatükk 8;
- peatükk 9;
- kirjandus.

Lisaks on täiendus ilma märgisteta viidud standardi pealkirja.

This document is a preview generated by EVS

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 73.040; 75.160.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact the Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

CONTENTS

Foreword	IV
Introduction.....	VI
1 Scope.....	3
2 Normative references.....	3
3 Principle.....	3
4 Reagents and materials.....	3
5 Apparatus.....	3
6 Preparation of the test sample.....	8
7 Procedure	8
8 Expression of results.....	8
9 Precision	9
10 Test report	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 562 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 562:1998), of which it constitutes a minor revision.

Introduction

In this International Standard the volatile matter is determined as the loss in mass, less that due to moisture, when coal or coke is heated out of contact with air under standardized conditions. The test is empirical and, in order to ensure reproducible results, it is essential that the rate of heating, the final temperature and the overall duration of the test be carefully controlled. It is also essential to exclude air from the coal or coke during heating to prevent oxidation. The fit of the crucible lid is, therefore, critical. The moisture content of the sample is determined at the same time as the volatile matter so that the appropriate correction can be made.

Mineral matter associated with the sample can also lose mass under the conditions of the test, the magnitude of the loss being dependent on both the nature and the quantity of the minerals present.

NOTE When applying this International Standard for classification purposes, to samples obtained directly from coal seams, it is required to give special care to the ash.

The apparatus and procedure are specified so that one or more determinations can be performed simultaneously in the furnace.

1 Scope

This International Standard specifies a method of determining the volatile matter of hard coal **[MOD]**, coke and oil shale**[MOD]**. It is not applicable to brown coals and lignites.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 687, *Solid mineral fuels — Coke — Determination of moisture in the general analysis test sample*

ISO 11722, *Solid mineral fuels — Hard coal — Determination of moisture in the general analysis test sample by drying in nitrogen*

[MOD] EVS-EN 15936, *Sludge, treated biowaste, soil and waste — Determination of total organic carbon (TOC) by dry combustion*

ISO 925, *Solid mineral fuels — Determination of carbonate carbon content — Gravimetric method*

GOST 7752, *Combustible shales. Method for the accelerated determination of carbon dioxide content of the carbonates* **[MOD]**

3 Principle

A portion of the sample is heated out of contact with air at 900 °C for 7 min. The percentage mass fraction of volatile matter is calculated from the loss in mass of the test portion after deducting the loss in mass due to moisture.

4 Reagents and materials

4.1 **Cyclohexane**, of recognized analytical grade.

5 Apparatus

5.1 **Furnace**, heated by electricity, in which a zone of uniform temperature of $900\text{ °C} \pm 5\text{ °C}$ can be maintained.

It may be of the stop-ended type or fitted at the back with a flue approximately 25 mm in diameter and 150 mm long (see Figure 1).

It is important for furnaces with flues that the furnace door seal well. The flue should not reach far out of the oven and should be fitted with a butterfly valve to restrict airflow through the furnace.

Its heat capacity shall be such that, with an initial temperature of 900 °C, the temperature is regained within 4 min after insertion of a cold stand and its crucibles. The temperature is measured with a thermocouple (5.2).

Normally, the furnace is designed specifically either for multiple determinations using a number of crucibles in one stand or for receiving one crucible and its stand. In the first case, the zone of uniform temperature shall be at least 160 mm × 100 mm; in the latter case, a zone with a diameter of 40 mm is sufficient.