Copper and copper alloys - Eddy current testing on the outer surface of rods, bars, hollow rods and wires for the detection of defects by encircling test coil



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

	keelset	This Estonian standard EVS-EN 17263:2019 consists of the English text of the European standard EN 17263:2019.		
Standard on jõustunud sellekohase avaldamisega EVS Teatajas	r	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.		
Euroopa standardimisorganisatsioonid on Euroopa standardi rahvuslikele liikr kättesaadavaks 03.07.2019.		Date of Availability of the European standard is 03.07.2019.		
Standard on kättesaadav Standardikeskusest.		The standard is available from the Estonian Centre for Standardisation.		

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

ICS 77.150.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD NORME EUROPÉENNE

EN 17263

EUROPÄISCHE NORM

July 2019

ICS 77.150.30

English Version

Copper and copper alloys - Eddy current testing on the outer surface of rods, bars, hollow rods and wires for the detection of defects by encircling test coil

Cuivre et alliages de cuivre - Contrôle par courants de Foucault de la surface externe des barres, des barres rectangulaires, des barres creuses et des fils pour la détection des défauts avec une bobine encerclante Kupfer und Kupferlegierungen - Wirbelstromprüfung an der Oberfläche von Stangen, Rechteckstangen, Hohlstangen und Drähten zur Messung von Fehlern mit umfassender Prüfspule

This European Standard was approved by CEN on 12 May 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

JOH	ents		Page
luran	ean foreword		2
-			
nu oc L			
2			
}			
ļ 5			
	•		
5 5.1			
5.1.1	Nominal frequency		6
5.1.2 5.2	Test coil		7 7
.2			
3	Accentance criteria		Ω
8.1	Detection of single local discontin	nuity by encircling coils systems	9 9
3.2	Detection of several local surface signal amplitudes as detection thi	effects by-encircling coils systems by using low reshold	9
)	Other methods		10
.0	Documentation		10
Biblio	graphy		11
			Ω,

European foreword

This document (EN 17263:2019) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2020, and conflicting national standards shall be withdrawn at the latest by January 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of She was a second of the second North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The eddy current testing (ET) described in this document has the objective of detecting defects located on or near the surface in copper and copper alloy rods, bars, hollow rods and wires in a non-destructive way.

The eddy current test referenced in this document is able to detect significant discontinuities of the short abrupt type (typical defects e.g. cracks, laps, fins, shells, rolled-in matter) by the differential method with encircling test coils. Inhomogeneities evenly extending longitudinally over a large area cannot always be detected with this method.

The purpose of this document is not to define a method of measuring the actual extent of the material inhomogeneities, as the signal amplitude is also depending of factors e.g. volume, form and position of the inhomogeneity.

. w. rts ma. For the tested rods, bars, hollow rods and wires with no inhomogeneities detected, no conclusions can be drawn as to the functionality of the parts made from these rods, bars, hollow rods and wires.

1 Scope

This document specifies a procedure for fully automatic eddy current testing with no operator involvement with an encircling test coil for detecting defects on the surface of copper and copper alloy rods, bars, hollow rods and wires with a minimum diameter or width across flats defined in the relevant product standards.

This test method can be continuous or discontinuous depending on the product.

The product size range and test acceptance level are defined in the relevant product standards.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 12718, Non-destructive testing — Eddy current testing — Vocabulary (ISO 12718)

EN ISO 9712, Non-destructive testing — Qualification and certification of NDT personnel (ISO 9712)

EN ISO 15549, Non-destructive testing — Eddy current testing — General principles (ISO 15549)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 12718 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

4 General requirements

The eddy current testing method with self-comparison mode using encircling test coils is employed. A suitable encircling test coil corresponding to the dimension of the rods, bars, hollow rods or wires to be tested is chosen. Since the distribution density of eddy currents decreases as the distance from the test coil increases, the amplitude of defect signals also decreases with increasing distance from the test coil. The mechanical arrangement shall be chosen in order that the material can pass through the test coil as concentrically and vibration-free as possible. The influence of the test speed on the signal amplitude shall be corrected by a suitable dynamic effect compensating unit. Signal evaluation is done automatically. All materials with signal amplitudes equal to or higher than the acceptance level set in accordance with 8.1 are to be considered defective.

Inline eddy-current testing before cutting to length would not be subject to end effect. During the test of individual rods an untested area occurs at both ends of the rods.

For the suppression of magnetic effects an additional constant field magnetization might be necessary.

If the evaluation operates by phase selection, the inhomogeneities to be detected shall lie within the evaluation range determined. It shall be taken into consideration that the phase depends on the type and position of the inhomogeneity.

Rods, bars, hollow rods and wires shall be sufficiently clean and straight to allow satisfactory operation of the drive mechanism and eddy current test equipment.