

INTERNATIONAL STANDARD

ISO
9852

First edition
1995-06-15

Unplasticized poly(vinyl chloride) (PVC-U) pipes — Dichloromethane resistance at specified temperature (DCMT) — Test method

*Tubes en poly(chlorure de vinyle) non plastifié (PVC-U) — Résistance au
dichlorométhane à une température spécifiée (DCMT) — Méthode d'essai*



Reference number
ISO 9852:1995(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9852 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This first edition of ISO 9852 cancels and replaces ISO 7676:1990, of which it constitutes a technical revision. The changes made to the method given in ISO 7676 are explained in the fourth paragraph of the introduction.

Annex A of this International Standard is for information only.

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

Studies carried out at international level show that the degree of gelation of converted PVC-U is one of the fundamental characteristics which determines the properties of pipes (matrix strength).

The method, using dichloromethane, proposed in this document enables the area of the tube whose degree of gelation is the lowest to be identified and estimated quantitatively. This is in contrast to other methods (test of elasticity at fusion or tensile test at temperatures in excess of 80 °C) which only give overall information.

The method also has the advantage of being capable of being carried out quickly during manufacture, thus enabling steps to be taken to correct any defects which have been identified.

The dichloromethane test which was specified in ISO 7676:1990, *Unplasticized poly(vinyl chloride) (PVC-U) pipes — Dichloromethane test* (see the foreword), is modified in the following way: the pipe, chamfered at one end so that the complete cross-section of the pipe is in contact with the fluid, is immersed in dichloromethane for a period of 30 min, then successively in baths whose temperature varies by increments of 5 °C, for example.

Under these conditions, the degree of gelation corresponds to the temperature at which attack of the PVC-U first occurs.

A study of a large number of samples with different degrees of gelation has established that attack can occur at temperatures over the range – 20 °C to + 30 °C. The results of these tests prove that the degree of gelation is defined by the highest temperature at which no attack of the PVC-U occurs.

In fact, the experimental results demonstrate that the correlation between the degree of gelation, as defined by the temperature, and the performance of the pipes with time is confirmed up to a level of approximately 10 °C to 15 °C.

Above these temperatures, the scatter increases and the curves tend to level off as parameters other than gelation influence the matrix strength.

In practice, it is sufficient to check that the gelation is greater than a minimum specified level. For this purpose, test pieces are immersed in dichloromethane at a specified temperature for 30 min. The test pieces are acceptable if there is no attack of the PVC-U.

This document is a preview generated by EVS

This page intentionally left blank

Unplasticized poly(vinyl chloride) (PVC-U) pipes — Dichloromethane resistance at specified temperature (DCMT) — Test method

1 Scope

This international Standard specifies a method for determining the resistance of unplasticized PVC pipes to dichloromethane at a specified temperature (DCMT).

The method can be used for any homogeneous plain-walled unplasticized-PVC pipes, irrespective of their intended application. It can be used as a rapid means of quality control during manufacture.

2 Principle

A piece of PVC-U pipe of specified length, chamfered at one end to an angle dependent on its thickness, is immersed for a fixed period of time in a thermo-controlled dichloromethane bath in order to verify that the PVC-U is not attacked at the temperature θ specified in the product standard.

The test pieces are dried in air and then examined to determine whether the PVC has been attacked or not.

NOTES

- 1 If the PVC has not been sufficiently gelled, whitening of the surface will occur and, in the worst case, a powdery precipitate will be produced.
- 2 The maximum temperature at which the PVC-U is not attacked gives an indication of the degree and homogeneity of gelation of the PVC-U of which the pipe is made. This characteristic is related to the mechanical properties, and in particular the long-term pressure resistance, of the pipe.
- 3 The minimum permitted bath temperature at which attack by the dichloromethane shall not take place is specified.

3 Reagent

3.1 Dichloromethane, analytical grade.

WARNING — Dichloromethane can be toxic by absorption through the skin and eyes. It is therefore necessary to take precautions when handling liquid dichloromethane or test pieces which have been immersed in it. Furthermore, the boiling point of dichloromethane is low (40 °C). Consequently, it has a high vapour pressure at ambient temperatures. The vapour is also toxic, the threshold limit value corresponding to the maximum admissible concentration being 500 ml/m³ (ppm). Ventilation of the room or area in which the container is kept and where the test pieces are dried is therefore essential.

4 Apparatus

4.1 Chamfering machine.

4.2 Glass or stainless-steel container, of suitable dimensions to accommodate one or more test pieces under the specified conditions (see 7.4). A mark on the inside surface to indicate a suitable dichloromethane level is useful.

4.3 Grating, fitted so that it is approximately 1 cm above the bottom of the container.

4.4 Lid, to limit evaporation of the dichloromethane.

4.5 Thermostat, to maintain the temperature of the dichloromethane at θ °C \pm 0,5 °C (see clause 2).