

INTERNATIONAL
STANDARD

ISO
10058

First edition
1992-06-15

Magnesites and dolomites — Chemical analysis

Produits de magnésie et de dolomie — Analyse chimique



Reference number
ISO 10058:1992(E)

Contents

	Page
1 Scope	1
2 Dissolution and determination of silica	1
3 Determination of alumina	4
4 Determination of total iron calculated as iron(III) oxide	6
5 Determination of titanium(IV) oxide	7
6 Determination of manganese(IV) oxide	9
7 Determination of chromium(III) oxide	10
8 Determination of calcium oxide	12
9 Determination of magnesium oxide	13
10 Determination of potassium, sodium and lithium oxides	15
11 Determination of the loss on ignition	16
12 Test report	16

Annex

A Determination of boron content of magnesites	17
--	----

© ISO 1992

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10058 was prepared by Technical Committee ISO/TC 33, *Refractories*, Sub-Committee SC 2, *Methods of testing*.

Annex A forms an integral part of this International Standard.

This document is a preview generated by EVS

This page intentionally left blank

Magnesites and dolomites — Chemical analysis

1 Scope

This International Standard specifies methods for the determination of silica, alumina, titania, iron oxide and oxides of manganese, chromium, calcium, magnesium, sodium, potassium and lithium. It also specifies methods for determining the loss on ignition of magnesite and dolomite, and of refractories based on these raw materials.

Annex A describes a method for the determination of the boron content of magnesites only.

NOTE 1 Physical methods are used increasingly for chemical analysis. At present, it is not possible to describe a standardized test method, because the type of apparatus used is important.

2 Dissolution and determination of silica

2.1 Principle

Decompose the sample with hydrochloric acid and separate the silica by coagulation with a polyethylene oxide solution. Filter, wash the residue, heat and weigh it, and submit it to a treatment with hydrofluoric and sulfuric acids. After this treatment, weigh the remaining residue again and fuse it in sodium carbonate and boric acid. It is then dissolved in the filtrate from the silica, and the solution is diluted to a standard volume to obtain the stock solution (A) of the sample.

In an aliquot, the small quantity of silica not separated by coagulation is subsequently determined by a spectrophotometric method based on the formation of molybdenum blue, using alternatively iron(II) sulfate or tin(II) chloride as a reducing agent. The absorbance maximum of the reduced silicomolybdate complex lies at a wavelength of 810 nm.

2.2 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

2.2.1 Sodium carbonate, anhydrous.

2.2.2 Boric acid, powdered.

2.2.3 Polyethylene oxide solution, 2,5 g/l.

Add 0,5 g of polyethylene oxide to 200 ml of water while stirring slowly, preferably with a mechanical stirrer, until dissolved. Discard after 2 weeks.

2.2.4 Accelerator granules, ashless, of mass about 1 g.

2.2.5 Hydrochloric acid, concentrated, $\rho = 1,19$ g/ml.

2.2.6 Hydrochloric acid, diluted 1 + 19.

Add 1 volume of hydrochloric acid (2.2.5) to 19 volumes of water.

2.2.7 Sulfuric acid, concentrated, $\rho = 1,84$ g/ml.

2.2.8 Hydrofluoric acid, 40 % (m/m).

2.3 Apparatus

Usual laboratory apparatus and the following.

2.3.1 Sand bath or hot plate.

2.3.2 Muffle furnace, capable of being controlled at 1 180 °C to 1 200 °C.

2.3.3 Platinum crucible.