INTERNATIONAL STANDARD

ISO 10312

First edition 1995-05-01

Ambient air — Determination of asbestos fibres — Direct-transfer transmission electron microscopy method

Air ambiant — Détermination des fibres d'amiante — Méthode de microscopie électronique à transmission directe



Contents

| | | Page |
|---------|--|------|
| 1 | Scope | . 1 |
| 2 | Normative references | . 2 |
| 3 | Definitions | . 2 |
| 4 | Principle | . 3 |
| 5 | Symbols of units and abareviations | . 4 |
| 6 | Reagents | . 5 |
| 7 | Apparatus | . 5 |
| 8 | Air sample collection | 10 |
| 9 | Procedure for analysis | 11 |
| 10 | Performance characteristics | 18 |
| 11 | Test report | 19 |
| Annexes | | |
| Α | Determination of operating conditions for plasma and the second s | 22 |
| в | Calibration procedures | 23 |
| С | Structure counting criteria | 25 |
| D | Fibre identification procedure | 33 |
| Е | Determination of the concentrations of asbestos fibres and bunc longer than 5 µm, and PCM equivalent asbestos fibres | |
| F | Calculation of results | 43 |
| G | Strategies for collection of air samples | 47 |
| н | Methods for removal of gypsum fibres | 48 2 |
| J | Bibliography | 49 |
| | | |

© ISO 1995

Printed in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization Case Postale 56 • CH-1211 Genève 20 • Switzerland

ISO (the inc. federation of nation... of preparing International ... which a technical committee has been. represented on that committee . International O... and non-governmental, in liaison with ISO, also take pro-collaborates closely with the International Electrotech IEC) on all matters of electrotechnical standardization. Draft International Standards adopted by the technic requires approval by at least 75 % of the mer "requires approval by at least 75 % of the mer "the SC 3, Ambie "the acc 3, Ambie ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission

Draft International Standards adopted by the technical committees are cito lated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10312 was prepared by Technical Committee ISO/TC 140 Air quality, Subcommittee SC 3, Ambient atmospheres.

Annexes A, B, C, D, E and F form an integral part of this International Standard. Annexes G, H and J are for information only.

Generated by FLS

Introduction

This International Standard Sapplicable to the determination of airborne asbestos in a wide range of ambient air situations, including the interior atmospheres of buildings, and for detailed evaluation of any atmosphere in which asbestos structures are fixely to be present. Because the best available medical evidence indicates that the numerical fibre concentration and the fibre sizes are the relevant parameters for evaluation of the inhalation hazards, a fibre counting technique is the only logical approach. Most fibres in ambient atmospheres are repaisbestos, and therefore there is a requirement for fibres to be identified. Wany airborne asbestos fibres in ambient atmospheres have diameters below the resolution limit of the optical microscope. This International Standard is based on transmission electron microscopy, which has adequate resolution to allow detection of small fibres and is currently the only technique capable of unequivocal identification of the majority of individual fibres of asbestos. Asbestos is often found, not as single fibres, but as very complex aggregated structures which may or may not be also aggregated with other particles. The fibres found suspended in an ambient atmosphere can often be identified unequivocally, if a sufficient measurement effort is expended. However, if each fibre were to be identified in this way, the analysis would become prohibitively expensive. Because of instrumental deficiencies of because of the nature of the particulate, some fibres cannot be positively identified as asbestos, even though the measurements all indicate that the could be asbestos. Subjective factors therefore contribute to this measurement, and consequently a very precise definition of the procedure for identific tion and enumeration of asbestos fibres is required. The method specifical sted by FLS in this International Standard is designed to provide the best description possible of the nature, numerical concentration, and sizes of asbestoscontaining particles found in an air sample. This International Standard is necessarily complex, because the instrumental techniques used are complex, and also because a very detailed and logical procedure must be specified to reduce the subjective aspects of the measurement. The method of data recording specified in this International Standard is designed to allow re-evaluation of the structure counting data as new medical evidence becomes available. All of the feasible specimen preparation techniques result in some modification of the airborne particulate. Even the collection of particles from a three-dimensional airborne dispersion onto a two-dimensional filter surface can be considered a modification of the particulate, and some of the particles in most samples are modified by the specimen preparation procedures. However, the procedures specified in this International Standard are designed to minimize the disturbance of the collected particulate material, and the effect of those disturbances which do occur can be evaluated.

This International Standard describes the method of analysis for a single air filter. However, one of the largest potential errors in characterizing asbestos in ambient atmospheres is associated with the variability between filter samples. For this reason, it is necessary to design a replicate sampling scheme in order to determine this International Standard's accuracy and precision. Ambient air — Determination of asbestos fibres — **Direct-transfer transmission electron microscopy** This document , method

Scope

1.1 Substance determined

This International Standard specifies aneference method using transmission electron microscopy for the determination of the concentration of asbestos structures in ambient atmospheres and includes measurement of the lengths, widths and aspect ratio of the asbestos structures. The method allows dete mination of the type(s) of asbestos fibres present. The method cannot discriminate between individual fibres of the asbestos and non-asbestos analogues of the same amphibole mineral.

1.2 Type of sample

The method is defined for polycarbonate capillary-pore filters or cellulose ester (either mixed esters of cellulose or cellulose nitrate) filters through which a known volume of air has been drawn. The method is suitable for determination of asbestos in both exterior and building atmospheres.

1.3 Measuring range

The range of concentration which can be determined is 50 structures/mm² to 7 000 structures/mm² on the filter. The air concentrations represented by these values are a function of the volume of air sampled. There is no lower limit to the dimensions of asbestos fibres which can be detected. In practice, microscopists vary in their ability to detect very small asbestos fibres. Therefore, a minimum length of 0,5 µm has been defined as the shortest fibre to be incorporated in the reported results.

1.4 Limit of detection

The limit of detection theoretically can be lowered indefinitely by filtration of progressively larger volumes of air and by extending the examination of the specimens in the electron microscope. In practice, the lowest achievable limit of detection for a particular area of TEM specimen examined is controlled by the total suspended particulate concentration.

For total suspended particulate concentrations of approximately 10 μg/m³, corresponding to clean, rural atmospheres, and assuming filtration of 4 000 litres of air, an analytical sensitivity of 0,5 structure/l can be obtained, equivalent to a limit of detection of 1,8 structure/l, if an area of 0,195 mm² of the TEM specifies is examined. If higher total suspended particulate operations are present, the volume of air filtered must be reduced in order to maintain an acceptable particulate loading on the filter, leading to a proportionate increase in the analytical sensitivity.

() Where this is the case, lower limits of detection can be achieved by increasing the area of the TEM specimens that is examined. In order to achieve lower limits of detection for fibres and bundles longer than 5 μ m, and for PCM equivalent fibres, lower magnifications are specified which permit more rapid examination of larger areas of the TEM specimens when the examination is limited to these dimensions of fibre. The direct analytical method cannot be used if the general particulate loading of the sample collection filter exceeds approximately 10 µg/cm² of filter surface, which corresponds to approximately 10 % coverage of the collection filter by particulate. If the total suspended particulate is largely organic material, the limit of detection can be lowered significantly by using an indirect preparation method.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 4225:1994, Air quality General aspects — Vocabulary.

ISO 4226:1993, Air quality — General aspects – Units of measurement.

ISO Standard Handbook No. 2:1993, Oraptities and units.

ISO Standard Handbook No. 3:1989, Statistical Methods.

3 Definitions

For the purposes of this International Standard, the following definitions apply (see also ISO 4225).

3.1 acicular: The shape of an extremely slender crystal with cross-sectional dimensions which are small relative to its length, i.e. needle-like.

3.2 amphibole: A group of rock-forming ferromagnesium silicate minerals, closely related in crystal form and composition, with the nominal formula:

where

In some varieties of amphibole, these elements can be partially substituted by Li, Pb or Zn. Amphibole is characterized by a cross-linked double chain of Si-O tetrahedra with a silicon:oxygen ratio of 4:11, by columnar or fibrous prismatic crystals and by good prismatic cleavage in two directions parallel to the crystal faces and intersecting at angles of about 56° and 124°.

3.3 amphibole asbestos: Amphibole in an asbestiform habit.

3.4 analytical sensitivity: The calculated airborne asbestos structure concentration in asbestos structures/litre, equivalent to counting of one asbestos structure in the analysis. The method in this International Standard does not specify an analytical sensitivity.

3.5 asbestiform: A specific type of mineral fibrosity in which the fibres and fibrils possess high tensile strength and flexibility.

3.6 asbestos: A term applied to a group of silicate minerals belonging to the serpentine and amphibole groups which have crystallized in the asbestiform habit, causing them to be easily separated into long. thin, strong fibres when crushed or processed. The Chemical Abstracts Service Registry Numbers of the most common asbestos varieties are: chrysotile (12001 - 29 - 5),crocidolite (12001-28-4), grünerite asbestos (amosite) (12172-73-5), anthophyllite asbestos (77536-67-5),tremolite asbestos (77536-68-6) and actinolite asbestos (77536-66-4).

asbestos structure: A term applied to any connected or overlapping grouping of asbestos fibres or bundes, with or without other particles.

3.8 aspect ratio: The ratio of length to width of a particle.

3.9 blank: A structure count made on TEM specimens prepared from an unused filter, to determine the background measurement.

3.10 camera length: The equivalent projection length between the specimen and its electron diffraction pattern, in the absence of lens action.

3.11 chrysotile: A fibrous mineral of the serpentine group which has the nominal composition

Most natural chrysotile deviates little from this nominal composition. In some varieties of chrysotile, minor substitution of silicon by Al^{3+} may occur. Minor substitution of magnesium by Al^{3+} , Fe^{2+} , Fe^{3+} , Ni^{2+} , Mn^{2+} and Co^{2+} may also be present. Chrysotile is the most prevalent type of asbestos.

3.12 cleavage: The breaking of a mineral along one of its crystallographic directions.