

Plastics - Preparation of test specimens by machining
(ISO 2818:2018)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 2818:2019 sisaldab Euroopa standardi EN ISO 2818:2019 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 2818:2019 consists of the English text of the European standard EN ISO 2818:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 09.01.2019.	Date of Availability of the European standard is 09.01.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Plastics - Preparation of test specimens by machining (ISO
2818:2018)

Plastiques - Préparation des éprouvettes par usinage
(ISO 2818:2018)

Kunststoffe - Herstellung von Probekörpern durch
mechanische Bearbeitung (ISO 2818:2018)

This European Standard was approved by CEN on 24 December 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 2818:2019) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2019, and conflicting national standards shall be withdrawn at the latest by July 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 2818:1996.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 2818:2018 has been approved by CEN as EN ISO 2818:2019 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test specimens	5
4.1 Shape and state of the test specimens.....	5
4.2 Preparation of test specimens.....	6
5 Machinery and tools	6
5.1 General.....	6
5.2 Milling cutters.....	6
5.3 Slicing or sawing machines.....	6
5.4 Tubular cutting machines.....	6
5.5 Lathes.....	7
5.6 Planing machines.....	7
5.7 Stamping tools.....	7
5.8 Broaching tools.....	7
6 Procedure	7
6.1 General.....	7
6.2 Preparation of dumb-bell specimens.....	7
6.3 Preparation of rectangular test specimens by sawing or cutting with an abrasive disc.....	7
6.4 Preparation of disc-shaped test specimens.....	7
6.5 Stamping out test specimens of any shape.....	8
6.6 Notching finished test specimens by milling or broaching.....	8
7 Test report	9
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Mechanical properties*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This fourth edition cancels and replaces the third edition (ISO 2818:1994), of which it constitutes a minor revision to update the references in [Clause 2](#). It also incorporates the Technical Corrigendum ISO 2818:1994/Cor 1:2007.

Introduction

The preparation of test specimens by machining influences the finished surfaces and, in some cases, even the internal structure of the specimens. Since test results are strongly dependent on both of these parameters, exact definitions of tools and machining conditions are required for reproducible test results with machined specimens.

Plastics — Preparation of test specimens by machining

1 Scope

This document establishes the general principles and procedures to be followed when machining and notching test specimens from compression-moulded and injection-moulded plastics, extruded sheets, plates and partially finished or wholly finished products.

In order to establish a basis for reproducible machining and notching conditions, the following general standardized conditions are applied. It is assumed, however, that the exact procedures used are selected or specified by the relevant material specification or by the standards on the particular test methods. If sufficiently detailed procedures are not thus specified, the interested parties agree upon the conditions to be used.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 Milling

NOTE In this machining operation, the tool has a circular primary motion and the workpiece a suitable feed motion. The axis of rotation of the primary motion retains its position with respect to the tool, independently of the feed motion (see ISO 3855). Complete dumb-bell and rectangular test specimens, as well as notches in finished specimens, may be prepared by milling.

3.1.1 Geometry (see ISO 3002-1 and [Figure 1](#))

NOTE Only a few details of the exact geometrical conditions of the milling tool and its position with respect to the workpiece given in ISO 3002-1 are relevant to this document.

3.1.1.1 tool-cutting-edge angle

α_r

angle between the tool-cutting-edge plane, P_s , and the assumed working plane, P_f , measured in the tool back plane, P_r

3.1.1.2 tool back clearance

α_p

angle between the flank, A_α , of the cutter and the tool-cutting-edge plane, P_s , measured in the tool back plane, P_p