

**Superconductivity - Part 13: AC loss measurements -
Magnetometer methods for hysteresis loss in
superconducting multifilamentary composites**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 61788-13:2012 sisaldab Euroopa standardi EN 61788-13:2012 ingliskeelset teksti.	This Estonian standard EVS-EN 61788-13:2012 consists of the English text of the European standard EN 61788-13:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.10.2012.	Date of Availability of the European standard is 05.10.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 17.220, 29.050

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English version

**Superconductivity -
Part 13: AC loss measurements -
Magnetometer methods for hysteresis loss in superconducting
multifilamentary composites
(IEC 61788-13:2012)**

Supraconductivité -
Partie 13: Mesure des pertes
en courant alternatif -
Méthodes de mesure par magnétomètre
des pertes par hystérésis dans les
composites multifilamentaires
supraconducteurs
(CEI 61788-13:2012)

Supraleitfähigkeit -
Teil 13: Messung der
Wechselstromverluste -
Magnetometerverfahren zur Messung
der Hystereseverluste von supraleitenden
Multifilament-Verbundleitern
(IEC 61788-13:2012)

This European Standard was approved by CENELEC on 2012-08-29. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of document 90/302/FDIS, future edition 2 of IEC 61788-13, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 61788-13:2012.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2013-05-29
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2015-08-29

This document supersedes EN 61788-13:2003.

EN 61788-13:2012 includes the following significant technical changes with respect to EN 61788-13:2003:

- to extend to the measurement of superconductors in general, in various sample sizes and shapes, and at temperatures other than 4,2 K;
- to use the word "uncertainty" for all quantitative (associated with a number) statistical expressions and eliminate the quantitative use of "precision" and "accuracy" in accordance with the decision at the June 2006 IEC/TC 90 meeting in Kyoto.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 61788-13:2012 was approved by CENELEC as a European Standard without any modification.

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050	Series	International Electrotechnical Vocabulary (IEV)	-	-
IEC 61788-5	-	Superconductivity - Part 5: Matrix to superconductor volume ratio measurement - Copper to superconductor volume ratio of Cu/Nb-Ti composite superconductors	EN 61788-5	-

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 General specifications	8
4.1 Target uncertainty	8
4.2 Uncertainty and uniformity of the applied field	8
4.3 VSM calibration	8
4.4 Temperature.....	9
4.5 Specimen length.....	9
4.6 Specimen orientation and demagnetization effects	9
4.7 Normalization volume.....	9
4.8 Mode of field cycling or sweeping	9
5 The VSM method of measurement.....	10
5.1 General.....	10
5.2 VSM measurement principle.....	10
5.3 VSM specimen preparation.....	10
5.4 VSM measurement conditions and calibration	12
5.4.1 Field amplitude	12
5.4.2 Direction of applied field	12
5.4.3 Rate of change of the applied field (sweep rate)	12
5.4.4 Waveform of the field change	12
5.4.5 Specimen size and shape correction.....	12
5.4.6 Allowance for addendum (background subtraction)	13
5.4.7 Data point density.....	13
6 Test report.....	13
6.1 General.....	13
6.2 Initiation of the test.....	13
6.3 Technical details	13
Annex A (informative) The SQUID method of measurement	15
Annex B (normative) Extension of the standard to the measurement of superconductors in general	16
Annex C (informative) Uncertainty considerations	18
Bibliography.....	23
Figure 1 – A typical experimental setup of VSM measurement	11
Figure 2 – Three alternative specimen configurations for the VSM measurement	11
Table C.1 – Output signals from two nominally identical extensometers	19
Table C.2 – Mean values of two output signals	19
Table C.3 – Experimental standard deviations of two output signals	19
Table C.4 – Standard uncertainties of two output signals	20
Table C.5 – Coefficient of variations of two output signals	20

INTRODUCTION

IEC Technical Committee 90 proposes magnetometer and pickup coil methods for measuring the AC losses of Cu/Nb-Ti composite superconducting wires in transverse time-varying magnetic fields. These represent initial steps in standardization of methods for measuring the various contributions to AC loss in transverse fields, the most frequently encountered configuration.

It was decided to split the initial proposal mentioned above into two documents covering two standard methods. One of them describes the magnetometer method for hysteresis loss and low frequency (or sweep rate) total AC loss measurement in a slowly varying magnetic field, and the other describes the pickup coil method for total AC loss measurement in higher frequency (or sweep rate) magnetic fields. The frequency range is 0 Hz – 0,06 Hz for the magnetometer method and 0,005 Hz – 60 Hz for the pickup-coil method. The overlap between 0,005 Hz and 0,06 Hz is a complementary frequency range for the two methods.

This standard deals with the magnetometer method.

SUPERCONDUCTIVITY –

Part 13: AC loss measurements – Magnetometer methods for hysteresis loss in superconducting multifilamentary composites

1 Scope

This part of IEC 61788 describes considerations for the measurement of hysteretic loss in Cu/Nb-Ti multifilamentary composites using DC- or low-ramp-rate magnetometry. This international standard specifies a method of the measurement of hysteretic loss in multifilamentary Cu/Nb-Ti composite conductors. Measurements are assumed to be on round wires with temperatures at or near 4,2 K. DC or low-ramp-rate magnetometry will be performed using either a superconducting quantum interference device (SQUID magnetometer, See Annex A.) or a vibrating-sample magnetometer (VSM). In case differences between the calibrated magnetometer results are noted, the VSM results, extrapolated to zero ramp rate, will be taken as definitive. Extension to the measurement of superconductors in general is given in Annex B.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050 (all parts), *International Electrotechnical Vocabulary* (available at <http://www.electropedia.org>)

IEC 61788-5, *Superconductivity – Part 5: Matrix to superconductor volume ratio measurement – Copper to superconductor volume ratio of Cu/Nb-Ti composite superconductors*

3 Terms and definitions

For the purposes of this part of IEC 61788, the terms and definitions given in IEC 60050-815, together with the following terms and definitions, apply.

3.1

AC loss

P

power dissipated in a composite superconductor due to application of a time-varying magnetic field or electric current

Note 1 to entry: The AC loss per magnetic field cycle is designated *Q*. Although all such loss is inevitably "hysteretic" in the general sense, the AC loss in a superconducting composite is assumed to be separable into "hysteresis-", "eddy-current-", and "coupling-" loss components, as defined below (see Note 1 and Note 2 of IEC 60050-815:2000, 815-04-54).

[SOURCE: IEC 60050-815:2000, 815-04-54, modified – The original two notes have been replaced by a new note to entry.]