

Plastics - Thermoplastic covering films for use in
agriculture and horticulture

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13206:2017+A1:2020 sisaldab Euroopa standardi EN 13206:2017+A1:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 13206:2017+A1:2020 consists of the English text of the European standard EN 13206:2017+A1:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 22.01.2020.	Date of Availability of the European standard is 22.01.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 65.040.30, 83.140.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Plastics - Thermoplastic covering films for use in agriculture and horticulture

Plastiques - Films de couverture thermoplastiques
pour utilisation en agriculture et horticulture

Kunststoffe - Thermoplastische Abdeckfolien für den
Einsatz in der Landwirtschaft und im Gartenbau

This European Standard was approved by CEN on 14 November 2016 and includes Amendment 1 approved by CEN on 11 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	4
1 Scope	5
2 Normative references.....	5
3 Terms and definitions.....	6
4 Types and use.....	7
5 Material	8
6 Durability.....	8
7 Requirements.....	9
7.1 General requirements.....	9
7.2 Requirement for appearance	11
8 Test methods	12
8.1 Determination of thickness.....	12
8.2 Determination of width	12
8.3 Determination of tensile characteristics	12
8.4 Determination of impact resistance	12
8.5 Determination of elongation under a steady load (creep test).....	13
8.6 Determination of visible light transmission	15
8.7 Determination of haze	15
8.8 Determination of IR effectiveness (η_{ir}) (thermal clear and thermal diffusing films)	15
8.9 Determination of resistance to weathering	16
8.10 Determination of the chlorine content of used films.....	17
8.11 Determination of the sulfur content of used films.....	17
8.12 Determination of the roll/sheet length	17
9 Film acceptance, storage and handling.....	18
9.1 Acceptance	18
9.2 Storage and handling of rolls.....	18
10 Designation	18
11 Marking	19
12 Instructions for installation, use of covering films.....	19
13 Instructions for disposal and end-of-life of covering films	19
Annex A (informative) Exposure to other light sources.....	20
Annex B (informative) Empirical correlation between durations of covering films exposed to artificial weathering and a natural exposure.....	24
Annex C (normative) Determination of the chlorine content by coulometry	27
Annex D (normative) Determination of the sulfur content by ICP- OES technique.....	31
Annex E (informative) Alternative method for the determination of chlorine and sulfur contents by X-ray fluorescence.....	35
Annex F (informative) Alternative methods for the determination of sulfur content by ultraviolet fluorescence method or by coulometry	37

Annex G (informative) Guidance for installation, use and disposal of covering films.....	42
Annex H (informative) Industrial standard formats of films.....	50
Bibliography	51

This document is a preview generated by EVS

European foreword

This document (EN 13206:2017+A1:2020) has been prepared by Technical Committee CEN/TC 249 “Plastics”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2020 and conflicting national standards shall be withdrawn at the latest by July 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 11 November 2019.

This document supersedes A1 EN 13206:2017 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

The following technical changes have been made in comparison to EN 13206:2001:

- a minimum thickness of the film is fixed;
- the test methods have been updated as appropriate;
- this revision specifies also test methods for the determination of the chlorine and sulfur contents of the films subjected to use and defines guidelines for installation, use and disposal;
- the classification for the durability of the covering films is extended to a further class.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies the requirements related to dimensional, mechanical, optical and thermal characteristics of thermoplastic films used for covering permanent or temporary greenhouses and walking tunnels and low tunnels used for forcing and semi-forcing vegetable, fruit and flower crops.

Lay-flat perforated cover films are also in the scope of this European Standard.

It specifies a classification for the durability of covering films and the test methods referred to in this standard.

This European Standard specifies also test methods for the determination of the chlorine and sulfur contents of films subjected to use.

This European Standard is applicable to thermoplastic covering films used in agriculture and horticulture in Europe, in the thickness range 20 µm up to more than 250 µm, based on polyethylene and/or ethylene copolymers materials, of the following types: non-thermal films, thermal clear films and thermal diffusing films.

This European Standard also defines guidance for installation, use and disposal of covering films. It defines the conventional expected lifetime, as well as rules that allow evaluating the remaining use potential in the event of a failure before the normal end-of-use date.

NOTE These rules allow estimating the residual value of the films. These provisions only apply to the film itself and the damage it has undergone. Any other problem falls within the scope of professional practices and the general terms and conditions of sale.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10244-2, *Steel wire and wire products - Non-ferrous metallic coatings on steel wire - Part 2: Zinc or zinc alloy coatings*

EN 13031-1, *Greenhouses - Design and construction - Part 1: Commercial production greenhouses*

EN 16472, *Plastics - Method for artificial accelerated photoageing using medium pressure mercury vapour lamps*

EN ISO 527-1, *Plastics - Determination of tensile properties - Part 1: General principles (ISO 527-1)*

EN ISO 527-3, *Plastics - Determination of tensile properties - Part 3: Test conditions for films and sheets (ISO 527-3)*

EN ISO 4892-1, *Plastics - Methods of exposure to laboratory light sources - Part 1: General guidance (ISO 4892-1)*

EN ISO 4892-2:2013, *Plastics - Methods of exposure to laboratory light sources - Part 2: Xenon-arc lamps (ISO 4892-2:2013)*

EN ISO 4892-3:2016, *Plastics - Methods of exposure to laboratory light sources - Part 3: Fluorescent UV lamps (ISO 4892-3)*

EN ISO 7765-1:2004, *Plastics film and sheeting - Determination of impact resistance by the free-falling dart method - Part 1: Staircase methods (ISO 7765-1:1988)*

ISO 4591, *Plastics - Film and sheeting - Determination of average thickness of a sample, and average thickness and yield of a roll, by gravimetric techniques (gravimetric thickness)*

ISO 4592, *Plastics - Film and sheeting - Determination of length and width*

ISO 4593, *Plastics - Film and sheeting - Determination of thickness by mechanical scanning*

ASTM D 1003-13, *Standard Test Method for Haze and Luminous Transmittance of Transparent Plastics*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

width

overall width of a film when laid flat

Note 1 to entry: It is expressed in millimetres.

3.2

nominal width

width of a film, as declared by the manufacturer/supplier

Note 1 to entry: It is expressed in millimetres.

3.3

nominal thickness

thickness of a film, as declared by the manufacturer/supplier

Note 1 to entry: It is expressed in micrometres (μm).

3.4

roll length

largest dimension of the film corresponding to the length of the unwinded roll

Note 1 to entry: It is expressed in metres.

3.5

nominal length

length of a film roll or sheet, as declared by the manufacturer/supplier

Note 1 to entry: It is expressed in metres.

3.6

nominal mass

mass of a roll or sheet, as declared by the manufacturer/supplier

Note 1 to entry: It is expressed in kilograms.