

Thermal resistant aluminium alloy wire for overhead line conductor

This document is a preview generated by EVS

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 62004:2009 sisaldab Euroopa standardi EN 62004:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.07.2009 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 24.06.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 62004:2009 consists of the English text of the European standard EN 62004:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.07.2009 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 24.06.2009.

The standard is available from Estonian standardisation organisation.

ICS 17.220.20, 29.240.20

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: +372 605 5050; E-mail: info@evs.ee

**Thermal-resistant aluminium alloy wire
for overhead line conductor
(IEC 62004:2007, modified)**

Fils en alliage d'aluminium
résistant à la chaleur
pour les conducteurs de lignes aériennes
(CEI 62004:2007, modifiée)

Wärmebeständige Drähte
aus Aluminiumlegierung
für Leiter von Freileitungen
(IEC 62004:2007, modifiziert)

This European Standard was approved by CENELEC on 2009-05-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of the International Standard IEC 62004:2007, prepared by IEC TC 7, Overhead electrical conductors, together with common modifications prepared by CENELEC BTTF 129-1, Thermal-resistant aluminium alloy wire for overhead line conductor, was submitted to the formal vote and was approved by CENELEC as EN 62004 on 2009-05-01.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2010-05-01
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2012-05-01

This European Standard is a consolidated version consisting of the text of the International Standard IEC 62004:2007 plus the agreed common modifications, which are identified by a vertical line in the left margin of the text.

Contents

1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Designation.....	4
5	Values for thermal-resistant aluminium alloy wire	5
6	Requirement	5
6.1	Material.....	5
6.2	Freedom from defects	5
6.3	Diameter and tolerance on diameter	5
6.4	Tensile stress.....	6
6.5	Elongation	6
6.6	Electrical resistivity	7
6.7	Thermal-resistant property	7
6.8	Length and tolerance on length	7
6.9	Joints	7
6.10	Wrapping.....	7
6.11	Sampling	8
7	Tests	8
7.1	Place of testing	8
7.2	Classification of tests	8
7.3	Test method	9
8	Acceptance and rejection.....	10
	Annex A (informative) Thermal-resistant property	11
	Bibliography.....	13
	Figure	
	Figure A.1 – Arrhenius plot (residual stress 90 %)	11
	Tables	
	Table 1 – Values for thermal-resistant aluminium alloy wire	5
	Table 2 – Diameter and tolerance on diameter.....	5
	Table 3 – Tensile stress and elongation of wires (before stranding)	6
	Table 4 – Electrical resistivity	7
	Table 5 – Duration and temperature of heating to affirm thermal-resistant property.....	7

1 Scope

This European Standard is applicable to thermal-resistant aluminium alloy wires before stranding for manufacture of stranded conductors for overhead lines. It specifies the mechanical, electrical and thermal-resistant properties of wires in the diameter range commercially available.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 50183:2000, *Conductors for overhead lines - Aluminium-magnesium-silicon alloy wires*

EN 60889:1997, *Hard-drawn aluminium wire for overhead line conductors* (IEC 60889:1987)

IEC 60468:1974, *Method of measurement of resistivity of metallic materials*

ISO 7802, *Metallic materials - Wire - Wrapping test*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

diameter

mean of two measured values at right angles taken at the same cross section

NOTE For non-round wires, the equivalent diameter of the round wire with the same section is used.

3.2

type

thermal-resistant aluminium alloy wires defined as “AT1”, “AT2”, “AT3” and “AT4”

3.3

thermal-resistant aluminium alloy wire

all types of aluminium-zirconium alloy wire, used at operation temperature higher than that of conventional aluminium-magnesium-silicon alloy wire, as specified in EN 50183, or hard-drawn aluminium wire for overhead line conductors, as specified in EN 60889, with an allowable operating temperature as described in Table 1.

The operation temperature of conventional hard-drawn aluminium wires as well as conventional aluminium-magnesium-silicon alloy wires is limited with 80 °C

4 Designation

The wire designations included in this standard are as follows:

- thermal-resistant aluminium alloy wire with maximum allowable continuous operating temperature of 150 °C, designated AT1;
- extra high-strength, thermal-resistant aluminium alloy wire with maximum allowable continuous operating temperature of 150 °C, designated AT2;
- super thermal-resistant aluminium alloy wire with maximum allowable continuous operating temperature of 210 °C, designated AT3;
- extra thermal-resistant aluminium alloy wire with maximum allowable continuous operating temperature of 230 °C, designated AT4.