

Nuclear fuel technology - Guidelines on the measurement of the specific surface area of uranium oxide powders by the BET method (ISO 12800:2017)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 12800:2019 sisaldab Euroopa standardi EN ISO 12800:2019 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 12800:2019 consists of the English text of the European standard EN ISO 12800:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 12.06.2019.	Date of Availability of the European standard is 12.06.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 27.120.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Nuclear fuel technology - Guidelines on the measurement
of the specific surface area of uranium oxide powders by
the BET method (ISO 12800:2017)**

Technologie du combustible nucléaire - Lignes
directrices pour le mesurage de l'aire massique
(surface spécifique) des poudres d'oxyde d'uranium
par la méthode BET (ISO 12800:2017)

Kernbrennstofftechnologie - Leitlinien für die Messung
des spezifischen Oberflächenbereiches von Uranoxid-
Pulvern mittels der BET-Methode (ISO 12800:2017)

This European Standard was approved by CEN on 8 March 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 12800:2017 has been prepared by Technical Committee ISO/TC 85 "Nuclear energy, nuclear technologies, and radiological protection" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 12800:2019 by Technical Committee CEN/TC 430 "Nuclear energy, nuclear technologies, and radiological protection" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 12800:2017 has been approved by CEN as EN ISO 12800:2019 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
4.1 Summary of the BET method	1
4.2 Isothermal adsorption curves.....	1
4.3 Conditions and assumptions.....	2
5 Procedure	3
5.1 Sample preparation	3
5.2 Volumetric measurement	3
5.3 Gravimetric measurement.....	3
5.4 Original and single-point methods.....	3
5.5 Dynamic method (carrier gas method).....	4
5.6 Alternative methods.....	4
6 Expression of results	4
6.1 Methods of calculation	4
6.1.1 Multipoint determination	4
6.1.2 Single-point determination	7
6.2 Precision and accuracy.....	7
7 Test report	7
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 85, *Nuclear energy, nuclear technologies, and radiological protection*, Subcommittee SC 5, *Nuclear installations, processes and technologies*.

This second edition cancels and replaces the first edition (ISO 12800:2003), which has been technically revised.

Nuclear fuel technology — Guidelines on the measurement of the specific surface area of uranium oxide powders by the BET method

1 Scope

This document gives guidelines on the determination of the specific surface area of as-fabricated uranium dioxide powder by volumetric or gravimetric determination of the amount of nitrogen adsorbed on the powder, and can be applied to other similar materials, e.g. U_3O_8 , $\text{UO}_2\text{-PuO}_2$ powders, and other bodies with similar surface areas, e.g. powder granules or green pellets, provided that the conditions described are fulfilled. Modifications using other adsorbing gases are included.

The method is relevant as long as the expected value is in the range between $1 \text{ m}^2/\text{g}$ and $10 \text{ m}^2/\text{g}$.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

4.1 Summary of the BET method

The BET method is based on the determination of the amount of gas necessary to cover the surface by a monomolecular layer. This amount is determined from the isothermal adsorption curve of nitrogen (N_2) at the temperature of liquid nitrogen (77,4 K) according to Reference [2]. The amount of N_2 adsorbed at a given pressure is determined by volumetric or gravimetric measurement[6]. In order to remove surface contamination of the adsorbent, the sample has to be evacuated and heated under appropriate conditions before the measurement is performed.

4.2 Isothermal adsorption curves

The isothermal adsorption curve describes the relationship between the mass of the adsorbate, m_A (N_2), adsorbed per gram of adsorbent (e.g. UO_2 powder) at an equilibrium pressure of p at constant temperature T , as shown in [Formula \(1\)](#):

$$m_A = f(p, T) \quad (1)$$

Generally, the relative pressure p/p_0 is introduced instead of the absolute pressure p , where p_0 is the saturation vapour pressure which is $1,013 \times 10^5 \text{ Pa}$ for nitrogen at 77,4 K.