

Self adhesive tapes - Determination of peel adhesion
properties (ISO 29862:2018)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 29862:2019 sisaldab Euroopa standardi EN ISO 29862:2019 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 29862:2019 consists of the English text of the European standard EN ISO 29862:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.06.2019.	Date of Availability of the European standard is 05.06.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.180

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Self adhesive tapes - Determination of peel adhesion properties (ISO 29862:2018)

Rubans auto-adhésifs - Détermination des caractéristiques du pouvoir adhésif linéaire (ISO 29862:2018)

Klebebänder - Bestimmung der Klebkraft (ISO 29862:2018)

This European Standard was approved by CEN on 8 April 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 29862:2018 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 29862:2019 by Technical Committee CEN/TC 193 "Adhesives" the secretariat of which is held by UNE.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1939:2003.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 29862:2018 has been approved by CEN as EN ISO 29862:2019 without any modification.

Contents

Page

Foreword.....	v
1 Scope.....	1
2 Normative references.....	2
3 Terms and definitions.....	2
4 Significance and use.....	2
5 Method 1 — Self adhesive tapes — Measurement of peel adhesion from stainless steel at an angle of 180°.....	3
5.1 Principle.....	3
5.2 Materials.....	3
5.3 Apparatus.....	3
5.4 Test samples and test pieces.....	4
5.5 Procedure.....	5
5.5.1 Standard test conditions.....	5
5.5.2 Preparation of the panel.....	5
5.5.3 Peel adhesion.....	5
5.6 Expression of results.....	5
5.7 Test report.....	5
6 Method 2 — Self adhesive tapes — Measurement of peel adhesion from its own backing at an angle of 180°.....	6
6.1 Principle.....	6
6.2 Apparatus.....	6
6.3 Test samples and test pieces.....	6
6.4 Procedure.....	7
6.4.1 Standard test conditions.....	7
6.4.2 Preparation of the panel.....	7
6.5 Expression of results.....	7
6.6 Test report.....	7
7 Method 3 — Self adhesive tapes — Measurement of peel adhesion of double sided and transfer tapes at an angle of 180°.....	7
7.1 Principle.....	7
7.2 Materials.....	7
7.3 Apparatus.....	7
7.4 Test samples and test pieces.....	7
7.5 Procedure.....	8
7.5.1 Standard test conditions.....	8
7.5.2 Preparation of the panel.....	8
7.5.3 Procedure for open side of double sided or adhesive transfer tape.....	8
7.5.4 Procedure for closed side of double sided or adhesive transfer tape.....	8
7.6 Expression of results.....	8
7.7 Test report.....	8
8 Method 4 — Self adhesive tapes — Measurement of adhesion of the liner to an adhesive tape at an angle of 180°.....	9
8.1 Principle.....	9
8.1.1 Double sided adhesive tapes.....	9
8.1.2 Single sided adhesive tapes.....	9
8.2 Materials.....	9
8.3 Apparatus.....	9
8.4 Test samples and test pieces.....	9
8.5 Procedure.....	9
8.5.1 Double sided tapes.....	9
8.5.2 Single sided tape.....	9
8.6 Expression of results.....	10

8.7 Test report..... 10

Annex A (normative) Self adhesive tapes — Measurement of peel adhesion from a surface at low temperature..... 11

Annex B (normative) Self adhesive tapes — Measurement of peel adhesion from a surface at an angle of 90° 12

Bibliography..... 14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition cancels and replaces the first edition (ISO 29862:2007) of which it constitutes a minor revision.

The changes compared to the previous edition are as follows:

- the normative references in [Clause 2](#) have been updated;
- definitions have been added in [Clause 3](#) for “self adhesive tape”, “liner” and “double sided adhesive tape”;
- a Bibliography has been added;
- the text has been editorially revised to comply with the most recent editing rules.

Self adhesive tapes — Determination of peel adhesion properties

1 Scope

This document specifies a series of methods for the determination of peel adhesion properties of self adhesives tapes.

This document contains:

- Method 1: Self adhesive tapes – Measurement of peel adhesion from stainless steel at an angle of 180°;
- Method 2: Self adhesive tapes – Measurement of peel adhesion from its own backing at an angle of 180°;
- Method 3: Self adhesive tapes – Measurement of peel adhesion of double sided and transfer tapes at an angle 180°;
- Method 4: Self adhesive tapes – Measurement of adhesion of the liner to an adhesive tape at an angle of 180°.

[Annexes A](#) and [B](#) specify further variations in the testing protocol according to specific conditions.

A guide to the use of these methods is given in [Table 1](#).

Table 1 — Methods and annexes

Method	Angle of peel	Temperature of test	
		23 °C	Low temperature
Method 1 Adhesion to steel	180°	—	Annex A
	90°	Annex B	-
Method 2 Adhesion to back- ing	180°	—	Annex A
	90°	Annex B	—
Method 3 Adhesion of double sided and transfer tape	180°	—	Annex A
	90°	Annex B	—
Method 4 Adhesion of liner	180°	—	Annex A
	90°	Annex B	-

NOTE 1 These methods provide a means of assessing the uniformity of the adhesion of a given type of self adhesive tape. The assessment may be within a roll of tape, between rolls or between production lots.

NOTE 2 Variations in the tape backing and adhesive affect the response. Therefore these methods cannot be used to pinpoint the specific cause(s) of non uniformity.

NOTE 3 These test methods may not be appropriate to test tapes having either relatively stiff backings, stiff liners or backing showing high stretch at low forces. These characteristics will result in a high variability for the test response which is not a true indication of the real nature of the adhesive bond.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12481, *Self adhesive tapes — Terminology*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12481 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

peel adhesion

force required to peel a strip of adhesive tape from a specified substrate at a specified angle and speed

3.2

open side

<adhesive> surface of the adhesive on a double sided tape which is exposed on normal unwinding or separation of the first liner

3.3

closed side

<adhesive> surface of the adhesive on a double sided tape which normally remains in contact with the release liner on normal unwinding or separation of the first liner

3.4

transfer tape

adhesive tape having two available pressure sensitive surfaces without the need for a carrier and with a release liner separating the adhesive surfaces. The adhesive may contain reinforcing material

3.5

self adhesive tape

pressure sensitive adhesive

adhesive which in a dry state is permanently tacky at room temperature and adheres readily to surfaces under brief and light pressure

3.6

liner

treated sheet to cover the adhesive temporarily to facilitate handling or unrolling

3.7

double sided adhesive tape

tape where adhesive is applied to both sides of the carrier

4 Significance and use

These test methods are tools for quality control use. Given specific self adhesive tape and a requirement in terms of the minimum or maximum value expected for this tape, the data from the test can be used in conjunction with acceptance criteria.

Test methods 1, 2, 3, and [Annexes A](#) and [B](#) can show the relative bond strength of a given tape to one or more surfaces (material and texture) as compared to the standard stainless steel panel. Substitution of representative samples of materials in question for the standard steel panel would suffice to do this.