

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

**Materials for printed boards and other interconnecting structures –  
Part 2-34: Reinforced base materials, clad and unclad – Non-halogenated  
modified or unmodified resin system, woven E-glass laminate sheets of defined  
relative permittivity (equal to or less than 3,7 at 1 GHz) and flammability (vertical  
burning test), copper-clad**

**Matériaux pour circuits imprimés et autres structures d'interconnexion –  
Partie 2-34: Matériaux de base renforcés, plaqués et non plaqués –  
Feuilles stratifiées en tissu de verre de type E, en résine isolante non halogénée  
modifiée ou non, de permittivité relative (inférieure ou égale à 3,7 à 1 GHz) et  
d'inflammabilité définies (essai de combustion verticale), plaquées cuivre**





## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2009 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembé  
CH-1211 Geneva 20  
Switzerland  
Email: [inmail@iec.ch](mailto:inmail@iec.ch)  
Web: [www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: [www.iec.ch/webstore/custserv](http://www.iec.ch/webstore/custserv)

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: [csc@iec.ch](mailto:csc@iec.ch)

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

### A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: [www.iec.ch/searchpub/cur\\_fut-f.htm](http://www.iec.ch/searchpub/cur_fut-f.htm)

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: [www.iec.ch/webstore/custserv/custserv\\_entry-f.htm](http://www.iec.ch/webstore/custserv/custserv_entry-f.htm)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: [csc@iec.ch](mailto:csc@iec.ch)

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00



IEC 61249-2-34

Edition 1.0 2009-02

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

Materials for printed boards and other interconnecting structures –  
Part 2-34: Reinforced base materials, clad and unclad – Non-halogenated  
modified or unmodified resin system, woven E-glass laminate sheets of defined  
relative permittivity (equal to or less than 3,7 at 1 GHz) and flammability (vertical  
burning test), copper-clad

Matériaux pour circuits imprimés et autres structures d'interconnexion –  
Partie 2-34: Matériaux de base renforcés, plaqués et non plaqués –  
Feuilles stratifiées en tissu de verre de type E, en résine isolante non halogénée  
modifiée ou non, de permittivité relative (inférieure ou égale à 3,7 à 1 GHz) et  
d'inflammabilité définies (essai de combustion verticale), plaquées cuivre

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX

ICS 31.180

ISBN 2-8318-1028-4

## CONTENTS

FOREWORD .....	4
1 Scope .....	6
2 Normative references .....	6
3 Materials and construction .....	6
3.1 Resin system .....	6
3.2 Metal foil .....	7
3.3 Reinforcement .....	7
4 Internal marking .....	7
5 Electrical properties .....	7
6 Non-electrical properties of the copper-clad laminate .....	8
6.1 Appearance of the copper-clad sheet .....	8
6.1.1 Indentations (pits and dents) .....	8
6.1.2 Wrinkles .....	8
6.1.3 Scratches .....	8
6.1.4 Raised areas .....	9
6.1.5 Surface waviness .....	9
6.2 Appearance of the unclad face .....	9
6.3 Laminate thickness .....	9
6.4 Bow and twist .....	10
6.5 Properties related to the copper foil bond .....	10
6.6 Punching and machining .....	11
6.7 Dimensional stability .....	11
6.8 Sheet sizes .....	11
6.8.1 Typical sheet sizes .....	11
6.8.2 Tolerances for sheet sizes .....	11
6.9 Cut panels .....	12
6.9.1 Cut panel sizes .....	12
6.9.2 Size tolerances for cut panels .....	12
6.9.3 Rectangularity of cut panels .....	12
7 Non-electrical properties of the base material after complete removal of the copper foil .....	12
7.1 Appearance of the dielectric base material .....	12
7.2 Flexural strength .....	13
7.3 Flammability .....	13
7.4 Water absorption .....	13
7.5 Measling .....	14
7.6 Glass transition temperature and cure factor .....	14
8 Quality assurance .....	14
8.1 Quality system .....	14
8.2 Responsibility for inspection .....	15
8.3 Qualification inspection .....	15
8.4 Quality conformance inspection .....	15
8.5 Certificate of conformance .....	15
8.6 Safety data sheet .....	15
9 Packaging and marking/labelling .....	15
10 Ordering information .....	16

Annex A (informative) Engineering information .....	17
Annex B (informative) Common laminate constructions.....	19
Annex C (informative) Guideline for qualification and conformance inspection.....	20
Bibliography .....	21
Table 1 – Electrical properties .....	7
Table 2 – Nominal thickness and tolerance of metal-clad laminate.....	9
Table 3 – Bow and twist .....	10
Table 4 – Pull-off and peel strength .....	10
Table 5 – Dimensional stability .....	11
Table 6 – Size tolerances for cut panel.....	12
Table 7 – Rectangularity of cut panel.....	12
Table 8 – Flexural strength.....	13
Table 9 – Flammability .....	13
Table 10 – Water absorption .....	14
Table 11 – Measling .....	14
Table 12 – Glass transition temperature and cure factor .....	14

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MATERIALS FOR PRINTED BOARDS AND  
OTHER INTERCONNECTING STRUCTURES –**

**Part 2-34: Reinforced base materials, clad and unclad –  
Non-halogenated modified or unmodified resin system, woven E-glass  
laminate sheets of defined relative permittivity (equal to or less than 3,7 at  
1 GHz) and flammability (vertical burning test), copper-clad**

**FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61249-2-34 has been prepared by IEC technical committee 91: Electronics assembly technology.

The text of this standard is based on the following documents:

FDIS	Report on voting
91/830/FDIS	91/845/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The list of all the parts of the IEC 61249 series, under the general title *Materials for printed boards and other interconnecting structures*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

This document is a preview generated by EVS

## MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

**Part 2-34: Reinforced base materials, clad and unclad –  
Non-halogenated modified or unmodified resin system, woven E-glass  
laminate sheets of defined relative permittivity (equal to or less than 3,7 at  
1 GHz) and flammability (vertical burning test), copper-clad**

### 1 Scope

This part of IEC 61249 specifies requirements for properties of non-halogenated epoxide woven E-glass laminate sheet of a thickness of 0,05 mm up to 3,2 mm, of defined flammability (vertical burning test), copper-clad. The glass transition temperature is defined to be 150 °C minimum. The relative permittivity is equal to or less than 3,7 and the dissipation factor is equal to or less than 0,007 0 at 1 GHz.

Some property requirements may have several classes of performance. The class desired should be specified in the purchase order, otherwise the default class of material will be supplied.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61189-2:2006, *Test methods for electrical materials, interconnection structures and assemblies – Part 2: Test method for interconnection structures*

IEC 61249-5-1:1995, *Materials for interconnection structures – Part 5: Sectional specification set for conductive foils and films with or without coatings – Section 1: Copper foils (for the manufacture of copper-clad base materials)*

ISO 9000, *Quality management systems – Fundamentals and vocabulary*

ISO 11014-1, *Safety data sheet for chemical products – Part 1: Content and order of sections*

ISO 14001, *Environmental management standards – Requirements with guidance for use*

### 3 Materials and construction

The sheet consists of an insulating base with metal-foil bonded to one side or both.

#### 3.1 Resin system

The resin system is modified multifunctional epoxide, or modified epoxide, with a glass transition temperature of the laminate sheet at 150 °C minimum. The flammability rating is achieved through the use of non-halogenated flame retardants. Inorganic fillers may be used.

The maximum total halogens contained in the resin plus reinforcement matrix is 1 500 ppm with a maximum chlorine of 900 ppm and maximum bromine being 900 ppm.