
**Nuclear fuel technology — Dissolution
of plutonium dioxide-containing
materials —**

Part 1:
**Dissolution of plutonium dioxide
powders**

*Technologie du combustible nucléaire — Dissolution des matériaux
contenant du dioxyde de plutonium —*

Partie 1: Dissolution des poudres de dioxyde de plutonium



This document is a preview generated by EMS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Summary of the method	1
5 Apparatus and reagents	2
5.1 Apparatus.....	2
5.2 Reagents.....	3
6 Sample dissolution	3
6.1 Procedure for common plutonium containing materials.....	3
6.2 Solution adjustment (optional).....	5
7 Quality control	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 85, *Nuclear energy, nuclear technologies, and radiological protection*, Subcommittee SC 5, *Nuclear installations, processes and technologies*.

A list of all the parts in the ISO 18256 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document describes a method to dissolve powder samples of plutonium oxide to provide suitable aliquots for subsequent analysis of elemental concentration and isotopic composition.

This document is a preview generated by EVS

Nuclear fuel technology — Dissolution of plutonium dioxide-containing materials —

Part 1:

Dissolution of plutonium dioxide powders

1 Scope

This document specifies the dissolution of powder samples of plutonium oxide for subsequent determination of elemental concentration and isotopic composition.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Summary of the method

Among the factors affecting the formation of solid solution and hence, the ease of dissolution are:

- the method of fuel fabrication (i.e. mechanically blended oxides, co-precipitated oxides, or sol-gel oxides);
- the degree of sintering.

Therefore, different dissolution methods are applied according to the type of plutonium oxide sample to be dissolved. For high-fired plutonium oxide procedure can be different.

The radiological hazard of plutonium and the need to minimize the waste shall be taken into account when choosing the mass of the sample to be dissolved. In most cases, PuO₂ masses between 0,1 g and 1 g are appropriate for the subsequent analysis.

For the highest possible assay accuracy only gravimetric dissolution methods are recommended. However for a less critical assay, volumetric dissolution may be appropriate.