

Klaas ehitusmaterjalina. Soojuskandeteguri (U-väärtuse) määramine. Kuuma plaadi meetod

Glass in building - Determination of thermal transmittance (U value) - Guarded hot plate method

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 674:2011 sisaldab Euroopa standardi EN 674:2011 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 29.07.2011 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 15.06.2011.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 674:2011 consists of the English text of the European standard EN 674:2011.

This standard is ratified with the order of Estonian Centre for Standardisation dated 29.07.2011 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 15.06.2011.

The standard is available from Estonian standardisation organisation.

ICS 81.040.20

Standardite reprodutseerimis- ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru str 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:
Aru str 10 Tallinn 10317 Estonia; www.evs.ee; Phone: 605 5050; E-mail: info@evs.ee

English Version

Glass in building - Determination of thermal transmittance (U value) - Guarded hot plate method

Verre dans la construction - Détermination du coefficient de transmission thermique, U - Méthode de l'anneau de garde

Glas im Bauwesen - Bestimmung des Wärmedurchgangskoeffizienten (U -Wert) - Verfahren mit dem Plattengerät

This European Standard was approved by CEN on 29 April 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Basic formula	5
5 Brief outline of the measuring procedure	5
6 Test apparatus	5
7 Dimensions of the specimens	6
8 Preparation of the specimens	6
9 Performance of the measurements	7
10 Evaluation of the results	7
10.1 Thermal resistance of the multiple glazing	7
10.2 Declared U Value.....	7
10.3 Design U value	8
11 Expression of the results	8
11.1 U values	8
11.2 Thermal resistance	8
11.3 Intermediate values	8
12 Test report	9
12.1 Information included in the test report.....	9
12.2 Identification of each glazing specimen.....	9
12.3 Cross section of the specimen.....	9
12.4 Results	9
Bibliography	11

Foreword

This document (EN 674:2011) has been prepared by Technical Committee CEN/TC 129 “Glass in building”, the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2011, and conflicting national standards shall be withdrawn at the latest by December 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 674:1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies a measurement method to determine the thermal transmittance of glazing with flat and parallel surfaces. Structured surfaces, e.g. patterned glass, can be considered to be flat.

This European Standard applies to multiple glazing with outer panes which are not transparent to far infrared radiation, which is the case for soda lime silicate glass products, borosilicate glass and glass ceramics. Internal elements may be far infrared transparent.

The procedure specified in this European Standard determines the U value¹⁾ (thermal transmittance) in the central area of glazing. The edge effects, due to the thermal bridge through the spacer of an insulating glass unit or through the window frame are not included. Furthermore energy transfer due to solar radiation is not taken into account.

The procedure specified in this European Standard should generally only be considered when the calculation method detailed in EN 673 is inappropriate or unsuitable.

The document for the calculation of the overall U value of windows, doors and shutters (see [3]) gives normative reference to the U value evaluated for the glazing components according to this standard.

A vertical position of the glazing is specified.

U values evaluated according to the present standard are used for product comparison as well as for other purposes, in particular for predicting:

- heat loss through glazing;
- conduction heat gains in summer;
- condensation on glazing surfaces;
- the effects of the absorbed solar radiation in determining the solar factor (see [1]).

Reference should be made to [4], [5], or other European Standards dealing with heat loss calculations for the application of glazing U values determined by this standard.

The determination of the thermal transmittance is performed for conditions which correspond to the average situation for glazing in practice.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12898, *Glass in building — Determination of the emissivity*

ISO 8302:1991, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

1) In some countries the symbol k has been used hitherto.