

Plastics - Determination of thermal stability of poly(vinyl chloride), related chlorine-containing homopolymers and copolymers and their compounds - Discoloration method (ISO 305:2019)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 305:2019 sisaldab Euroopa standardi EN ISO 305:2019 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 305:2019 consists of the English text of the European standard EN ISO 305:2019.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 12.06.2019.	Date of Availability of the European standard is 12.06.2019.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 83.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

Plastics - Determination of thermal stability of poly(vinyl chloride), related chlorine-containing homopolymers and copolymers and their compounds - Discoloration method (ISO 305:2019)

Plastiques - Détermination de la stabilité thermique du poly(chlorure de vinyle), des homopolymères et copolymères chlorés apparentés et de leurs compositions - Méthode du changement de couleur (ISO 305:2019)

Kunststoffe - Bestimmung der Thermostabilität von Polyvinylchlorid (PVC), verwandten chlorhaltigen Homopolymeren und Copolymeren und ihren Formmassen - Verfärbungsverfahren (ISO 305:2019)

This European Standard was approved by CEN on 26 May 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, North Macedonia, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## European foreword

This document (EN ISO 305:2019) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 305:1999.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 305:2019 has been approved by CEN as EN ISO 305:2019 without any modification.

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
4.1 Method A: Oil-bath method.....	1
4.2 Method B: Oven method.....	2
<b>5 Preparation and number of test specimens</b> .....	<b>2</b>
<b>6 Test temperature</b> .....	<b>2</b>
<b>7 Method A: Oil-bath method</b> .....	<b>2</b>
7.1 Apparatus.....	2
7.2 Procedure.....	3
<b>8 Method B: Oven method</b> .....	<b>3</b>
8.1 Apparatus.....	3
8.2 Procedure.....	4
<b>9 Expression of results</b> .....	<b>4</b>
<b>10 Precision</b> .....	<b>5</b>
<b>11 Test report</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>6</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This third edition cancels and replaces the second edition (ISO 305:1990), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- editorial changes have been applied to align the document with the ISO structure;
- [Clauses 2](#) and [3](#) have been added and subsequent clauses have been renumbered.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Plastics — Determination of thermal stability of poly(vinyl chloride), related chlorine-containing homopolymers and copolymers and their compounds — Discoloration method

## 1 Scope

This document specifies two methods for the determination of the thermal stability of products and compounds based on vinyl chloride homopolymers and copolymers (referred to simply as PVC in the following text) by the extent of the discoloration that occurs when they are exposed, in the form of sheet, to elevated temperatures. The two methods are:

- Method A: Oil-bath method;
- Method B: Oven method.

These methods are particularly applicable to the determination of the resistance of PVC to degradation by heat, as assessed by the change in colour after different times of heating under standardized conditions. The results are comparative only, and can be unsatisfactory when coloured PVC materials are tested.

The stability times given by the two methods might not be similar and cannot be used for direct-comparison purposes.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Principle

### 4.1 Method A: Oil-bath method

Method A is a simple method, which requires little expenditure on apparatus and permits materials to be tested almost in the absence of air.

A series of test specimens is heated at an elevated temperature for different lengths of time in a temperature-controlled oil bath. The test specimens are placed between an aluminium block and an aluminium cylinder to promote heat transfer and restrict air access.