

---

---

**Crosslinked polyethylene (PE-X)  
and crosslinked medium density  
polyethylene (PE-MDX) — Effect of  
time and temperature on expected  
strength**

*Tubes en polyéthylène réticulé (PE-X et PE-MDX) — Influence du  
temps et de la température sur la résistance espérée*

This document is a preview generated by ERS



# **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Characteristics</b> .....	<b>2</b>
<b>5 Basic formulae</b> .....	<b>2</b>
<b>6 Expected strength</b> .....	<b>3</b>
6.1 Extrapolation limits .....	3
6.2 Graphical representation .....	4
6.3 Tabulated values .....	4
<b>Annex A (normative) Demonstrating conformance of pipes to the reference lines</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>11</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This second edition cancels and replaces the first edition (ISO 10146:1997), which has been technically revised. The main changes compared to the previous edition are as follows:

- a second type of material termed crosslinked medium density polyethylene (PE-MDX) has been added in accordance with DIN 16894:2011 [1];
- the minimum degree of crosslinking applicable for pipe conforming to this document is specified.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Crosslinked polyethylene (PE-X) and crosslinked medium density polyethylene (PE-MDX) — Effect of time and temperature on expected strength

## 1 Scope

This document specifies the minimum values for expected strength as a function of time and temperature in the form of reference lines, for use in calculations on crosslinked polyethylene (PE-X) pipes and crosslinked medium density polyethylene (PE-MDX) pipes.

NOTE 1 This document is applicable for pipes with the minimum level of crosslinking after production in accordance with [Clause 4](#).

NOTE 2 The density range for medium density polyethylene is 926 kg/m<sup>3</sup> to 940 kg/m<sup>3</sup> in accordance with ISO 17855-1:2014[2].

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 10147, *Pipes and fittings made of crosslinked polyethylene (PE-X) — Estimation of the degree of crosslinking by determination of the gel content*

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

### 3.1 reference lines

generic description of the minimum long-term hydrostatic strength to be expected from a particular polymer

Note 1 to entry: Reference lines are not to be considered as characteristic of a specific grade or of material from a specific supplier.

Note 2 to entry: The lines are described by a mathematical equation which permits interpolation and extrapolation in an unambiguous way at various temperatures.