

ICS 83.160.01

English Version

Material derived from End-of-Life tyres - Granulates and powders - Elastomers identification: Gas-chromatography and mass-spectrometric detection of pyrolysis products in solution

Matériaux obtenus à partir de pneumatiques en fin de vie - Granulats et poudre - Identification des élastomères : Détection par chromatographie en phase gazeuse et spectrométrie de masse des produits de pyrolyse en solution

Material aus Altreifen - Granulat und Mehle - Identifizierung von Elastomeren: Gaschromatographie und massenspektrometrische Detektion von Pyrolyseprodukten in Lösung

This Technical Specification (CEN/TS) was approved by CEN on 14 January 2019 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page
European foreword		3
Introduction		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Principle	5
5	Reagents	5
6	Apparatus	5
7	Procedure	7
8	Interpretation of the GC/MS data	8

European foreword

This document (CEN/TS 17307:2019) has been prepared by Technical Committee CEN/TC 366 "Materials obtained from End-of-Life Tyres (ELT)", the secretariat of which is held by UNI.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

WARNING — Persons using this European Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

This document is a preview generated by EVS

1 Scope

This document specifies a method for the identification of the elastomers in granulates or powder derived from End-of-Life Tyres.

The method specified is a qualitative method only.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1407, *Rubber — Determination of solvent extract*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

A sufficient amount of granules or powder is compacted and homogenized in a laboratory mill and a small aliquot of the homogenized sample is then solvent extracted and subjected to pyrolysis at elevated temperature. Few drops of the liquid pyrolysis products are then diluted in dichloromethane for the GC/MS analysis. The use of the mass-spectrometric detector is a mean for improving the sensitivity and reliability of the identification of the elastomers present in low or trace amount, with threshold limit estimated to about 5 %.

The use of this standard pre-supposes sufficient working knowledge of the principles and techniques of gas chromatography/mass-spectrometry (GC/MS) for the analyst to perform the operations described and interpret the results correctly.

5 Reagents

5.1 Dichloromethane

5.2 Acetone

5.3 Nitrogen, for flushing the pyrolysis product.

6 Apparatus

All reagents shall be of analytical grade

6.1 Extraction apparatus. The apparatus specified in ISO 1407 is satisfactory.