
**Plastics — Guidance on fire
characteristics and fire performance
of PVC materials used in building
applications**

*Plastiques — Lignes directrices relatives aux caractéristiques et
aux performances au feu des matériaux en PVC utilisés dans les
applications de construction*



This document is a preview generated by ERS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 PVC building materials and products	3
4.1 Definition and description.....	3
4.1.1 General.....	3
4.1.2 PVC-U based products.....	4
4.1.3 PVC-P based products.....	4
4.1.4 PVC-C based products.....	5
4.1.5 Flame retardants.....	5
4.2 Product standards.....	6
5 Fire safety strategy	8
5.1 Fire safety objectives.....	8
5.1.1 General.....	8
5.1.2 Safety of life.....	9
5.1.3 Conservation of property.....	9
5.1.4 Continuity of business or service operations.....	10
5.1.5 Protection of the environment.....	10
5.1.6 Preservation of heritage.....	11
5.2 Fire scenarios.....	11
6 Fire test methods — Description and relevance	13
6.1 General.....	13
6.1.1 Reaction to fire tests applicable to plastics construction products.....	13
6.1.2 Intermediate scale plastics reaction to fire tests.....	14
6.1.3 Fire stage and fire tests.....	14
6.1.4 Assessment of the fire threat to people.....	14
6.2 Relevance of results and studies comparisons.....	15
7 Material fire characteristics relevant for PVC construction products	16
7.1 Combustibility.....	16
7.2 Ignitability.....	18
7.2.1 Ignition temperature.....	18
7.2.2 Ignitability measured by the cone calorimeter test.....	19
7.3 Oxygen index.....	20
7.4 Heat release and heat release rate.....	21
7.4.1 General.....	21
7.4.2 Heat release data.....	22
7.5 Flame spread.....	24
7.5.1 General.....	24
7.5.2 Flame spread by flame propagation.....	26
7.5.3 Flame spread by flaming droplets.....	26
7.6 Smoke generation.....	27
7.6.1 Smoke obscuration.....	27
7.6.2 Smoke toxicity.....	28
7.6.3 Smoke corrosivity.....	31
7.6.4 HCl decay.....	32
7.7 Char formation and intumescence.....	33
Annex A (informative) Example of reaction to fire performance — PVC-U pipe	34
Annex B (informative) Example case history — Plastimet accident	35

Bibliography	36
---------------------------	-----------

This document is a preview generated by EVS

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Fire safety is an essential consideration in building design regardless of the type and nature of products used. Effective measures should be taken to prevent or reduce the likelihood of fires that may result in casualties, injuries or property damage.

National codes and regulations are the basis of such fire safety measures. Technical details are given in standards and related documents, referred to as specific documents or incorporated in the said codes or regulations. Such details are particularly important when performance-based behaviour is concerned. A specific case is the European Construction Products Regulation [77], which specifies that products need to be tested and classified regarding their fire performance according to the EU harmonized classification systems for reaction to fire and for resistance to fire.

The construction industry makes significant efforts to protect society from the dramatic consequences of fires. As a result, 1 % to 8 % of total construction costs are spent on fire safety measures. These costs are directly dependent on the type of building and can increase considerably for sensitive buildings like schools and theatres. In the case of shopping centres, fire safety measures can amount to 10 % of total building costs.

Plastic products are increasingly specified by architects and used by builders. They contribute to greater energy efficiency, cost savings and to a more comfortable and safer environment. The role of plastics in fire safety should be addressed despite the fact that they are considered as a major combustible contributor only in less than 15 % of fires.

Plastic materials or products can be tailored to meet specific needs and to reduce their contribution to the propagation of a fire. Some families of plastics, such as halogen containing polymers like PVC, inherently have superior fire performance. The same performance can be achieved or even improved with other plastics by:

- adding flame retardants;
- covering them with less combustible layers.

Each type of building has its own specific potential fire hazards and fire risks linked to the permanent elements of the building (i.e. construction products and overall design) as well as its content including furniture, papers, clothes, domestic and leisure articles. Fire hazard and fire risk are also linked to the proper use and installation of construction products in the building structure. This is also valid for PVC and for plastic materials in general, which, like all other construction materials, should be used in the correct applications and under appropriate conditions.

NOTE Data from various market surveys show that only 10 % to 15 % of all plastics contained in a private house are in construction products. 85 % to 90 % of plastics are brought into the building by the occupants in, for example, furniture (including, for example, wooden furniture containing minor plastics elements), decorations, household and media appliances, clothes, toys and packaging. This means that although PVC is a significant component of many construction products, other combustible materials often comprise a more important potential source of fuel, in particular in private houses.

A fire usually involves a combination of different combustible and non-combustible materials. Organic materials (including all plastics, wood and other carbon containing materials) produce a mixture of gaseous substances (making fire smoke always hazardous) in addition to a certain degree of heat release.

As fire is a complex phenomenon, the type and quantity of materials involved are only two of the various parameters influencing the development and consequences of a fire. The other factors that come into play include building design, location, potential ignition sources and other fire scenario parameters.

Fire tests results relate only to the behaviour of test specimens under the particular conditions of the test. They are not intended to be the sole criterion of assessing the potential fire hazard of the product in use.

This document provides information on the fire characteristics and fire performance of PVC based materials and products used in building applications. It is to be considered as a documentary and

technical reference document for any entity interested in fire safety in building and construction, when products containing PVC are concerned, including at the design or pre-building phase.

The intended audience for this document includes but is not necessarily limited to:

- materials and products manufacturers;
- building designers, specifiers and architects;
- building owners and managers;
- fire fighters and investigators;
- public health authorities;
- fire testing laboratories.

Plastics — Guidance on fire characteristics and fire performance of PVC materials used in building applications

1 Scope

This document provides information on the fire characteristics and performance in fire tests of PVC materials and products for use in building applications.

It illustrates a number of suitable applications incorporating primarily PVC materials, including unplasticized PVC (PVC-U), plasticized (or flexible) PVC (PVC-P) and chlorinated PVC (PVC-C) based products. Except where otherwise stated, there is no restriction with reference to the content of PVC (in terms of quantity and composition) in the products mentioned in this document.

This document draws attention to the limits of applicability or the unsuitability of some standard fire test methods for certain applications of PVC based products in buildings.

This document applies to products during their use phase in the building and does not apply to the manufacturing phase of plastic products. It neither applies to general safety measures applicable to the installation phase nor to the dismantling or the demolition phase of the building.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 13943, *Fire safety — Vocabulary*

IEC 60695-4, *Fire hazard testing — Part 4: Terminology concerning fire tests for electrotechnical products*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 13943, IEC 60695-4 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

composite

solid product consisting of two or more distinct phases, including a binding material (matrix) and a particulate or fibrous material

Note 1 to entry: Solid product consisting of two or more layers (often in a symmetrical assembly) of, for instance, plastic film or sheet, normal or syntactic cellular plastic, metal, wood or a composite, with or without adhesive interlayers.

[SOURCE: ISO 472:2013, 2.182.1 and 2.182.2, modified — 2.182.1 and 2.182.2 have been merged into one entry.]