

**Advanced technical ceramics - Thermomechanical  
properties of monolithic ceramics - Part 5:  
Determination of elastic moduli at elevated temperatures**

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN 820-5:2009 sisaldab Euroopa standardi EN 820-5:2009 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 31.08.2009 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 08.07.2009.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN 820-5:2009 consists of the English text of the European standard EN 820-5:2009.

This standard is ratified with the order of Estonian Centre for Standardisation dated 31.08.2009 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

Date of Availability of the European standard text 08.07.2009.

The standard is available from Estonian standardisation organisation.

ICS 81.060.30

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute Estonian Standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: +372 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

English Version

Advanced technical ceramics - Thermomechanical properties of  
monolithic ceramics - Part 5: Determination of elastic moduli at  
elevated temperatures

Céramiques techniques avancées - Propriétés  
thermomécaniques des céramiques monolithiques - Partie  
5 : Détermination des modules élastiques à température  
élevées

Hochleistungskeramik - Thermomechanische  
Eigenschaften monolithischer Keramik - Teil 5:  
Bestimmung der elastischen Moduln bei erhöhten  
Temperaturen

This European Standard was approved by CEN on 12 June 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

Page

Foreword .....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms and definitions .....	5
4 Method A: Static bending method .....	5
4.1 Principle .....	5
4.2 Apparatus .....	5
4.3 Test pieces .....	9
4.4 Procedure .....	9
4.5 Calculation of results .....	9
4.6 Accuracy and interferences .....	11
5 Method B: Resonance method .....	12
5.1 Principle .....	12
5.2 Apparatus .....	12
5.3 Test pieces .....	15
5.4 Procedure .....	15
5.5 Calculation of results .....	16
5.6 Accuracy and interferences .....	18
6 Method C: Impulse excitation method .....	18
6.1 Principle .....	18
6.2 Apparatus .....	18
6.3 Test pieces .....	21
6.4 Procedure .....	21
6.5 Calculation .....	21
6.6 Accuracy and interferences .....	22
7 Test report .....	22
7.1 General .....	22
7.2 Method A .....	23
7.3 Method B .....	23
7.4 Method C .....	24
Bibliography .....	25

## Foreword

This document (EN 820-5:2009) has been prepared by Technical Committee CEN/TC 184 "Advanced technical ceramics", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2010, and conflicting national standards shall be withdrawn at the latest by January 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 820-5:2004.

EN 820 consists of five parts, under the general title "Advanced technical ceramics - Methods of testing monolithic ceramics - Thermomechanical properties":

- Part 1: Determination of flexural strength at elevated temperatures
- Part 2: Determination of self-loaded deformation
- Part 3: Determination of resistance to thermal shock by water quenching
- Part 4: Determination of flexural creep deformation at elevated temperatures
- Part 5: Determination of elastic moduli at elevated temperatures

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This part of EN 820 describes methods for determining the elastic moduli, specifically Young's modulus, shear modulus and Poisson's ratio, of advanced monolithic technical ceramics at temperatures above room temperature. The standard prescribes three alternative methods for determining some or all of these three parameters:

- A the determination of Young's modulus by static flexure of a thin beam in three- or four-point bending.
- B the determination of Young's modulus by forced longitudinal resonance, or Young's modulus, shear modulus and Poisson's ratio by forced flexural and torsional resonance, of a thin beam.
- C the determination of Young's modulus from the fundamental natural frequency of a struck bar (impulse excitation method).

This part of EN 820 extends the above-defined room-temperature methods described in EN 843-2 to elevated temperatures. All the test methods assume the use of homogeneous test pieces of linear elastic materials. The test assumes that the test piece has isotropic elastic properties. At high porosity levels all of the methods can become inappropriate. The maximum grain size (see EN 623-3), excluding deliberately added whiskers, should be less than 10 % of the minimum dimension of the test piece.

NOTE 1 Method C in EN 843-2 based on ultrasonic time of flight measurement has not been incorporated into this part of EN 820. Although the method is feasible to apply, it is specialised, and outside the capabilities of most laboratories. There are also severe restrictions on test piece geometries and methods of achieving pulse transmission. For these reasons this method has not been included in EN 820-5.

NOTE 2 The upper temperature limit for this test depends on the properties of the test pieces, and can be limited by softening within the timescale of the test. In addition, for method A there can be limits defined by the choice of test jig construction materials.

NOTE 3 Methods B and C may not be appropriate for materials with significant levels of porosity (i.e. > 15 %) which cause damping and an inability to detect resonances or natural frequencies, respectively.

NOTE 4 This method does not provide for the effects of thermal expansion, i.e. the measurements are based on room temperature dimensions. Depending upon the use to which the data are put, it can be necessary to make a further correction by multiplying each dimensional factor in the relevant equations by a factor  $(1 + \bar{\alpha} \Delta T)$  where  $\bar{\alpha}$  is the mean linear expansion coefficient over the temperature interval  $\Delta T$  from room temperature.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 820-1, *Advanced technical ceramics — Method of testing monolithic ceramics — Thermo-mechanical properties — Part 1: Determination of flexural strength at elevated temperatures*

EN 843-1:2006, *Advanced technical ceramics — Mechanical properties of monolithic ceramics at room temperature — Part 1: Determination of flexural strength*

EN 60584-2, *Thermocouples — Part 2: Tolerances (IEC 60584-2:1982 + A1:1989)*

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1:2004)*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*  
(ISO/IEC 17025:2005)

ISO 463, *Geometrical Product Specifications (GPS) — Dimensional measuring equipment — Design and metrological characteristics of mechanical dial gauges*

ISO 3611, *Micrometer callipers for external measurement*

ISO 6906, *Vernier callipers reading to 0,02 mm*