INTERNATIONAL STANDARD



Fourth edition 2019-04

Plastics — Determination of dynamic mechanical properties —

P'r Part 1: General principles

Dé. rincipes gén Plastiques — Détermination des propriétés mécaniques dynamiques —

Partie 1: Principes généraux



Reference number ISO 6721-1:2019(E)



© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

| Contents |
|----------|
|----------|

| Fore | eword | iv | | | | |
|-------------|---|---|--|--|--|--|
| Intro | oduction | v | | | | |
| 1 | Scope | | | | | |
| 2 | Normative references | | | | | |
| 3 | Terms and definitions | | | | | |
| 4 | Principle | | | | | |
| 5 6 7 | Test apparatus5.1Type5.2Mechanical, electronic and recording systems5.3Temperature-controlled enclosure5.4Gas supply5.5Temperature-measurement device5.6Devices for measuring test specimen dimensionsTest specimens6.1General6.2Shape and dimensions6.3Preparation | 12 12 12 12 12 12 12 12 12 12 12 12 12 1 | | | | |
| 8 | Conditioning | | | | | |
| 9 | Procedure9.1Test atmosphere9.2Measurement of specimen cross-section9.3Mounting the test specimens9.4Varying the temperature9.5Varying the frequency9.6Varying the dynamic-strain amplitude | 13 13 13 13 13 13 14 14 | | | | |
| 10 | Expression of results Precision | | | | | |
| Anne | Test reportex A (informative) Resonance curves | | | | | |
| | | 12 S | | | | |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <u>www.iso</u> .org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This fourth edition cancels and replaces the third edition (ISO 6721-1:2011), which has been technically revised. The main changes compared to the previous edition are as follows:

- the document has been revised editorially;
- normative references have been changed to undated and added as references into <u>Tables 4</u> and <u>5</u>.

A list of all parts in the ISO 6721 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

00 02 17 . (

Introduction

The methods specified in the first nine parts of ISO 6721 can be used for determining storage and loss moduli of plastics over a range of temperatures or frequencies by varying the temperature of the specimen or the frequency of oscillation. Plots of the storage or loss moduli, or both, are indicative of viscoelastic characteristics of the specimen. Regions of rapid changes in viscoelastic properties at particular temperatures or frequencies are normally referred to as transition regions. Furthermore, from the temperature and frequency dependencies of the loss moduli, the damping of sound and vibration of polymer or metal-polymer systems can be estimated.

Apparent discrepancies may arise in results obtained under different experimental conditions. Without changing the observed data, reporting in full (as described in the various parts of ISO 6721) the conditions under which the data were obtained will enable apparent differences observed in different studies to be reconciled.

The definitions of complex moduli apply exactly only to sinusoidal oscillations with constant amplitude and constant frequency during each measurement. On the other hand, measurements of small phase angles between stress and strain involve some difficulties under these conditions. Because these difficulties are not involved in some methods based on freely decaying vibrations and/or varying frequency near resonance, these methods are used frequently (see ISO 6721-2 and ISO 6721-3). In these cases, some of the equations that define the viscoelastic properties are only approximately valid.

| 00 | | | | |
|------|----|------|---|---|
| 0,01 | | | | |
| | Q | | | |
| | 00 | | | |
| | | 0,0, | | |
| | | | | |
| | | | 6 | |
| | | | < | 2 |
| | | | | S |

this document is a preview demendence of the document is a preview demendence of the document of the document

Plastics — Determination of dynamic mechanical properties —

Part 1: General principles

1 Scope

The various parts of ISO 6721 specify methods for the determination of the dynamic mechanical properties of rigid plastics within the region of linear viscoelastic behaviour. This document specifies the definitions and describes the general principles including all aspects that are common to the individual test methods described in the subsequent parts.

Different deformation modes can produce results that are not directly comparable. For example, tensile vibration results in a stress which is uniform across the whole thickness of the specimen, whereas flexural measurements are influenced preferentially by the properties of the surface regions of the specimen.

Values derived from flexural-test data will be comparable to those derived from tensile-test data only at strain levels where the stress-strain relationship is linear and for specimens which have a homogeneous structure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, Plastics — Standard atmospheres for conditioning and testing

ISO 4593, Plastics — Film and sheeting — Determination of thickness by mechanical scanning

ISO 6721-2, Plastics — Determination of dynamic mechanical properties — Part 2: Torsion-pendulum method

ISO 6721-3, Plastics — Determination of dynamic mechanical properties — Part 3: Flexural vibration — Resonance-curve method

ISO 6721-4, Plastics — Determination of dynamic mechanical properties — Part 4: Tensile vibration — Non-resonance method

ISO 6721-5, Plastics — Determination of dynamic mechanical properties — Part 5: Flexural vibration — Non-resonance method

ISO 6721-6, *Plastics* — *Determination of dynamic mechanical properties* — *Part 6: Shear vibration* — *Non-resonance method*

ISO 6721-7, Plastics — Determination of dynamic mechanical properties — Part 7: Torsional vibration — Non-resonance method

ISO 6721-8, Plastics — Determination of dynamic mechanical properties — Part 8: Longitudinal and shear vibration — Wave-propagation method

ISO 6721-9, Plastics — Determination of dynamic mechanical properties — Part 9: Tensile vibration — Sonic-pulse propagation method

ISO 6721-10, Plastics — Determination of dynamic mechanical properties — Part 10: Complex shear viscosity using a parallel-plate oscillatory rheometer

ISO 6721-12, Plastics — Determination of dynamic mechanical properties — Part 12: Compressive vibration — Non-resonance method

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at <u>http://www.electropedia.org/</u>

NOTE Some of the terms defined here are also defined in ISO 472. The definitions given here are not strictly identical with, but more detailed than those in ISO 472.

3.1

complex modulus

М*

ratio of dynamic stress, given by $\sigma(t) = \sigma_A \exp(i2\pi ft)$ and dynamic strain, given by $\varepsilon(t) = \varepsilon_A \exp[i(2\pi ft - \delta)]$, of a viscoelastic material that is subjected to a sinusoidal vibration, where σ_A and ε_A are the amplitudes of the stress and strain cycles, *f* is the frequency, δ is the phase angle between stress and strain and *t* is time

Note 1 to entry: It is expressed in Pascals (Pa).

Note 2 to entry: The *phase angle* (3.5), δ , is shown in Figure 1.

Note 3 to entry: Depending on the mode of deformation, the complex modulus might be one of several types: E^* , G^* , K^* or L^* (see Table 3).

 $M^* = M' + i M''$

where $i = (-1)^{1/2} = \sqrt{-1}$ and *M*' and *M*'' are as defined in <u>3.2</u> and <u>3.3</u> respectively.

For the relationships between the different types of complex modulus, see Table 1.

Note 4 to entry: For isotropic viscoelastic materials, only two of the elastic parameters G^* , E^* , K^* , L^* and μ^* are independent (μ^* is the complex Poisson's ratio, given by $\mu^* = \mu' + i\mu''$).

Note 5 to entry: The most critical term containing Poisson's ratio μ is the "volume term" $1 - 2\mu$, which has values between 0 and 0,4 for μ between 0,5 and 0,3. The relationships in <u>Table 1</u> containing the "volume term" $1 - 2\mu$ can only be used if this term is known with sufficient accuracy.

It can be seen from Table 1 that the "volume term" $1 - 2\mu$ can only be estimated with any confidence from a knowledge of the bulk modulus *K* or the uniaxial-strain modulus *L* and either *E* or *G*. This is because *K* and *L* measurements involve deformations when the volumetric strain component is relatively large.

Note 6 to entry: Up to now, no measurement of the dynamic mechanical bulk modulus *K*, and only a small number of results relating to relaxation experiments measuring *K*(*t*), have been described in the literature.

Note 7 to entry: The uniaxial-strain modulus *L* is based upon a load with a high hydrostatic-stress component. Therefore, values of *L* compensate for the lack of *K* values, and the "volume term" $1 - 2\mu$ can be estimated with sufficient accuracy based upon the modulus pairs (*G*, *L*) and (*E*, *L*). The pair (*G*, *L*) is preferred, because *G* is based upon loads without a hydrostatic component.

Note 8 to entry: The relationships given in <u>Table 1</u> are valid for the complex moduli as well as their *magnitudes* (<u>3.4</u>).