

**Advanced technical ceramics -
Monolithic ceramics. Mechanical
properties at room temperature - Part 5:
Statistical analysis**

Advanced technical ceramics - Monolithic ceramics.
Mechanical properties at room temperature - Part 5:
Statistical analysis

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN 843-5:2007 sisaldab Euroopa standardi EN 843-5:2006 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 29.01.2007 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN 843-5:2007 consists of the English text of the European standard EN 843-5:2006.</p> <p>This document is endorsed on 29.01.2007 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala: This part of EN 843 specifies a method for statistical analysis of ceramic strength data in terms of a two-parameter Weibull distribution using a maximum likelihood estimation technique. It assumes that the data set has been obtained from a series of tests under nominally identical conditions.</p>	<p>Scope: This part of EN 843 specifies a method for statistical analysis of ceramic strength data in terms of a two-parameter Weibull distribution using a maximum likelihood estimation technique. It assumes that the data set has been obtained from a series of tests under nominally identical conditions.</p>
---	---

ICS 81.060.30

Võtmesõnad:

English Version

Advanced technical ceramics - Mechanical properties of monolithic ceramics at room temperature - Part 5: Statistical analysis

Céramiques techniques avancées - Propriétés mécaniques
des céramiques monolithiques à température ambiante -
Partie 5: Analyse statistique

Hochleistungskeramik - Mechanische Eigenschaften
monolithischer Keramik bei Raumtemperatur - Teil 5:
Statistische Auswertung

This European Standard was approved by CEN on 11 November 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....3

1 Scope4

2 Normative references4

3 Terms and definitions4

3.1 Flaws4

3.2 Flaw distributions5

3.3 Mechanical evaluation5

3.4 Statistical terms6

3.5 The Weibull distribution7

4 Symbols8

5 Significance and use10

6 Principle of calculation11

6.1 Maximum likelihood method11

6.2 Bias correction12

6.3 Confidence interval12

7 Procedure13

7.1 Graphical representation of data13

7.2 Determination of Weibull parameters by maximum likelihood method13

7.3 Determination of limits of the confidence interval14

8 Test report14

Annex A (informative) Relationship between characteristic strengths of test pieces or components of different size or shape, or with different stress fields applied15

Annex B (informative) FORTRAN program for calculating Weibull parameters17

Annex C (informative) PASCAL program for calculating Weibull parameters23

Annex D (informative) BASIC program for calculating Weibull parameters28

Annex E (normative) Unbiasing factors for estimation of Weibull modulus, \hat{m} 33

Annex F (normative) Confidence factors for characteristic strength, $\hat{\sigma}_0$ 34

Annex G (normative) Confidence factors for Weibull modulus, \hat{m} 36

Annex H (informative) Worked examples38

Annex I (informative) Example test report43

Bibliography45

Foreword

This document (EN 843-5:2006) has been prepared by Technical Committee CEN/TC 184 "Advanced technical ceramics", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2007, and conflicting national standards shall be withdrawn at the latest by June 2007.

This document supersedes ENV 843-5:1996.

EN 843 *Advanced technical ceramics — Mechanical properties of monolithic ceramics at room temperature* comprises six parts:

Part 1: *Determination of flexural strength*

Part 2: *Determination of Young's modulus, shear modulus and Poisson's ratio*

Part 3: *Determination of subcritical crack growth parameters from constant stressing rate flexural strength tests*

Part 4: *Vickers, Knoop and Rockwell superficial hardness*

Part 5: *Statistical analysis*

Part 6: *Guidance for fractographic investigation*

At the time of publication of this Revision of Part 5, Part 6 was available as a Technical Specification.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This part of EN 843 specifies a method for statistical analysis of ceramic strength data in terms of a two-parameter Weibull distribution using a maximum likelihood estimation technique. It assumes that the data set has been obtained from a series of tests under nominally identical conditions.

NOTE 1 In principle, Weibull analysis is considered to be strictly valid for the case of linear elastic fracture behaviour to the point of failure, i.e. for a perfectly brittle material, and under conditions in which strength limiting flaws do not interact and in which there is only a single strength-limiting flaw population.

If subcritical crack growth or creep deformation preceding fracture occurs, Weibull analysis can still be applied if the results fit a Weibull distribution, but numerical parameters may change depending on the magnitude of these effects. Since it is impossible to be certain of the degree to which subcritical crack growth or creep deformation has occurred, this European Standard permits the analysis of the general situation where crack growth or creep may have occurred, provided that it is recognized that the parameters derived from the analysis may not be the same as those derived from data with no subcritical crack growth or creep.

NOTE 2 This European Standard employs the same calculation procedures as method A of ISO 20501:2003 [1], but does not provide a method for dealing with censored data (method B of ISO 20501).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 843-1:2006, *Advanced technical ceramics — Mechanical properties of monolithic ceramics at room temperature — Part 1: Determination of flexural strength*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:2005)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 843-1:2006 and the following apply.

NOTE Definitions of additional statistical terms can be found in ISO 2602 [2], ISO 3534-1 [3], or other source literature on statistics.

3.1 Flaws

3.1.1

flaw

inhomogeneity, discontinuity or structural feature in a material which when loaded provides a stress concentration and a risk of mechanical failure

NOTE 1 This could be, for example, a grain boundary, large grain, pore, impurity or crack.

NOTE 2 The term flaw should not be taken as meaning the material is functionally defective, but rather as containing an inevitable microstructural inhomogeneity.

3.1.2

critical flaw

flaw acting as the source of failure