

**Täitematerjalide geomeetriliste omaduste katsetamine.
Osa 1: Terastikulise koostise määramine.
Sõelumismeetod**

**Tests for geometrical properties of aggregates - Part 1:
Determination of particle size distribution - Sieving
method**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 933-1:2012 sisaldab Euroopa standardi EN 933-1:2012 ingliskeelset teksti.	This Estonian standard EVS-EN 933-1:2012 consists of the English text of the European standard EN 933-1:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 11.01.2012.	Date of Availability of the European standard is 11.01.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.15

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Tests for geometrical properties of aggregates - Part 1: Determination of particle size distribution - Sieving method

Essais pour déterminer les caractéristiques géométriques
des granulats - Partie 1: Détermination de la granularité -
Analyse granulométrique par tamisage

Prüfverfahren für geometrische Eigenschaften von
Gesteinskörnungen - Teil 1: Bestimmung der
Korngrößenverteilung - Siebverfahren

This European Standard was approved by CEN on 29 October 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	5
5 Apparatus	5
6 Preparation of test portions	5
7 Procedure	6
7.1 Washing	6
7.2 Sieving	7
7.3 Weighing	8
8 Calculation and expression of results	8
8.1 Calculations	8
8.2 Validating the results	8
8.3 Precision	9
9 Test report	9
9.1 Required data	9
9.2 Optional data	9
Annex A (normative) Alternative test method for all-in aggregate with $D \geq 31,5$ mm	11
A.1 Principle	11
A.2 Apparatus	11
A.3 Procedure	11
A.3.1 Preparation of the initial test portion	11
A.3.2 First washing stage – particles retained on the 16 mm size test sieve	12
A.3.3 First dry sieving stage – particles retained on the 16 mm size test sieve	12
A.3.4 Preparation stage – dry subsample passing the 16 mm size test sieve	12
A.3.5 Second washing stage – reduced subsample passing the 16 mm size test sieve	12
A.3.6 Second dry sieving stage – reduced subsample passing the 16 mm size test sieve	12
A.4 Calculation and expression of results	13
A.4.1 Original dry mass	13
A.4.2 Mass retained on the sieves at the first dry sieving stage	13
A.4.3 Mass retained on the sieves at the second dry sieving stage	13
A.4.4 Mass of fines passing the 0,063 mm sieve	13
A.4.5 Particle size distribution	14
A.4.6 Validating the results	14
Annex B (normative) Test method for aggregates unsuitable for oven-drying	15
Annex C (informative) Example of test data sheet	16
Annex D (informative) Graphical presentation of results	17
Bibliography	18

Foreword

This document (EN 933-1:2012) has been prepared by Technical Committee CEN/TC 154 “Aggregates”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2012, and conflicting national standards shall be withdrawn at the latest by July 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 933-1:1997.

EN 933 — Tests for geometrical properties of aggregates, consists of the following parts:

- Part 1: Determination of particle size distribution — Sieving method;*
- *Part 2: Determination of particle size distribution — Test sieves, nominal size of apertures;*
- *Part 3: Determination of particle shape — Flakiness index;*
- *Part 4: Determination of particle shape — Shape index;*
- *Part 5: Determination of percentage of crushed and broken surfaces in coarse aggregate particles;*
- *Part 6: Assessment of surface characteristics — Flow coefficient of aggregates;*
- *Part 7: Determination of shell content — Percentage of shells for coarse aggregates;*
- *Part 8: Assessment of fines — Sand equivalent test;*
- *Part 9: Assessment of fines — Methylene blue test;*
- *Part 10: Assessment of fines — Grading of filler aggregates (air jet sieving);*
- *Part 11: Classification test for the constituents of coarse recycled aggregate.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard describes the reference washing and dry sieving method used for type testing and in case of dispute, for determination of the particle size distribution of aggregates. For other purposes, in particular factory production control, other methods may be used, provided that an appropriate working relationship with the reference method has been established. It applies to all aggregates, including lightweight aggregates, up to 90 mm nominal size, but excluding filler.

NOTE 1 The determination of the grading of fillers is specified in EN 933-10 *Assessment of fines — Grading of filler aggregates (air jet sieving)*.

NOTE 2 Dry sieving without washing may be used for aggregates free from particles which cause agglomeration.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 932-2, *Tests for general properties of aggregates — Part 2: Methods for reducing laboratory samples*

EN 932-5, *Tests for general properties of aggregates — Part 5: Common equipment and calibration*

EN 933-2, *Tests for geometrical properties of aggregates — Part 2: Determination of particle size distribution — Test sieves, nominal size of apertures*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 3310-2, *Test sieves — Technical requirements and testing — Part 2: Test sieves of perforated metal plate*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

aggregate

granular material used in construction which may be natural, manufactured or recycled

3.2

test portion

sample used as a whole in a single test

3.3

constant mass

mass determined by successive weighings performed at least 1 h apart and not differing by more than 0,1 %

NOTE In many cases constant mass can be achieved after a test portion has been dried for a pre-determined period in a specified oven (see 5.3) at $(110 \pm 5)^\circ\text{C}$. Test laboratories may determine the time required to achieve constant mass for specific types and sizes of sample dependent upon the drying capacity of the oven used.