

**Täitematerjalide geomeetriliste omaduste katsetamine.
Osa 3: Tera kuju määramine. Plaatsustegur**

**Tests for geometrical properties of aggregates - Part 3:
Determination of particle shape - Flakiness index**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 933-3:2012 sisaldab Euroopa standardi EN 933-3:2012 ingliskeelset teksti.	This Estonian standard EVS-EN 933-3:2012 consists of the English text of the European standard EN 933-3:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 18.01.2012.	Date of Availability of the European standard is 18.01.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.15

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

English Version

Tests for geometrical properties of aggregates - Part 3: Determination of particle shape - Flakiness index

Essais pour déterminer les caractéristiques géométriques
des granulats - Partie 3: Détermination de la forme des
granulats - Coefficient d'aplatissement

Prüfverfahren für geometrische Eigenschaften von
Gesteinskörnungen - Teil 3: Bestimmung der Kornform -
Plattigkeitskennzahl

This European Standard was approved by CEN on 29 October 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	6
5 Apparatus	6
6 Preparation of test portions	8
7 Procedure	8
7.1 Sieving on test sieves	8
7.2 Sieving on bar sieves	8
8 Calculation and expression of results	8
9 Test report	9
9.1 Mandatory data	9
9.2 Optional data	9
Annex A (informative) Example of test data sheet	10
Annex B (informative) Precision	11

Foreword

This document (EN 933-3:2012) has been prepared by Technical Committee CEN/TC 154 "Aggregates", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2012, and conflicting national standards shall be withdrawn at the latest by July 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 933-3:1997.

The following changes have been made to the previous edition:

- a) the CEN Technical Specification has been adopted as European Standard;
- b) the document has been editorially revised.

This standard forms part of a series of tests for geometrical properties of aggregates. Test methods for other properties are covered by the following European Standards:

EN 932 *Tests for general properties of aggregates;*

EN 1097 *Tests for mechanical and physical properties of aggregates;*

EN 1367 *Tests for thermal and weathering properties of aggregates;*

EN 1744 *Tests for chemical properties of aggregates;*

EN 13179 *Tests for filler aggregate used in bituminous mixtures.*

EN 933, *Tests for geometrical properties of aggregates*, consists of the following parts:

- *Part 1: Determination of particle size distribution — Sieving method;*
- *Part 2: Determination of particle size distribution — Test sieves, nominal size of apertures;*
Part 3: Determination of particle shape — Flakiness index;
- *Part 4: Determination of particle shape — Shape index;*
- *Part 5: Determination of percentage of crushed and broken surfaces in coarse aggregate particles;*
- *Part 6: Assessment of surface characteristics — Flow coefficient of aggregates;*
- *Part 7: Determination of shell content — Percentage of shells for coarse aggregates;*
- *Part 8: Assessment of fines — Sand equivalent test;*

- *Part 9: Assessment of fines — Methylene blue test;*
- *Part 10: Assessment of fines — Grading of filler aggregates (air jet sieving);*
- *Part 11: Classification test for the constituents of coarse recycled aggregate.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard describes the reference method, used for type testing and in case of dispute, for determination of the flakiness index of aggregates. For other purposes, in particular production control, other methods may be used, provided that an appropriate working relationship with the reference method has been established.

This European Standard applies to natural, manufactured or recycled aggregates.

The test procedure specified in this part of this European Standard is not applicable to particle sizes less than 4 mm or greater than 100 mm.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 932-2, *Tests for general properties of aggregates — Part 2: Methods for reducing laboratory samples*

EN 932-5, *Tests for general properties of aggregates — Part 5: Common equipment and calibration*

EN 933-1, *Tests for geometrical properties of aggregates — Part 1: Determination of particle size distribution — Sieving method*

EN 933-2, *Tests for geometrical properties of aggregates — Part 2: Determination of particle size distribution — Test sieves, nominal size of apertures*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

constant mass

mass determined by successive weighings performed at least 1 h apart and not differing by more than 0,1 %

Note 1 to entry: In many cases, constant mass can be achieved after a test portion has been dried for a pre-determined period in a specified oven (see 5.4) at (110 ± 5) °C. Test laboratories can determine the time required to achieve constant mass for specific types and sizes of sample dependent upon the drying capacity of the oven used.

3.2

laboratory sample

sample intended for laboratory testing

3.3

particle size fraction(d_i/D_i)

fraction of an aggregate passing the larger (D_i) of two sieves and retained on the smaller (d_i)

Note 1 to entry: The lower limit for d_i may be zero.

3.4

test portion

sample used as a whole in a single test