
**Plastics piping systems for water
supply and for drainage and sewerage
under pressure — Polyethylene (PE) —**

**Part 1:
General**

*Systèmes de canalisations en plastique destinés à l'alimentation
en eau et aux branchements et collecteurs d'assainissement sous
pression — Polyéthylène (PE) —*

Partie 1: Généralités



This document is a preview generated by ERS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	3
3.1 Geometrical terms.....	3
3.2 Material terms.....	5
3.3 Terms related to material characteristics.....	5
3.4 Terms related to service conditions.....	6
3.5 Terms related to joints.....	6
4 Symbols and abbreviated terms	7
4.1 Symbols.....	7
4.2 Abbreviated terms.....	7
5 Material	8
5.1 Material of the component.....	8
5.2 Compound.....	8
5.2.1 Additives and pigments.....	8
5.2.2 Colour.....	8
5.3 Physical characteristics of the compound.....	9
5.3.1 Characteristics of the compound in the form of granules.....	9
5.3.2 Characteristics of the compound in the form of pipe.....	10
5.4 Fusion compatibility.....	12
5.5 Classification and designation.....	13
6 Effects on water quality	13
Annex A (informative) Pressure reduction coefficient	14
Annex B (informative) Resistance to rapid crack propagation	15
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fitting and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*.

This second edition cancels and replaces the first edition (ISO 4427-1:2007), which has been technically revised. It also incorporates Technical Corrigendum ISO 4427-1:2007/Cor 1:2008 and Amendment ISO 4427-1:2007/Amd 1:2015.

The main changes compared to the previous edition are:

- update of the normative references;
- technical consistency with ISO 4437-1 (see Reference [1] in the Bibliography).

A list of all parts in the ISO 4427 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The ISO 4427 series of standards are a set of system standards that specify the requirements for a piping system and its components when made from polyethylene (PE). The piping system is intended to be used in buried or above ground applications, for the conveyance of water for human consumption, raw water prior to treatment, drainage and sewerage under pressure, vacuum sewer systems, and water for other purposes.

In respect of potential adverse effects on the quality of water intended for human consumption caused by the products covered by the ISO 4427 series, it does not provide information on the restriction on the use of products.

NOTE Guidance for assessment of conformity can be found in Reference [2] in the Bibliography.

Plastics piping systems for water supply and for drainage and sewerage under pressure — Polyethylene (PE) —

Part 1: General

1 Scope

This document specifies the general aspects of polyethylene (PE) compounds for the manufacture of pressure pipes and fittings (mains and service pipes) for buried or above ground applications, intended for the conveyance of:

- water for human consumption;
- raw water prior to treatment;
- drainage and sewerage under pressure;
- vacuum sewer systems;
- water for other purposes.

This document also specifies the test parameters and requirements for the test methods referred to in this document.

In conjunction with other parts of the ISO 4427 series, this document is applicable to PE pipes and fittings, their joints and to joints with components made of PE and other materials, intended to be used under the following conditions:

- a) a maximum allowable operating pressure (PFA) up to and including 25 bar¹⁾;
- b) an operating temperature of 20 °C as the reference temperature.

NOTE 1 For other operating temperatures, guidance is given in [Annex A](#).

The ISO 4427 series covers a range of maximum allowable operating pressures and gives requirements concerning colours.

NOTE 2 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and installation practices or codes.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3, *Preferred numbers — Series of preferred numbers*

ISO 472, *Plastics — Vocabulary*

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

1) 1 bar = 0,1 MPa = 10⁵ Pa; 1 MPa = 1 N/mm².

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 4427-2, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 2: Pipes*

ISO 4427-3, *Plastics piping systems for water supply, and for drainage and sewerage under pressure — Polyethylene (PE) — Part 3: Fittings*

ISO 6259-1, *Thermoplastics pipes — Determination of tensile properties — Part 1: General test method*

ISO 6259-3, *Thermoplastics pipes — Determination of tensile properties — Part 3: Polyolefin pipes*

ISO 6964, *Polyolefin pipes and fittings — Determination of carbon black content by calcination and pyrolysis — Test method*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*

ISO 11413, *Plastics pipes and fittings — Preparation of test piece assemblies between a polyethylene (PE) pipe and an electrofusion fitting*

ISO 11414, *Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test piece assemblies by butt fusion*

ISO 12162, *Thermoplastics materials for pipes and fittings for pressure applications — Classification, designation and design coefficient*

ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test)*

ISO 13478, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Full-scale test (FST)*

ISO 13479, *Polyolefin pipes for the conveyance of fluids — Determination of resistance to crack propagation — Test method for slow crack growth on notched pipes*

ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*

ISO 13954, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm*

ISO 15512, *Plastics — Determination of water content*

ISO 16871, *Plastics piping and ducting systems — Plastics pipes and fittings — Method for exposure to direct (natural) weathering*

EN 12099, *Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 3, ISO 472 and ISO 1043-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 Geometrical terms

3.1.1

nominal size

DN/OD

numerical designation of the size of a component related to the outside diameter

Note 1 to entry: It is a convenient round number approximately equal to the manufacturing dimension in millimetres (mm). It is not applicable to components designated by thread size.

3.1.2

nominal outside diameter

d_n

specified outside diameter assigned to a nominal size DN/OD

Note 1 to entry: Nominal outside diameter is expressed in millimetres.

3.1.3

outside diameter at any point

d_e

value of the measurement of the outside diameter through its cross-section at any point of the pipe, rounded to the next greater 0,1 mm

3.1.4

mean outside diameter

d_{em}

value of the measurement of the outer circumference of the pipe or spigot end of a fitting in any cross-section divided by π ($\approx 3,142$), rounded to the next greater 0,1 mm

3.1.5

minimum mean outside diameter

$d_{em,min}$

minimum value for the mean outside diameter as specified for a given nominal size

3.1.6

maximum mean outside diameter

$d_{em,max}$

maximum value for the mean outside diameter as specified for a given nominal size

3.1.7

out-of-roundness

ovality

difference between the maximum and the minimum outside diameters in the same cross-section of a pipe or spigot