

---

---

**Paints and varnishes — Lighting and  
procedure for visual assessments of  
coatings**

*Peintures et vernis — Éclairage et mode opératoire pour évaluations  
visuelles des revêtements*



This document is a preview generated by ERS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>1</b>
<b>6 Procedure for visual assessment</b> .....	<b>2</b>
6.1 General.....	2
6.2 Assessment in natural daylight.....	2
6.3 Assessment under artificial lighting.....	2
<b>7 Test report</b> .....	<b>2</b>
<b>Annex A (informative) Examples of applications</b> .....	<b>4</b>
<b>Bibliography</b> .....	<b>5</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 13076:2012), which has been technically revised. The main changes compared to the previous edition are as follows:

- addition of [Clause 2](#) on normative references;
- addition of [Clause 3](#) on terms and definitions;
- addition of a new light source, LED;
- addition of examples on the applications of this document in [Table A.1](#);
- complete editorial revision.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Paints and varnishes — Lighting and procedure for visual assessments of coatings

## 1 Scope

This document specifies the lighting and the procedure for the visual assessment of degraded areas, spots or other defects on or in coatings.

This document is not applicable to the visual comparison of colour, which can be assessed using ISO 3668.

NOTE See [Annex A](#) for examples of the possible applications of this document.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Principle

The panel is visually assessed under specified conditions of illumination for degraded areas, spots or other defects.

## 5 Apparatus

**5.1 Fluorescent lamp or dull LED (light-emitting diode)**, comprising a wide-angle light source with an aluminium-coated reflector positioned to reflect the light downwards (see [Figure 1](#)), a colour temperature of 6 500 K and a degree of colour rendering index (CRI) of 9 (corresponding to colour rendering class 1A, i.e. a CRI,  $R_a$ , of 90 to 100). This colour temperature is realized in the CIE standard illuminant D65, as described in CIE 15:2004.

NOTE 1 This colour temperature and colour rendering give the light colour 965.

NOTE 2 Physical relationship of luminance and luminous flux:  $1 \text{ lx} = 1 \text{ lm/m}^2$  and  $1 \text{ lm} = 1 \text{ cd} \cdot \text{sr}$ .