

**Metallkatted. Ülevaade poorsuskatsetest**

Metallic coatings - Review of porosity tests

This document is a preview generated by EVS

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

Käesolev Eesti standard EVS-EN ISO 10308:1999 sisaldab Euroopa standardi EN ISO 10308:1997 ingliskeelset teksti.

Standard on kinnitatud Eesti Standardikeskuse 12.12.1999 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.

Standard on kättesaadav Eesti standardiorganisatsioonist.

This Estonian standard EVS-EN ISO 10308:1999 consists of the English text of the European standard EN ISO 10308:1997.

This standard is ratified with the order of Estonian Centre for Standardisation dated 12.12.1999 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.

The standard is available from Estonian standardisation organisation.

ICS 25.220.40

katsed, katted, kindlakstegemine, metallkatted, määramine, pinna omadused, poorid, poorsus, vaatlused

### Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:  
Aru 10 Tallinn 10317 Eesti; [www.evs.ee](http://www.evs.ee); Telefon: 605 5050; E-post: [info@evs.ee](mailto:info@evs.ee)

### Right to reproduce and distribute belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without permission in writing from Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact Estonian Centre for Standardisation:  
Aru str 10 Tallinn 10317 Estonia; [www.evs.ee](http://www.evs.ee); Phone: 605 5050; E-mail: [info@evs.ee](mailto:info@evs.ee)

ICS 25.220.40

Descriptors: Metallic coatings, testing, porosity, review.

**English version**

**Metallic coatings**

Review of porosity tests  
(ISO 10308 : 1995)

Revêtements métalliques – Passage  
en revue des essais de porosité  
(ISO 10308 : 1995)

Metallische Überzüge – Übersicht der  
Porenprüfverfahren  
(ISO 10308 : 1995)

This European Standard was approved by CEN on 1997-06-22.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

**Central Secretariat: rue de Stassart 36, B-1050 Brussels**

## Foreword

International Standard

ISO 10308 : 1995 Metallic coatings – Review of porosity tests,

which was prepared by ISO/TC 107 ‘Metallic and other inorganic coatings’ of the International Organization for Standardization, has been adopted by Technical Committee CEN/TC 262 ‘Protection of metallic materials against corrosion’, the Secretariat of which is held by DIN, as a European Standard.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by January 1998 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard:

Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

## Endorsement notice

The text of the International Standard ISO 10308 : 1995 was approved by CEN as a European Standard without any modification.

NOTE: Normative references to international publications are listed in Annex ZA (normative).

## Contents

<b>1</b>	Scope.....	4
<b>2</b>	Normative references.....	4
<b>3</b>	Definitions .....	5
<b>4</b>	Principle .....	5
<b>5</b>	Common features of porosity tests .....	5
<b>6</b>	Test specimens .....	5
<b>7</b>	Specific porosity tests .....	5
<b>7.1</b>	Alizarin test.....	5
<b>7.2</b>	Anthraquinone test.....	5
<b>7.3</b>	Cadmium sulfide test .....	6
<b>7.4</b>	Copper sulfate (Preece) test.....	6
<b>7.5</b>	Copper sulfate (Dupernell) test .....	6
<b>7.6</b>	Corrodokote test (CORR) .....	6
<b>7.7</b>	Electrographic tests.....	6
<b>7.8</b>	Ferrocyanide test.....	7
<b>7.9</b>	Ferron test.....	7
<b>7.10</b>	Ferroxyl test .....	7
<b>7.11</b>	Flowers of sulfur porosity test .....	7
<b>7.12</b>	Hot water test .....	8
<b>7.13</b>	Hydrogen sulfide or sulfur dioxide/hydrogen sulfide test.....	8
<b>7.14</b>	Logwood test .....	8
<b>7.15</b>	Magneson test .....	8
<b>7.16</b>	Nitric acid vapour test.....	8
<b>7.17</b>	Oxine test.....	8
<b>7.18</b>	Permanganate test.....	9
<b>7.19</b>	Polysulfide test.....	9
<b>7.20</b>	Porotest test.....	9

<b>7.21</b>	Salt spray tests [neutral (NSS), acetic (AASS) and cuproacetic (CASS)].....	9
<b>7.22</b>	Sulfur dioxide test.....	9
<b>7.23</b>	Sulfurous acid/sulfur dioxide vapour test.....	9
<b>7.24</b>	Thiocyanate test .....	10
<b>7.25</b>	Thioacetamide test (TAA) .....	10
<b>7.26</b>	Watch case acetic acid test.....	10
<b>7.27</b>	Watch case sodium bisulfite test .....	10

## **Annexes**

<b>A</b>	Table of porosity tests .....	11
<b>B</b>	Typical report and evaluation of porosity tests.....	13
<b>B.1</b>	Report.....	13
<b>B.2</b>	Evaluation .....	13
<b>B.3</b>	Precision and bias .....	13
<b>C</b>	Schematic representation of types of pore .....	14
<b>D</b>	Classification of discontinuities in metallic and other inorganic coatings .....	15
<b>E</b>	Classification of methods of testing coating porosity .....	16
<b>F</b>	Alphabetical list of tests by substrate and coating .....	17
<b>G</b>	Bibliography .....	25
<b>ZA</b>	Normative references to international publications with their relevant European publications .....	27

## 1 Scope

This International Standard reviews published methods for revealing pores (see ISO 2080) and discontinuities in coatings of aluminium, anodized aluminium, brass, cadmium, chromium, cobalt, copper, gold, indium, lead, nickel, nickel-boron, nickel-cobalt, nickel-iron, nickel-phosphorus, palladium, platinum, vitreous or porcelain enamel, rhodium, silver, tin, tin-lead, tin-nickel, tin-zinc, zinc and chromate or phosphate conversion coatings (including associated organic films) on aluminium, beryllium-copper, brass, copper, iron, kovar (NiFeCo) alloys, magnesium, nickel, nickel-boron, nickel-phosphorus, phosphor-bronze, silver, steel, tin-nickel and zinc alloy base metal.

The tests summarized in this International Standard are designed to react with the substrate when exposed, by a discontinuity, in such a way as to form an observable reaction product.

### NOTES

1 Pores are usually perpendicular to the coating surface but may be inclined to the coating surface. They are frequently cylindrical in shape but may also assume a twisted shape (see annex C).

2 Porosity may vary in size from the submicroscopic, invisible under a light microscope, to the microscopic, visible from  $\times 10$  to  $\times 1\,000$ , to the macroscopic, visible to the naked eye.

3 Porosity may be visibly indicated by discoloration of the coated surface.

4 Porosity in a coating is not always detrimental. In microdiscontinuous chromium, for example, porosity or microcracking is required and tests are conducted to indicate the pores.

5 Results obtained from porosity tests expressed in terms such as pores per square centimetre are relative values related to the specific test method used and the magnification used during examination. Annex B gives typical report criteria.

## 2 Normative references

The following standards contain provisions which, through references in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards listed below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1456:1988, *Metallic coatings — Electrodeposited coatings of nickel plus chromium and of copper plus nickel plus chromium.*

ISO 2080:1981, *Electroplating and related processes — Vocabulary.*

ISO 2085:1976, *Anodizing of aluminium and its alloys — Check of continuity of thin anodic oxide coatings — Copper sulphate test.*

ISO 3160-2:1992, *Watch cases and accessories — Gold alloy coverings — Part 2: Determination of fineness, thickness, corrosion resistance and adhesion.*

ISO 4524-2:1985, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 2: Environmental tests.*

ISO 4524-3:1985, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 3: Electrographic tests for porosity.*

ISO 4525:1985, *Metallic coatings — Electroplated coatings of nickel plus chromium on plastics materials.*

ISO 4526:1984, *Metallic coatings — Electroplated coatings of nickel for engineering purposes.*



ISO 4527:1987, *Autocatalytic nickel-phosphorus coatings — Specification and test methods.*

ISO 4538:1978, *Metallic coatings — Thioacetamide corrosion test (TAA test).*

ISO 4540:1980, *Metallic coatings — Coatings cathodic to the substrate — Ratings of electroplated test specimens subjected to corrosion tests.*

ISO 4541:1978, *Metallic and other non-organic coatings — Corrodokote corrosion test (CORR test).*

ISO 6158:1984, *Metallic coatings — Electroplated coatings of chromium for engineering purposes.*

ISO 6988:1985, *Metallic and other non-organic coatings — Sulfur dioxide test with general condensation of moisture.*

ISO 9227:1990, *Corrosion tests in artificial atmospheres — Salt spray tests.*

ISO 10309:1994, *Metallic coatings — Porosity tests — Ferroxy test.*

### 3 Definitions

For the purposes of this International Standard, the definitions given in ISO 2080 as well as the following apply.

**3.1 discontinuities:** Cracks, micro-holes, pits, scratches or any other opening in the coating surface that exposes a different underlying metal.

For further information on discontinuities see annex D and reference [1] in annex G.

### 4 Principle

Porosity test results occur as chemical reaction end-products. Some occur *in situ*, others on paper or in a gel coating. Observations are made that are consistent with the test method and the items being tested as specified by the buyer. These may be visual inspections (naked eye) or at  $\times 10$  magnification (microscope). Other methods may involve enlarged photographs or photo-micrographs. See references [1, 2, 3, 5 and 6] in annex G (see also annex A for a tabular summary of the porosity tests and annex D for a classification of discontinuities).

### 5 Common features of porosity tests

Porosity tests differ from corrosion and ageing tests particularly concerning testing time. Porosity tests are

primarily short-time tests. A good porosity test process must clean, depolarize and activate the substrate metal exposed by the pore and attack it to such a degree as to cause the reaction product to fill the pore to the surface of the coating. Ideally, the corrosive provided for this should not react with the coating surface. It is essential that the time of reaction be limited, particularly with thin coatings, since the corrosive will attack the substrate in all directions and in so doing, will undermine the coatings such that false observations will be made. When the corrosion product is soluble in the reagent, the precipitating indicator is used to form the reaction product. (See annex E for classification of methods of porosity testing.)

## 6 Test specimens

Porosity tests are generally destructive in nature and are designed to assess the quality of the coating process of the substrate. Therefore, separate test specimens are not ordinarily allowed.

## 7 Specific porosity tests

### 7.1 Alizarin test

#### 7.1.1 Scope

For coatings of chromium (including Cr/Ni/Cu and Cr/Ni/Ni), cobalt, copper, nickel, nickel-boron, nickel-cobalt, nickel-iron and nickel-phosphorus on aluminium substrate.

#### 7.1.2 Summary of method

The test specimens are treated with sodium hydroxide, sodium alizarin sulfonate and glacial acetic acid under defined conditions. Formation of red markings or spots indicates porosity. Details of the test procedure can be found in ISO 4527. See also references [9, 31 and 37] in annex G.

### 7.2 Anthraquinone test

#### 7.2.1 Scope

For coatings of chromium (including Cr/Ni/Ni), cobalt, nickel, nickel-boron, nickel-cobalt, nickel-iron and nickel-phosphorus on aluminium, magnesium or zinc alloy substrates.

#### 7.2.2 Summary of method

The test specimens are treated with sodium hydroxide and potassium 1-aminoanthraquinone-2-carboxylic acid under defined conditions. Formation of red markings or spots indicates porosity. Details of the test procedure can be found in reference [13] in annex G.