

---

---

**Determination of the resistance  
to cryogenic spill of insulation  
materials —**

**Part 2:  
Vapour exposure**

*Détermination de la résistance des matériaux d'isolation thermique  
suite à un refroidissement cryogénique —*

*Partie 2: Phase vapeur*



This document is a preview generated by ERS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>Introduction</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Test configurations</b>	<b>2</b>
<b>5 Construction of the test apparatus and substrates</b>	<b>2</b>
5.1 Apparatus	2
5.2 Materials and tolerances	3
5.3 Release nozzle	3
5.3.1 Nozzle construction	3
5.3.2 Nozzle position	4
5.4 Test assembly supports	4
5.5 Test specimen and recirculation chamber	4
<b>6 Cryogenic spill protection materials</b>	<b>5</b>
6.1 General	5
6.2 Wet applied coating systems	6
6.3 Preformed system testing	6
<b>7 Instrumentation for test specimens</b>	<b>6</b>
7.1 General	6
7.2 Thermocouple location	6
<b>8 Test environment</b>	<b>7</b>
<b>9 Test procedure</b>	<b>7</b>
<b>10 Repeatability and reproducibility</b>	<b>8</b>
<b>11 Uncertainty of measurement</b>	<b>8</b>
<b>12 Test report</b>	<b>8</b>
<b>13 Practical applications of test results</b>	<b>9</b>
13.1 General	9
13.2 Performance criteria	10
13.2.1 General	10
13.2.2 Coatings and spray-applied materials — Substrate temperature	10
13.2.3 Systems and assemblies	10
13.3 Factors affecting the validity of the test	11
13.3.1 General	11
13.3.2 Failure at nozzle	11
13.3.3 Failure of thermocouples	11
<b>Annex A (normative) Methods for fixing thermocouples</b>	<b>12</b>
<b>Annex B (informative) Classification</b>	<b>13</b>
<b>Bibliography</b>	<b>15</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 9, *Liquefied natural gas installations and equipment*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 282, *Installation and equipment for LNG*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 20088 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

The test is intended to be, as far as practicable, representative of a potential accidental pressurised release of cryogenic LNG material manufactured in industrial plants. The test includes

- a) release from of cryogenic liquid under pressure, and
- b) scenarios where the conditions in the jet characterized predominantly by gaseous exposure.

Liquid jet release may be formed upon release of Liquified Natural Gas (LNG) from process equipment operating at pressure, e.g., some liquefaction processes utilise 40 - 60 bar operating pressure. However, at specific distances from the release point, it is expected that the liquid fraction will diminish such that there is practically no effect from liquid cooling in the stream.

This test is designed to give an indication of how cryogenic spill protection materials will perform in a sudden exposure to cryogenic jet where it is expected that little or no liquid fraction is present.

The dimensions of the test specimen might be smaller than typical items of structure and plant. The liquid cryogenic jet mass flow rates can be substantially less than that which might occur in a credible event. However, individual thermal loads imparted to the cryogenic spill protection materials, from the cryogenic release defined in the procedure described in this document, have been shown to be representative of areas exposed to a cryogenic LNG accidental release where little or no liquid is present.



# Determination of the resistance to cryogenic spill of insulation materials —

## Part 2: Vapour exposure

**CAUTION** — The attention of all persons concerned with managing and carrying out cryogenic spill testing is drawn to the fact that liquid nitrogen testing can be hazardous and that there is a danger of oxygen condensation (risk of explosion), receiving a 'cold burn' and/or the possibility that harmful gases (risk of anoxia) can be evolved during the test. Mechanical and operational hazards can also arise during the construction of the test elements or structures, their testing and disposal of test residues.

An assessment of all potential hazards and risks to health shall be made, and safety precautions shall be identified and provided. Appropriate training and Personal Protection Equipment (PPE) shall be given to relevant personnel.

The test laboratory is responsible for conducting an appropriate risk assessment in order to consider the impact of liquid and gaseous nitrogen exposure to equipment, personnel and the environment.

### 1 Scope

This document describes a method for determining the resistance of Cryogenic Spill Protection (CSP) systems to vapour generated from a cryogenic liquid release where the liquid content is practically zero. It is applicable where CSP systems are installed on carbon steel.

The test provided in this document is not applicable to high pressure cryogenic liquid releases that can be found in refrigeration circuits and in LNG streams immediately post-liquefaction.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 22899-1, *Determination of the resistance to jet fires of passive fire protection materials — Part 1: General requirements*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>