# **INTERNATIONAL STANDARD**

**ISO** 15096

> Third edition 2020-02

## Jewellery and precious metals — Determination of high purity silver — **Difference method using ICP-OES**

lerie thode pu. Joaillerie et métaux précieux — Dosage de l'argent à haute pureté —



Reference number ISO 15096:2020(E)



© ISO 2020

Vementation, no par hanical, includin requested fir All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents			Page	
Forev	vord		iv	
1	Scop	oe	1	
2	Norn	mative references	1	
3	Tern	ns and definitions	1	
4	Prin	ciple	1	
5	Reag	gents	1	
6	Apparatus		2	
7	Sampling		2	
8	Proc 8.1 8.2 8.3 8.4 8.5	General Sample solution Silver matrix calibration solutions (10 g/l) Aqua regia matrix calibration solutions Measurement	3 3 4	
9	9.1 9.2 9.3	ulation and expression of the results Calibration curves Calculation Repeatability	4 4 5	
10		report		
Anne	<b>x A</b> (in	nformative) Wavelengths	6	
Anne	<b>x B</b> (no	ormative) Determination of fineness of and above 999,9 ‰	7	
Biblio	ograph	hy	9	
		4		

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 174, *Jewellery and precious metals*.

This third edition cancels and replaces the second edition (ISO 15096:2014), which has been technically revised. The main changes compared to the previous edition are as follows:

- a) change of title of standard:
- b) change of scope for measuring also silver with a nominal content above 999 ‰ (parts per thousands);
- c) revision of this document in order to comply in structure with ISO 15093;

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

# Jewellery and precious metals — Determination of high purity silver — Difference method using ICP-OES

### 1 Scope

This document specifies the analytical procedure for the determination of silver with a nominal content of and above 999 ‰ (parts per thousand).

This document specifies a method intended to be used as the recommended method for the determination of silver of fineness of and above 999 ‰. For the determination of fineness of and above 999,9 ‰, modifications described in Annex B apply.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11596, Jewellery — Sampling of precious metal alloys for and in jewellery and associated products

#### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="http://www.iso.org/obp">http://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="http://www.electropedia.org/">http://www.electropedia.org/</a>

### 4 Principle

The sample is weighed and dissolved in nitric acid to prepare a 10~g/l solution (higher concentration is used for fineness of and above 999,9 ‰). The suspension, which can be present in that solution, is isolated by centrifugation or microfiltration and dissolved in aqua regia. Both nitric and aqua regia solutions are analysed separately by ICP-OES and the total content of each impurity (see Table A.1 for wavelengths) in the sample is obtained by adding together the results of the two analyses. The silver content is obtained by subtraction of the total content of impurities in the sample from 1 000 ‰. For the determination of fineness of and above 999,9 ‰, modifications described in Annex B shall be applied.

### 5 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

- **5.1 Hydrochloric acid** (HCl), 30 % to 37 % HCl (mass fraction).
- **5.2** Nitric acid (HNO<sub>3</sub>), 65 % to 70 % HNO<sub>3</sub> (mass fraction).
- **5.3** Aqua regia (should be prepared just before use). Mix three volumes of hydrochloric acid (5.1) and one volume of nitric acid (5.2).