

Bituminous mixtures - Test methods - Part 45:
Saturation Ageing Tensile Stiffness (SATS) conditioning
test

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12697-45:2020 sisaldab Euroopa standardi EN 12697-45:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 12697-45:2020 consists of the English text of the European standard EN 12697-45:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 26.02.2020.	Date of Availability of the European standard is 26.02.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 93.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Bituminous mixtures - Test methods - Part 45: Saturation Ageing Tensile Stiffness (SATS) conditioning test

Mélanges bitumineux - Méthodes d'essai - Partie 45 :
Essai de module en traction après saturation
conditionnée (SATS)

Asphalt - Prüfverfahren - Teil 45: Alterungsprüfung an
gesättigten Asphalt-Probekörpern (SATS-Prüfung)

This European Standard was approved by CEN on 18 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 Principle	5
5 Apparatus.....	5
5.1 Sample manufacture	5
5.2 Conditioning regime.....	5
5.3 Comparative test	9
6 Solvent and other materials.....	9
7 Sample preparation.....	9
8 Conditioning procedure.....	11
9 Comparative test procedure	12
10 Calculation	12
10.1 Bulk density and air voids content	12
10.2 Saturation before conditioning.....	13
10.3 Saturation after conditioning	13
10.4 Stiffness ratio.....	13
11 Test report.....	14
12 Precision.....	15
Bibliography.....	16

European foreword

This document (EN 12697-45:2020) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2020, and conflicting national standards shall be withdrawn at the latest by August 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-45:2012.

The following is a list of significant technical changes since the previous edition:

- the title no longer makes the method exclusively for hot mix asphalt;
- [ge] editorial update according to current standard template;
- [ge] dated references for test methods deleted in relevant places;
- [ge] NOTES modified and adjusted to normal text and vice versa where appropriate according to ISO/IEC Directives – Part 2:2016, 24.5;
- [Clause 1] irrelevant NOTE deleted, indicating a future development of alternative conditions not covered by this document;
- [Clause 2] titles for test methods EN 12697-serie adjusted;
- [Bibliography] test methods referred to in normal text moved to Clause 2 Normative references.

A list of all parts in the EN 12697 series can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document specifies a test method to assess the durability of adhesion in base and binder course asphalt mixtures. The Saturation Ageing Tensile Stiffness (SATS) conditioning regime is used to age the specimens in the presence of water. A comparative test for assessing their performance before and after conditioning is also conducted.

The applicability of this test method is limited to bituminous specimens with consistent air voids contents and hard binder, in particular, to asphalt concrete mixtures with a binder content between 3,5 % and 5,5 %, air voids contents between 6 % and 10 % and 10/20 pen hard paving grade bitumen.

The test is intended to be used as a screening test for the assessment of a combination of aggregate, filler and additives with respect to the retained adhesion properties after simulated ageing in a moist atmosphere for lean/stiff base and binder course mixtures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-5, *Bituminous mixtures — Test methods — Part 5: Determination of the maximum density*

EN 12697-6, *Bituminous mixtures — Test methods — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-8, *Bituminous mixtures — Test methods — Part 8: Determination of void characteristics of bituminous specimens*

EN 12697-26:2018, *Bituminous mixtures — Test methods — Part 26: Stiffness*

EN 12697-30, *Bituminous mixtures — Test methods — Part 30: Specimen preparation by impact compactor*

EN 12697-31, *Bituminous mixtures — Test methods — Part 31: Specimen preparation by gyratory compactor*

EN 12697-33, *Bituminous mixtures — Test method — Part 33: Specimen prepared by roller compactor*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12697-5, EN 12697-6 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

3.1

saturation before conditioning

saturation of the mixture, determined as the calculated proportion of air voids filled with water after partial vacuum saturation, prior to conditioning by storage under increased pressure and elevated temperature, in percent