

This document is a preview generated by EVS

Natural stone test methods - Determination of
resistance to salt crystallisation

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12370:2020 sisaldab Euroopa standardi EN 12370:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 12370:2020 consists of the English text of the European standard EN 12370:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 04.03.2020.	Date of Availability of the European standard is 04.03.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 73.020, 91.100.15

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Natural stone test methods - Determination of resistance to salt crystallisation

Méthodes d'essai pour pierres naturelles -
Détermination de la résistance à la cristallisation des
sels

Prüfverfahren für Naturstein - Bestimmung des
Widerstandes gegen Kristallisation von Salzen

This European Standard was approved by CEN on 1 December 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
Introduction.....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Symbols.....	5
5 Principle	5
6 Apparatus.....	5
7 Preparation of specimens	6
7.1 Sampling.....	6
7.2 Dimensions of test specimens	6
7.3 Washing	6
7.4 Drying.....	6
8 Procedure.....	6
9 Expression of results.....	7
10 Test report.....	7
Bibliography.....	9

European foreword

This document (EN 12370:2020) has been prepared by Technical Committee CEN/TC 246 “Natural stones”, the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2020, and conflicting national standards shall be withdrawn at the latest by September 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12370:1999.

The significant changes between this document and the previous edition are listed herewith:

- updating of Clause 8.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This document describes a test designed to assess the salt crystallization resistance of natural stones where it is relevant. The test cannot be used in isolation and results will be considered with other physical tests to indicate durability; these include EN 12371 "Determination of frost resistance".

This document is a preview generated by EVS

1 Scope

This document specifies a test method to assess the relative resistance of natural stones with an open porosity of greater than 5 %, measured in accordance with EN 1936, to damage caused by the crystallization of salts. The test is not necessary for low porosity stones.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12407, *Natural stone test methods — Petrographic examination*

EN 12440, *Natural stone — Denomination criteria*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

4 Symbols

For the purposes of this document, the following symbols apply.

M_d	is the mass of the dried specimen, in grams
M_{d1}	is the mass of the dried specimen with label before first cycle, in grams
M_f	is the mass of the dried specimen with label, after 15 cycles, in grams
ΔM	is the relative difference of masses before and after testing (mass loss or mass gain), in percent.

5 Principle

After drying to constant mass, the specimen is immersed in a solution of sodium sulphate, dried and allowed to cool to room temperature. This cycle is carried out 15 times and the percentage mass change measured.

6 Apparatus

- 6.1 A ventilated oven capable of maintaining a temperature of $(105 \pm 5) ^\circ\text{C}$
- 6.2 A weighing instrument capable of weighing the specimens to $\pm 0,001 \text{ g}$
- 6.3 A room or water bath capable of maintaining the temperature of the specimens and solution to $(20 \pm 0,5) ^\circ\text{C}$
- 6.4 A 14 % solution of sodium sulphate decahydrate (i.e. 14 g of $\text{Na}_2\text{SO}_4 \cdot 10 \text{ H}_2\text{O}$ for every 86 g de-ionized water). The density of this solution at $20 ^\circ\text{C}$ is $1\,055 \text{ kg/m}^3$.