
**Plastics — Differential scanning
calorimetry (DSC) —**

**Part 2:
Determination of glass transition
temperature and step height**

Plastiques — Analyse calorimétrique différentielle (DSC) —

*Partie 2: Détermination de la température et de la hauteur de palier
de transition vitreuse*



This document is a preview generated by ERS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus and materials	2
6 Test specimens	2
7 Test conditions and specimen conditioning	2
8 Calibration	2
9 Procedure	2
9.1 Setting up the apparatus	2
9.2 Loading the test specimen into the crucible	2
9.3 Insertion of crucibles	2
9.4 Temperature scan	2
10 Expression of results	3
10.1 Determination of glass transition temperatures	3
10.1.1 General	3
10.1.2 Equal-areas method	4
10.1.3 Half-step-height method	6
10.1.4 Inflection-point method	7
10.2 Determination of glass transition step height	8
11 Precision	8
12 Test report	8
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 11357-2:2013), which has been technically revised. The main changes compared to the previous edition are as follows:

- revision of definition of glass transition step height;
- correction of unit of glass transition step height;
- assessment of methods for determination of T_g ;
- revision of rounding of T_g ;
- strong restriction of re-using crucibles.

A list of all parts in the ISO 11357 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Differential scanning calorimetry (DSC) —

Part 2: Determination of glass transition temperature and step height

1 Scope

This document specifies methods for the determination of the glass transition temperature and the step height related to the glass transition of amorphous and partially crystalline plastics.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and ISO 11357-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

glass transition temperature

T_g
characteristic value of the temperature range over which the glass transition takes place

Note 1 to entry: The assigned glass transition temperature (T_g) may vary, depending on the specific property and on the method and conditions selected to measure it.

3.2

glass transition step height

$\Delta c_p(T_g)$
difference of specific heat capacity of the upper and lower extrapolated baselines at T_g

Note 1 to entry: See [Figure 1](#) and [Figure 2](#).

Note 2 to entry: For partially crystalline polymers, the glass transition step height is proportional to the amorphous content.

4 Principle

The principle is specified in ISO 11357-1.