

Timber structures - Testing of joints made with
mechanical fasteners - Requirements for timber density
(ISO 8970:2020)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 8970:2020 sisaldab Euroopa standardi EN ISO 8970:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 8970:2020 consists of the English text of the European standard EN ISO 8970:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 01.04.2020.	Date of Availability of the European standard is 01.04.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Timber structures - Testing of joints made with
mechanical fasteners - Requirements for timber density
(ISO 8970:2020)**

Structures en bois - Essai sur assemblages réalisés par
organes mécaniques - Exigences concernant la masse
volumique du bois (ISO 8970:2020)

Holzbauwerke - Prüfung von mechanischen
Verbindungen - Anforderungen an die Rohdichte des
Holzes (ISO 8970:2020)

This European Standard was approved by CEN on 13 March 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 8970:2020) has been prepared by Technical Committee ISO/TC 165 "Timber structures" in collaboration with Technical Committee CEN/TC 124 "Timber structures" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2020, and conflicting national standards shall be withdrawn at the latest by October 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 8970:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 8970:2020 has been approved by CEN as EN ISO 8970:2020 without any modification.

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols	1
5	Wood sampling method and requirements	1
5.1	General.....	1
5.2	Sampling method and requirements.....	2
6	Test report	2
Annex A (normative) Corrections to target conditions		4
Annex B (informative) Background information		6
Bibliography		9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 165, *Timber structures*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 124, *Timber structures*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 8970:2010), which has been technically revised.

The main changes compared to the previous edition are as follows:

In this edition the sampling method aims not only at ensuring that the selected pieces have a mean density comparable to the wood to which the test result is intended to be applied^[1], but also requiring the coefficient of variation of the density to be reflected. Only then the characteristic value of the strength determined by the test can be used directly^[2].

If it is not possible to obtain wood with the target mean value and variation of the wood density, the normative [Annex A](#) provides a correction method. The informative [Annex B](#) provides background to the correction procedure.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The sampling method given aims at ensuring that the selected pieces have a density distribution comparable to the timber to which the test result is intended to be applied. When this is fulfilled, the results can be used directly to determine the characteristic value of the strength parameter.

As it is often difficult to obtain a variation of the density similar to that allowed in a strength class, a correction method is given to obtain a corrected coefficient of variation for the strength parameter.

It should be kept in mind that the effect of density on the load-bearing capacity of connections is in many cases less significant than expected, and that many other parameters influence it.

Timber structures — Testing of joints made with mechanical fasteners — Requirements for timber density

1 Scope

This document specifies a method based on density, for the selection of pieces of wood used in determining the strength and stiffness properties of joints between members of structural timber made with mechanical fasteners. It is intended to be used in conjunction with a test standard specifying a test method.

It is assumed that the wood pieces are conditioned to the relevant conditions, that the wood density is normally distributed and that any deviations are reported.

This document is applicable only to specimens of structural timber.

NOTE It is emphasized that the wood density is only one of the properties that can influence the strength of a joint. Other relevant properties are, for example, growth-ring size and orientation, toughness and hardness.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13061-2, *Physical and mechanical properties of wood — Test methods for small clear wood specimens — Part 2: Determination of density for physical and mechanical tests*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Symbols

ρ is the density of a wood piece, expressed in kilograms per cubic metre.

5 Wood sampling method and requirements

5.1 General

The wood shall be at equilibrium at a relative humidity (RH) of $(65 \pm 5) \%$ and a temperature of $(20 \pm 2) ^\circ\text{C}$ at the time of testing. It shall be reported whether the wood was dried or moistened during the conditioning.

NOTE The moisture content at equilibrium is lower when reached by moistening than if reached by drying, which can affect the test results. The product test standard can specify if the equilibrium condition is to be reached through drying.