

ASFALTSEGUD. KATSEMEETODID. OSA 6:
ASFALTPROOVIKEHADE MAHUMASSI MÄÄRAMINE

Bituminous mixtures - Test methods - Part 6:
Determination of bulk density of bituminous specimens

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12697-6:2020 sisaldab Euroopa standardi EN 12697-6:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 12697-6:2020 consists of the English text of the European standard EN 12697-6:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 26.02.2020.	Date of Availability of the European standard is 26.02.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 93.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Bituminous mixtures - Test methods - Part 6: Determination of bulk density of bituminous specimens

Mélanges bitumineux - Méthodes d'essai - Partie 6 :
Détermination de la masse volumique apparente des
éprouvettes bitumineuses

Asphalt - Prüfverfahren - Teil 6: Bestimmung der
Raumdichte von Asphalt-Probekörpern

This European Standard was approved by CEN on 18 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	6
5 Materials	6
5.1 General.....	6
5.2 Additional materials for the sealed specimen procedure.....	6
6 Apparatus	6
6.1 General.....	6
6.2 Additional apparatus for the dry, SSD and sealed specimen procedures.....	6
6.3 Additional apparatus for the SSD-procedure.....	7
6.4 Additional apparatus for the dimensions procedure.....	7
7 Sample sizes and sample handling	7
8 Preparation of sample	7
9 Procedure	7
9.1 General.....	7
9.2 Procedure A: Bulk density — dry.....	7
9.3 Procedure B: Bulk density — Saturated surface dry (SSD).....	8
9.4 Procedure C: Bulk Density — Sealed specimen.....	8
9.5 Procedure D: Bulk density by dimensions.....	9
10 Calculation	9
10.1 Procedure A: Bulk density — dry.....	9
10.2 Procedure B: Bulk density — SSD.....	9
10.3 Procedure C: Bulk density — Sealed specimen.....	10
10.4 Procedure D: Bulk density by dimensions.....	10
10.4.1 Cylindrical specimen.....	10
10.4.2 Rectangular specimen.....	11
11 Precision	11
11.1 General.....	11
11.2 Repeatability (same observer — same apparatus).....	11
11.3 Reproducibility (different observers — different apparatus).....	11
12 Test report	12
Annex A (informative) General guidance on selection of a test procedure to determine the bulk density of compacted bituminous materials	13
A.1 General.....	13
A.2 Background (see Figure A.1).....	13
A.3 Guidance.....	14
Bibliography	16

European foreword

This document (EN 12697-6:2020) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2020, and conflicting national standards shall be withdrawn at the latest by August 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-6:2012.

The following is a list of significant technical changes since the previous edition:

- the title no longer makes the method exclusively for hot mix asphalt;
- [ge] editorial update according to current standard template;
- [ge] NOTES adjusted according to ISO/IEC Directives – Part 2:2016, 24.5;
- [Clause 2] correction of title for EN 12697-29. Reference to EN 13108-20 deleted;
- [6.1.1] description of accuracy for balance amended to; "With an accuracy of at least 0,1 g for masses up to 5 kg, and 1 g for masses over 5 kg. (Ref. EN 12697-38);
- [6.2.2] description added for accuracy of thermometer to $\pm 0,5$ °C (Ref. EN 12697-38);
- [6.4.1] dated reference of EN 12697-29 deleted;
- [9.3 f)] clarified that also procedure D may be applicable;
- [9.4 a)] amended to include procedure when damp specimen is tested;
- [9.4 c)] added reference to 5.2 Additional materials for the sealed specimen procedure;
- [11.1] editorial: $\sigma_R = (8 - 28)$ amended to read $\sigma_R = (8 \text{ to } 28)$ and $R = (22 - 82)$ amended to read $R = (22 \text{ to } 82)$;
- [A.1] reference to EN 13108-20 deleted;
- [A.2] new NOTE 2 added referring to relevant ASTM methods;
- [A.3 a)] completed with limitation for procedure A, up to void content 7 %;
- [A.3 b)] limitation for procedure A, amended to void content 7 %;
- [A.3 c)] air voids level amended from 15 % to 10 %;
- [A.3 c)] sentence, stating that procedure C is less convenient and rarely used, deleted;
- [A.3 d)] air voids level amended from 15 % to 10 %.

A list of all parts in the EN 12697 series can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This document specifies test methods for determining the bulk density of a compacted bituminous specimen. The test methods are intended for use with laboratory compacted specimens or specimens from the pavement after placement and compacting, either by coring or sawing.

This document specifies the following four procedures, the choice of which is used being dependent on the estimated content and accessibility of voids in the specimen:

- a) bulk density — dry (for specimens with a very closed surface);
- b) bulk density — saturated surface dry (SSD) (for specimens with a closed surface);
- c) bulk density — sealed specimen (for specimens with an open or coarse surface);
- d) bulk density by dimensions (for specimens with a regular surface and with geometric shapes, i.e. squares, rectangles, cylinders, etc.).

NOTE Annex A (informative) gives general guidance on selecting the appropriate procedure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-29, *Bituminous mixtures — Test methods — Part 29: Determination of the dimensions of a bituminous specimen*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

3.1

bulk density

mass per unit volume, including the air voids, of a specimen at known test temperature

3.2

maximum density

mass per unit volume, without air voids, of a bituminous mixture at known test temperature