
**Plastics — Determination of total
luminous transmittance and
reflectance**

*Plastiques — Détermination de la transmission lumineuse totale et de
la réflectance*



This document is a preview generated by EBS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Apparatus.....	2
6 Specimen.....	3
7 Conditioning.....	4
8 Procedure.....	4
9 Calculation procedure.....	5
10 Precision.....	5
11 Expression of results.....	5
12 Test report.....	6
Annex A (informative) Measurement examples of total luminous transmittance and total luminous reflectance.....	7
Annex B (informative) Derivation of formulae.....	10
Bibliography.....	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document specifies not only the total luminous transmittance of colourless and transparent plastics that have been covered by ISO 13468-1, but also specifies the transmittance of translucent materials such as opal sheets and the reflectance of materials such as translucent and/or opaque sheets or films.

Plastics — Determination of total luminous transmittance and reflectance

1 Scope

This document specifies the determination of total luminous transmittance and total luminous reflectance on clear, translucent or opaque plastics. Specimen shapes include moulded plaque or discs, films and sheets.

Fluorescent plastics and chromatic colour plastics are not covered by this document.

NOTE The scope of ISO 13468-1 shows that ISO 13468-1 covers planar transparent and substantially colourless plastics. The method in this document provide the way to trap diffused light and covers to measure translucent and opaque plastics.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO/CIE 11664-1, *Colorimetry — Part 1: CIE standard colorimetric observers*

ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

total luminous transmittance

τ_t

ratio of the transmitted luminous flux to the incident luminous flux when a collimated beam of light passes through a specimen

3.2

total luminous reflectance

ρ_t

ratio of the reflected luminous flux to the incident luminous flux when a collimated beam of light reflected on a specimen

4 Principle

When evaluating the total luminous transmittance of light diffusing material, the scattered light will go toward the edge of the specimen by its light diffusing property. This method intends to collect scattered