Plastics - Sulfone polymer moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 24025-2:2020)



#### EESTI STANDARDI EESSÕNA

#### NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 24025-2:2020 sisaldab Euroopa standardi EN ISO 24025-2:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 24025-2:2020 consists of the English text of the European standard EN ISO 24025-2:2020.	
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.	
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 27.05.2020.	Date of Availability of the European standard is 27.05.2020.	
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.	

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

#### ICS 83.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Koduleht <u>www.evs.ee</u>; telefon 605 5050; e-post <u>info@evs.ee</u>

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

# **EUROPEAN STANDARD**

### NORME EUROPÉENNE

**EUROPÄISCHE NORM** 

May 2020

**EN ISO 24025-2** 

ICS 83.080.20

Supersedes EN ISO 25137-2:2017

#### **English Version**

#### Plastics - Sulfone polymer moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 24025-2:2020)

Plastiques - Matériaux à base de polymères sulfone pour moulage et extrusion - Partie 2: Préparation des éprouvettes et détermination des propriétés (ISO 24025-2:2020)

Kunststoffe - Sulfonpolymer-Werkstoffe für das Spritzgießen und die Extrusion - Teil 2: Herstellung von Probekörpern und Bestimmung von Eigenschaften (ISO 24025-2:2020)

This European Standard was approved by CEN on 16 May 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

#### **European foreword**

This document (EN ISO 24025-2:2020) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2020, and conflicting national standards shall be withdrawn at the latest by November 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 25137-2:2017.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

#### **Endorsement notice**

The text of ISO 24025-2:2020 has been approved by CEN as EN ISO 24025-2:2020 without any modification.

	ontents	Page
Fore	eword	iv
1	Scope	
2	Normative references	1
3	Terms and definitions	2
4	Preparation of test specimens	
	4.1 General	
	4.2 Treatment of the material before moulding	3
5	Conditioning of test specimens	
6	Determination of properties	
Bibl	liography	6
	This a protein a	
© ISO	50 2020 – All rights reserved	iii

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 24025-2 cancels and replaces ISO 25137-2:2009, which has been technically revised.

The main changes compared to the previous edition are as follows:

- the normative references have been updated to the latest version;
- <u>Clause 3</u> has been added;
- <u>Table 2</u> has been updated according to the revised ISO 10350-1;
- three properties have been added: moulding shrinkage, luminous transmittance, yellowness index.

A list of all parts in the ISO 24025 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

### Plastics — Sulfone polymer moulding and extrusion materials —

#### Part 2:

## Preparation of test specimens and determination of properties

#### 1 Scope

- **1.1** This document specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of sulfone polymer moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.
- **1.2** Procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize sulfone polymer moulding and extrusion materials are listed.
- **1.3** The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this document, as are the designatory properties specified in ISO 24025-1.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, Plastics — Determination of water absorption

ISO 75-2, Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite

ISO 178, Plastics — Determination of flexural properties

ISO 179-1, Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test

ISO 179-2, Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test

ISO 291, Plastics — Standard atmospheres for conditioning and testing

ISO 294-1, Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens

ISO 294-3, Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates

ISO 294-4, Plastics — Injection moulding of test specimens of thermoplastic materials — Part 4: Determination of moulding shrinkage

ISO 306, Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)

ISO 527-2, Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics

ISO 899-1, Plastics — Determination of creep behaviour — Part 1: Tensile creep

ISO 1133-1, Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method

ISO 1183-1, Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method

ISO 4589-2, Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test

ISO 8256, Plastics — Determination of tensile-impact strength

ISO 10350-1, Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials

ISO 11357-2, Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and glass transition step height

ISO 15512, Plastics — Determination of water content

ISO 17223, Plastics — Determination of yellowness index and change in yellowness index

ISO 20753, Plastics — Test specimens

ISO 26723, Plastics — Determination of total luminous transmittance and reflectance

IEC 60112, Method for the determination of the proof and the comparative tracking indices of solid insulating materials

IEC 60243-1, Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies

IEC 60296, Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and Switchgear

IEC 60695-11-10, Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods

IEC 62631-2-1, Dielectric and resistive properties of solid insulating materials — Part 2-1: Relative permittivity and dissipation factor — Technical frequencies (0.1 Hz to 10 MHz) — AC Methods

IEC 62631-3-1, Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method

IEC 62631-3-2, Dielectric and resistive properties of solid insulating materials — Part 3-2: Determination of resistive properties (DC methods) — Surface resistance and surface resistivity

#### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="http://www.electropedia.org/">http://www.electropedia.org/</a>