

ASFALTSEGUD. KATSEMEETODID. OSA 1: LAHUSTUVA  
SIDEAINE SISALDUS

Bituminous mixtures - Test methods - Part 1: Soluble  
binder content

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

|   |  |
|---|--|
| See Eesti standard EVS-EN 12697-1:2020 sisaldab Euroopa standardi EN 12697-1:2020 ingliskeelset teksti.             | This Estonian standard EVS-EN 12697-1:2020 consists of the English text of the European standard EN 12697-1:2020.                  |
| Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.  | This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation. |
| Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 11.03.2020. | Date of Availability of the European standard is 11.03.2020.   |
| Standard on kättesaadav Eesti Standardikeskusest.   | The standard is available from the Estonian Centre for Standardisation.  |

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 93.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

## Bituminous mixtures - Test methods - Part 1: Soluble binder content

Mélanges bitumineux - Méthodes d'essai - Partie 1 :  
Teneur en liant soluble

Asphalt - Prüfverfahren - Teil 1: Löslicher  
Bindemittelgehalt

This European Standard was approved by CEN on 18 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

| <b>Contents</b>  | <b>Page</b> |
|--|-------------|
| European foreword.....   | 5           |
| Introduction .....   | 7           |
| 1 Scope.....   | 8           |
| 2 Normative references.....  | 8           |
| 3 Terms and definitions .....  | 8           |
| 4 Preparation of laboratory samples .....                                  | 10          |
| 5 Determination of binder content .....                                    | 10          |
| 5.1 General principles of test .....                                       | 10          |
| 5.2 Binder extraction .....  | 10          |
| 5.2.1 Solvent.....   | 10          |
| 5.2.2 Apparatus.....   | 11          |
| 5.2.3 Procedure.....   | 11          |
| 5.3 Separation of mineral matter .....                                     | 11          |
| 5.3.1 Apparatus.....   | 11          |
| 5.3.2 Procedure.....   | 11          |
| 5.4 Binder quantity.....   | 12          |
| 5.4.1 Apparatus.....   | 12          |
| 5.4.2 Procedure.....   | 12          |
| 5.5 Calculation and expression of results.....                             | 12          |
| 5.5.1 General.....   | 12          |
| 5.5.2 Binder content determined by difference.....                         | 12          |
| 5.5.3 Binder content by total recovery.....                                | 12          |
| 5.5.4 Binder content by recovery from portion (volume calculation) .....   | 13          |
| 5.5.5 Binder content by recovery from portion (mass calculation) .....     | 13          |
| 6 Drying to constant mass .....  | 14          |
| 6.1 General.....   | 14          |
| 6.2 Apparatus.....   | 14          |
| 6.3 Procedure.....   | 14          |
| 7 Reporting of results.....  | 14          |
| 7.1 Results.....   | 14          |
| 7.2 Test report.....   | 15          |
| 8 Precision data.....  | 15          |
| 8.1 General.....   | 15          |
| 8.2 Precision — Experiment 1 .....   | 15          |
| 8.3 Precision — Experiment 2 .....   | 16          |
| 8.4 Precision — Experiment 3 .....   | 17          |
| 8.5 Precision — Experiment 4 .....   | 17          |
| 8.6 Precision — Experiment 5 .....   | 17          |
| Annex A (informative) Guidance on the determination of binder content..... | 18          |
| A.1 Evaluation of the results.....   | 18          |
| A.2 Effect of water content .....  | 19          |
| A.3 Choice of test equipment and the sequence of operations.....           | 19          |

|   |  |    |
|---|--|----|
| A.4   | Determination of total binder content.....                               | 19 |
| Annex B (normative) Use of equipment for the determination of binder content .....  |  | 21 |
| B.1   | Binder extraction.....   | 21 |
| B.1.1   | Hot extractor (paper filter) method .....                                | 21 |
| B.1.2   | Hot extractor (wire mesh filter) method .....                            | 26 |
| B.1.3   | Soxhlet extractor method .....   | 27 |
| B.1.4   | Bottle rotation machine method.....                                      | 29 |
| B.1.5   | Centrifuge extractor method .....  | 32 |
| B.1.6   | Cold mix dissolution of bitumen by agitation.....                        | 34 |
| B.1.7   | Automatic extractor method .....   | 35 |
| B.2   | Separation of mineral matter.....  | 36 |
| B.2.1   | Continuous flow centrifuge.....  | 36 |
| B.2.2   | Pressure filter .....  | 38 |
| B.2.3   | Bucket type centrifuge — Type 1.....                                     | 39 |
| B.2.4   | Bucket type centrifuge — Type 2.....                                     | 41 |
| B.3   | Soluble binder content .....   | 41 |
| B.3.1   | Method by recovery from a portion using a volume calculation.....        | 41 |
| B.3.2   | Method by recovery from a portion using a mass calculation.....          | 44 |
| Annex C (normative) Determination of residual mineral matter in the binder extract by incineration .....                  |  | 45 |
| C.1   | General .....  | 45 |
| C.2   | Method 1 .....   | 45 |
| C.2.1   | Apparatus .....  | 45 |
| C.2.2   | Reagent.....   | 45 |
| C.2.3   | Procedure .....  | 45 |
| C.3   | Method 2 .....   | 46 |
| C.3.1   | Apparatus .....  | 46 |
| C.3.2   | Procedure .....  | 46 |
| Annex D (informative) Guidance on determination of soluble binder content of mixtures with polymer-modified binders ..... |  | 48 |
| D.1   | General .....  | 48 |
| D.2   | Preparatory treatment of laboratory samples of bituminous mixtures ..... | 48 |
| D.3   | Determination of binder content.....                                     | 48 |
| D.3.1   | General principles of test.....  | 48 |
| D.3.2   | Binder extraction.....   | 48 |
| D.3.3   | Separation of mineral matter.....  | 50 |
| D.3.4   | Binder quantity .....  | 51 |

**D.3.5 Calculation and expression of results..... 51**

**D.4 Drying to constant mass ..... 51**

**D.5 Reporting of results..... 51**

**D.6 Precision data..... 51**

**Bibliography..... 52**

## European foreword

This document (EN 12697-1:2020) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2020, and conflicting national standards shall be withdrawn at the latest by September 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-1:2012.

The following is a list of significant technical changes since the previous edition:

- the title no longer makes the method exclusively for hot mix asphalt;
- [ge] editorial update according to current standard template;
- [ge] NOTES modified or adjusted to normal text where appropriate according to ISO/IEC Directives – Part 2:2016, 24.5;
- [ge] the wording “accuracy of” has been altered to “to the nearest” in relevant procedures;
- [ge] The unit  $\text{mm}^3 \times 10^3 \text{mm}^3$  corrected to  $\text{cm}^3$ ;
- [Clause 2 and 5.3.2.4] EN 933-1 replaced by EN 12697-2;
- [Clause 4] Title amended to read: Preparation of laboratory samples. Completed with description for mixtures with high mineral matter content;
- [5.2.2.1], [6.2.2] and [B.1.7.1.6] accuracy for balance of 0,05 % amended to  $\pm 0,1 \text{ g}$ ;
- [5.2.3.1] clause deleted (superfluous). Following clauses renumbered accordingly;
- [5.5.2 to 5.5.5] Titles amended for clarification;
- [6.1] completed with observation about influence of water for the result of binder content;
- [8.2.2 and 8.2.3] dated reference deleted for EN 12697-28:2000;
- [8.6] new clause about precision of automatic devices;
- [Figure A.1] new figure introduced. Completed with Automatic extractor method. Minor editorial corrections;
- [B.1.5.1.5] table with dimensions related to Figure B.7 has been corrected in accordance with figure;
- [B.1.7] procedure for automatic extractor method included;
- [B.2.1.1.1] acceleration amended to  $25\,000 \text{ m/s}^2$  for consistency with EN 12697-3;

- [C.2.1.1.1] accuracy of balance amended to read  $\pm 1$  mg;
- [C.2.1.5] capacity of ignitions dishes clarified: **Ignition dish**, of at least 125 cm<sup>3</sup> capacity;
- [C.3.1.1] accuracy of balance, amended to read  $\pm 10$  mg;
- [Bibliography] updated.

A list of all parts in the EN 12697 series can be found on the CEN website

WARNING — The method described in this document may require the use of dichloromethane (methylene chloride), 1,1,1-trichloroethane, benzene, trichloroethylene, xylene, toluene, perchloroethylene (tetrachloroethylene) or other solvents capable of dissolving bitumen. These solvents are hazardous to health and are subject to occupational exposure limits as detailed in relevant legislation and regulations.

Exposure levels are related to both handling procedures and ventilation provision and it is emphasized that adequate training should be given to staff employed in the usage of these substances.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



## Introduction

This document describes a unified approach to the examination of bituminous mixtures that allows some divergence in the detail of procedures followed by individual laboratories. In Clause 5 of this document, a description is given of the basic operations that together form the test method for the proper determination of the binder content of bituminous mixtures. Guidance on the test method is given in Annex A and Figure A.1, while the use of alternative items of equipment that are equally suitable for carrying out particular parts of the test method are described in Annex B. Although the apparatus specified for the separation of mineral filler from the binder solution obtained after extraction is of a suitably efficient level not to affect the precision of the test described in Clause 8, a method for determining the amount of residual mineral matter in the extract is given in Annex C for use in those particular cases where some doubt may exist.

Methods and equipment other than those described in Annex B and Annex C, including automated equipment, are permissible provided that they have been demonstrated to provide the same results as one of the methods in Annex B or Annex C within the limits of the precision given in this document. Guidance on determination of soluble binder content of mixtures with polymer-modified binders is given in Annex D.

## 1 Scope

This document describes test methods for the determination of the soluble binder content of samples of bituminous mixtures.

The test methods described are suitable for quality control purposes during the production of plant mix and for checking compliance with a product specification.

For the analysis of mixtures containing modified binders, the guidance of Annex D should be followed.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-2, *Bituminous mixtures — Test methods — Part 2: Determination of particle size distribution*

EN 12697-3, *Bituminous mixtures — Test methods — Part 3: Bitumen recovery: Rotary evaporator*

EN 12697-4, *Bituminous mixtures — Test methods — Part 4: Bitumen recovery: Fractionating column*

EN 12697-14, *Bituminous mixtures — Test methods — Part 14: Water content*

EN 12697-28, *Bituminous mixtures — Test methods — Part 28: Preparation of samples for determining binder content, water content and grading*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 3310-2, *Test sieves — Technical requirements and testing — Part 2: Test sieves of perforated metal plate*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

### 3.1 soluble binder content

percentage by mass of extractable binder in an anhydrous sample, determined by extracting the binder from the sample

### 3.2 insoluble binder content

percentage by mass of binder that adheres to the aggregate particles after extraction