

Ferronickel - Specification and delivery requirements
(ISO 6501:2020)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 6501:2020 sisaldab Euroopa standardi EN ISO 6501:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 6501:2020 consists of the English text of the European standard EN ISO 6501:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.06.2020.	Date of Availability of the European standard is 17.06.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.100

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Ferronickel - Specification and delivery requirements (ISO
6501:2020)**

Ferro-nickel - Spécifications et conditions de livraison
(ISO 6501:2020)

Ferronickel - Spezifikation und Lieferbedingungen (ISO
6501:2020)

This European Standard was approved by CEN on 4 April 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 6501:2020) has been prepared by Technical Committee ISO/TC 155 "Nickel and nickel alloys" in collaboration with CCMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2020, and conflicting national standards shall be withdrawn at the latest by December 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 26501:1992.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6501:2020 has been approved by CEN as EN ISO 6501:2020 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Information for ordering	2
5 Requirements	2
5.1 Chemical composition	2
5.2 Form of delivery and formation of lots	3
5.2.1 General.....	3
5.2.2 Ferronickel in ingots.....	3
5.2.3 Ferronickel in pieces.....	3
5.2.4 Ferronickel in the form of shot.....	4
5.3 Contamination.....	4
6 Control	4
6.1 General.....	4
6.2 Sampling for analysis.....	4
6.3 Analysis.....	4
6.3.1 Ferronickel furnished with analysis certificate.....	4
6.3.2 Ferronickel settled with exchange analysis.....	4
6.4 Procedures in case of dispute.....	5
6.4.1 General.....	5
6.4.2 Contradictory procedure.....	5
6.4.3 Arbitration procedure.....	5
Annex A (informative) Examples of ferronickel classification	6

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC SS M14, *Nickel*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 6501:1988), which has been technically revised. The main changes compared with the previous edition are as follows:

- expressions such as “agreement between parties” have been reduced or eliminated (because if a standard or part of it is to be agreed, there is no need for that International Standard);
- the ferronickel delivery market requirements have been updated;
- FeNi classification has been clarified according chemical composition and combination of Ni content ([Table 1](#)) and impurities ([Table 2](#)); this was previously in one table.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Ferronickel — Specification and delivery requirements

1 Scope

This document specifies the technical delivery requirements for the various forms of ferronickel (ingots, pieces and shot) usually supplied for steel making and foundry use.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6352, *Ferronickel — Determination of nickel content — Dimethylglyoxime gravimetric method*

ISO 8049, *Ferronickel shot — Sampling for analysis*

ISO 8050, *Ferronickel ingots or pieces — Sampling for analysis*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

ferronickel

master alloy of iron and nickel having a nickel content equal to or greater than a mass fraction of 15 % and less than a mass fraction of 80 %, obtained from oxide ores or other nickel-bearing materials

3.2

K

number that represents the lowest nickel content that is part of the lot to be delivered

3.3

splitting limit

maximum acceptable difference between analytical results of nickel or other element agreed by two parties (buyer and seller)

3.4

lot

discrete and defined quantity of ferronickel ingots, pieces or shots answering to the same quality specification (chemical composition and physical characteristics)