

ASFALTSEGUD. KATSEMEETODID. OSA 34: MARSHALLI  
KATSE

Bituminous mixtures - Test methods - Part 34: Marshall  
test

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12697-34:2020 sisaldb Euroopa standardi EN 12697-34:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 12697-34:2020 consists of the English text of the European standard EN 12697-34:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 26.02.2020.	Date of Availability of the European standard is 26.02.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 93.080.20

Standardite reproduutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN 12697-34

February 2020

ICS 93.080.20

Supersedes EN 12697-34:2012

English Version

Bituminous mixtures - Test methods - Part 34: Marshall  
test

Mélanges bitumineux - Méthodes d'essai - Partie 34 :  
Essai Marshall

Asphalt - Prüfverfahren - Teil 34: Marshall-Prüfung

This European Standard was approved by CEN on 18 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## Contents

	Page
<b>European foreword.....</b>	<b>3</b>
<b>1 Scope.....</b>	<b>4</b>
<b>2 Normative references.....</b>	<b>4</b>
<b>3 Terms and definitions .....</b>	<b>4</b>
<b>4 Principle .....</b>	<b>5</b>
<b>5 Apparatus.....</b>	<b>5</b>
<b>6 Procedure.....</b>	<b>6</b>
<b>6.1 Specimen preparation.....</b>	<b>6</b>
<b>6.2 Test procedure.....</b>	<b>6</b>
<b>7 Expression of results.....</b>	<b>7</b>
<b>8 Test report.....</b>	<b>7</b>
<b>9 Precision.....</b>	<b>8</b>
<b>Annex A (normative) Marshall stability and flow values.....</b>	<b>9</b>
<b>Annex B (normative) Testing head.....</b>	<b>10</b>
<b>Bibliography.....</b>	<b>11</b>

## European foreword

This document (EN 12697-34:2020) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2020, and conflicting national standards shall be withdrawn at the latest by August 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-34:2012.

The following is a list of significant technical changes since the previous edition:

- the title no longer makes the method exclusively for hot mix asphalt;
- [ge] editorial update according to current standard template;
- [Clause 2] titles for test methods EN 12697-series adjusted, reference EN ISO 7500-1:2018, Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500 1:2018) replaced by: EN ISO 7500-1:2018, Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system (ISO 7500-1:2018);
- [6.1.1 and 6.2.4] NOTES modified according to ISO/IEC Directives – Part 2:2016, 24.5;
- [7.1] correction of Formula (1). Factor  $v$  realigned as exponent;
- [Bibliography] EN 12697-35 deleted. Referred to in Clause 2 Normative references.

A list of all parts in the EN 12697 series can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This document specifies a test method for determining the stability, flow and the Marshall quotient values of specimens of bituminous mixtures mixed according to EN 12697-35 and prepared using the impact compactor method of test EN 12697-30. It is limited to dense graded asphalt concrete and hot rolled asphalt.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-6, *Bituminous mixtures — Test methods — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-29, *Bituminous mixtures — Test method — Part 29: Determination of the dimensions of a bituminous specimen*

EN 12697-30, *Bituminous mixtures — Test methods — Part 30: Specimen preparation by impact compactor*

EN 12697-35, *Bituminous mixtures — Test methods — Part 35: Laboratory mixing*

EN ISO 7500-1:2018, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system (ISO 7500-1:2018)*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

### 3.1

#### stability

*S*

maximum load, in kilonewtons (kN), of a moulded asphalt specimen

### 3.2

#### flow

*F*

deformation of the moulded specimen in millimetres (mm) at maximum load less the nominal deformation obtained by extrapolation of the tangent of the graph of load against deformation back to zero load (A to M' in Figure A.1)

### 3.3

#### tangential flow

*F<sub>t</sub>*

nominal deformation of the moulded specimen, in millimetres (mm) obtained by extrapolation of the tangent of the graph of load against deformation forward to the stability load less the nominal deformation obtained by extrapolation of the tangent back to zero load (A to B' in Figure A.1)