

Textiles - Tests for colour fastness - Part B06: Colour fastness and ageing to artificial light at high temperatures: Xenon arc fading lamp test (ISO 105-B06:2020)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 105-B06:2020 sisaldab Euroopa standardi EN ISO 105-B06:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 105-B06:2020 consists of the English text of the European standard EN ISO 105-B06:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 01.07.2020.	Date of Availability of the European standard is 01.07.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 59.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:  
Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

## Textiles - Tests for colour fastness - Part B06: Colour fastness and ageing to artificial light at high temperatures: Xenon arc fading lamp test (ISO 105-B06:2020)

Textiles - Essais de solidité des coloris - Partie B06: Solidité des coloris et vieillissement à la lumière artificielle à hautes températures: Essai avec lampe à arc au xénon (ISO 105-B06:2020)

Textilien - Farbechtheitsprüfungen - Teil B06: Farbechtheit und Alterung gegen künstliches Licht bei hohen Temperaturen: Prüfung mit der Xenonbogenlampe (ISO 105-B06:2020)

This European Standard was approved by CEN on 7 June 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## European foreword

This document (EN ISO 105-B06:2020) has been prepared by Technical Committee ISO/TC 38 "Textiles" in collaboration with Technical Committee CEN/TC 248 "Textiles and textile products" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2021, and conflicting national standards shall be withdrawn at the latest by January 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 105-B06:2004.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 105-B06:2020 has been approved by CEN as EN ISO 105-B06:2020 without any modification.

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
4.1 Light fastness test .....	2
4.2 Ageing test .....	2
<b>5 Reference materials and apparatus</b> .....	<b>2</b>
5.1 Reference materials .....	2
5.1.1 General .....	2
5.1.2 References 1 to 8 .....	2
5.1.3 References L2 and L4 .....	2
5.2 Apparatus .....	3
5.2.1 Exposure apparatus .....	3
5.2.2 Optical light source and filter system .....	3
5.2.3 Radiometer for monitoring the exposure conditions .....	3
5.2.4 Temperature sensors .....	4
5.2.5 Opaque cardboard .....	4
5.2.6 Grey scale for assessing change in colour .....	4
5.2.7 Computerized spectral colour-measuring instrument .....	4
5.2.8 Polyester (PES) nonwoven fabric .....	4
<b>6 Preparation of specimens and exposure card</b> .....	<b>4</b>
<b>7 Procedure</b> .....	<b>5</b>
7.1 Exposure conditions .....	5
7.2 Setting the exposure conditions for set No. 3 .....	7
7.3 Exposure methods .....	7
7.3.1 General .....	7
7.3.2 Exposure Method 1 (end point determined by change in colour in the specimen) .....	7
7.3.3 Exposure Method 2 (end point determined by change in colour of reference) .....	7
7.3.4 Exposure Method 3 (end point determined on the ageing test of <a href="#">4.2</a> ) .....	7
7.3.5 Exposure Method 4 (end point determined on radiant energy) .....	8
<b>8 Assessment of colour fastness to light</b> .....	<b>8</b>
<b>9 Test report</b> .....	<b>9</b>
<b>Annex A (normative) Exposure methods and optical filter types</b> .....	<b>10</b>
<b>Annex B (normative) Apparatus for determining colour fastness and ageing with air-cooled xenon arc lamps</b> .....	<b>11</b>
<b>Annex C (normative) Apparatus for determining colour fastness and ageing with water-cooled xenon arc lamps</b> .....	<b>13</b>
<b>Annex D (normative) Guidance on performing the test according to set of conditions No. 5 (in addition to requirements specified in <a href="#">Annex C</a>)</b> .....	<b>15</b>
<b>Bibliography</b> .....	<b>17</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 248, *Textiles*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 105-B06:1998), which has been technically revised. It also incorporates the Amendment ISO 105-B06:1998/Amd.1:2002.

The main changes compared to the previous edition are as follows:

- dates in normative references have been removed;
- flat array apparatus for testing has been introduced.

A list of all parts in the ISO 105 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Textiles — Tests for colour fastness —

## Part B06:

# Colour fastness and ageing to artificial light at high temperatures: Xenon arc fading lamp test

## 1 Scope

This document specifies a method for determining the colour fastness and ageing properties of all kinds and forms of dyed and printed textiles and/or other organic substrates under the action of an artificial light source representative of natural daylight (D65), and under the simultaneous action of heat. Of the five different sets of exposure conditions specified (see 7.1.1), four use D65, and the other one uses a somewhat lower cut-off wavelength. The test method gives special consideration to the light and heat conditions that occur in the interior of a motor vehicle.

The five different sets of conditions using the different optical filter systems specified can produce different test results. Results from tests performed using different apparatus (instrument types) for the same set of conditions and optical filter system are not comparable because comparable performance has not been validated.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, *Textiles — Tests for colour fastness — Part A01: General principles of testing*

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-A05, *Textiles — Tests for colour fastness — Part A05: Instrumental assessment of change in colour for determination of grey scale rating*

ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*

ISO 105-B05, *Textiles — Tests for colour fastness — Part B05: Detection and assessment of photochromism*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>