
Additions for concrete

Ajout pour béton



This document is a preview generated by EKO



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Specifications	4
4.1 General	4
4.2 Silica fume	4
4.2.1 General	4
4.2.2 Chemical requirements	4
4.2.3 Physical requirements	5
4.3 Fly ash	6
4.3.1 Chemical requirements	6
4.3.2 Physical requirements	8
4.3.3 Specific provisions for fly ash from co-combustion	9
4.4 Ground granulated blastfurnace slag	10
4.4.1 General	10
4.4.2 Chemical requirements	10
4.4.3 Physical requirements	11
4.5 Durability requirements	12
4.6 Release of dangerous substances and emission of radioactivity	12
4.7 Information to be supplied upon request	12
5 Sampling	13
6 Conformity control and evaluation of conformity	13
7 Packaging, labelling and marking	13
Annex A (normative) Method of determining the moisture content of ground granulated blastfurnace slag	14
Annex B (normative) Determination of the water requirement for Category S fly ash	15
Annex C (normative) Determination method on the content of soluble phosphate in fly ash (expressed as P₂O₅)	17
Annex D (informative) Guidance on conformity control and evaluation of conformity	19
Bibliography	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 71, *Concrete, reinforced concrete and pre-stressed concrete*, Subcommittee SC 3, *Concrete production and execution of concrete structures*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Silica fume consists of mainly spherical particles of amorphous silicon dioxide smaller than 10^{-6} m and is highly pozzolanic. It is collected by filters as a by-product of the smelting process to produce silicon metal and ferro-silicon alloys. It can be supplied as collected from the filters (undensified), after treatment to increase its bulk density (densified), or as a slurry. Silica fume from more than one furnace, filter or intermediate storage silo will normally be blended in the production plant.

Many years of research and practical experience have demonstrated that silica fume which satisfies the requirements in this document has highly pozzolanic properties and can be used to produce concrete with improved properties in both the fresh and hardened states. Silica fume is normally used in combination with a plasticizer and/or superplasticizer.

The use of coal for electricity production results in the generation of large quantities of fly ash. Different types of coal and the type of boiler used in this process produce different fly ashes, such as siliceous, silico-calcareous, or calcareous fly ashes with pozzolanic and/or latent hydraulic properties. All these types of fly ash are used in concrete production in some countries, based on national experience and tradition.

Before use, fly ash can be subject to processing, for example by classification, selection, sieving, drying, blending, grinding or carbon reduction, to optimize its fineness, reduce its water demand or to improve other properties. Such processed fly ashes can conform to this document to which reference is made in such a case. If they are out of the scope of this document, their suitability for use as Type II additions in concrete according to ISO 22965-2 can also be established from national standards or provisions valid in the place of use of the concrete and which refer specifically to the use of the addition in concrete conforming to ISO 22965-2.

When using fly ashes conforming to this document, it should be noted that, apart from the effect from the pozzolanicity of the fly ash, certain properties of fresh and hardened concrete can be affected. Where relevant, such effects need to be considered in concrete mix design (see ISO 22965-2).

Blast-furnace slag is classified into two types, air-cooled blast-furnace slag and granulated blast-furnace slag, according to the cooling process after the molten slag of approximately 1 500 °C is removed from the furnace. Granulated slag is made by rapidly chilling molten slag, such as by water jet, into a granulated glassy material, which is used for ground granulated blast-furnace slag, a material for slag cement. The amorphous glassy granulated slag has hydraulicity. When finely ground into ground granulated blast-furnace slag, it also demonstrates hardening and strength-developing properties (latent hydraulicity), as the slag itself undergoes hydration, similarly to cement, in the co-presence of cement (an alkaline stimulant) and water.

Additions for concrete

1 Scope

This document specifies requirements for the properties for silica fume, siliceous fly ash and ground granulated blastfurnace slag for use as a type II addition for production of concrete conforming to ISO 22965. Additions according to this document can also be used in mortars and grouts.

This document applies to the silica fume which is a by-product of the smelting process used to produce silicon metal and ferro-silicon alloys.

Fly ash produced with other types or higher percentages of co-combustion materials than those provided for in this document is outside the scope of this document.

Ground granulated blastfurnace slag containing any added materials other than grinding aids and/or gypsum (calcium sulfate) is not within the scope of this document.

It is not within the scope of this document to specify provisions for the practical application of additions in the production of concrete, mortar or grout, i.e. requirements concerning composition, mixing, placing, curing, etc.

NOTE Some rules are given in ISO 22965-2, e.g. provisions on general suitability and use of additions. Guidance on batching, control of additions content and the use of the *k*-value concept are also given in ISO 22965-2.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 679, *Cement — Test methods — Determination of strength*

ISO 9277, *Determination of the specific surface area of solids by gas adsorption — BET method*

ISO 9286, *Abrasive grains and crude — Chemical analysis of silicon carbide*

ISO 9597, *Cement — Test methods — Determination of setting time and soundness*

ISO 10694, *Soil quality — Determination of organic and total carbon after dry combustion (elementary analysis)*

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*

ISO 16559, *Solid biofuels — Terminology, definitions and descriptions*

ISO 19596, *Admixtures for concrete*

ISO 20290-1, *Aggregates for concrete — Test methods for mechanical and physical properties — Part 1: Determination of bulk density, particle density, particle mass-per-volume and water absorption*

ISO 22965-2, *Concrete — Part 2: Specification of constituent materials, production of concrete and compliance of concrete*

ISO 29581-1, *Cement — Test methods — Part 1: Analysis by wet chemistry*

ISO 29581-2, *Cement — Test methods — Part 2: Chemical analysis by X-ray fluorescence*

EN 196-6, *Methods of testing cement — Part 6: Determination of fineness*

EN 196-7, *Methods of testing cement — Part 7: Methods of taking and preparing samples of cement*

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 413-2:2005, *Masonry cement — Part 2: Test methods*

EN 451-1, *Method of testing fly ash — Part 1: Determination of free calcium oxide content*

EN 451-2, *Method of testing fly ash — Part 2: Determination of fineness by wet sieving*

EN 933-10, *Tests for geometrical properties of aggregates — Part 10: Assessment of fines — Grading of filler aggregates (air jet sieving)*

EN 1015-3:1999, *Methods of test for mortar for masonry — Part 3: Determination of consistence of fresh mortar (by flow table)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 activity index

ratio (in percent) of the compressive strength of a mortar where a specific percentage of the cement is replaced with the addition, relative to the compressive strength of the reference mortar specimens made from the test cement, tested at the same age

3.2 characteristic value

value having a prescribed probability of not being attained in a hypothetical unlimited test series

Note 1 to entry: Equivalent to "fractile" which is defined in ISO 3534-1:1993.

[SOURCE: ISO 8930:1987]

3.3 densified

state of silica fume that has been treated to increase the bulk density by particle agglomeration, the bulk density typically being above 450 kg/m³

3.4 fly ash

fine powder of mainly spherical, glassy particles, derived from burning of pulverised coal, with or without co-combustion materials, which has pozzolanic properties and consists essentially of SiO₂ and Al₂O₃ and which:

- is obtained by electrostatic or mechanical precipitation of dust-like particles from the flue gases of the power stations;
- can be processed, for example by classification, selection, sieving, drying, blending, grinding or carbon reduction, or by combination of these processes, in adequate production plants, in which case it can consist of fly ashes from different sources, each conforming to the definition given in this document

Note 1 to entry: Municipal and industrial waste incineration ashes do not conform to this definition.