

Binders for paints and varnishes - Determination of softening point - Part 1: Ring-and-ball method (ISO 4625-1:2020)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 4625-1:2020 sisaldab Euroopa standardi EN ISO 4625-1:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 4625-1:2020 consists of the English text of the European standard EN ISO 4625-1:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 19.08.2020.	Date of Availability of the European standard is 19.08.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.060.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Binders for paints and varnishes - Determination of
softening point - Part 1: Ring-and-ball method (ISO 4625-
1:2020)**

Liants pour peintures et vernis - Détermination du
point de ramollissement - Partie 1: Méthode de
l'anneau et de la bille (ISO 4625-1:2020)

Bindemittel für Beschichtungsstoffe - Bestimmung der
Erweichungstemperatur - Teil 1: Verfahren mit Ring
und Kugel (ISO 4625-1:2020)

This European Standard was approved by CEN on 30 June 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 4625-1:2020) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2021, and conflicting national standards shall be withdrawn at the latest by February 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4625-1:2006.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 4625-1:2020 has been approved by CEN as EN ISO 4625-1:2020 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Sampling and preparation of test pieces	2
5.1 Sampling	2
5.2 Preparation of test pieces by the pour method	2
5.2.1 Field of application	2
5.2.2 Apparatus	2
5.2.3 Procedure	2
5.3 Preparation of test pieces from samples with a low softening point (up to 35 °C)	2
5.3.1 Apparatus	2
5.3.2 Procedure	3
6 Materials (heating-bath liquids)	3
7 Automated ring-and-ball method (reference method)	3
7.1 Apparatus	3
7.2 Calibration	4
7.3 Procedure for materials with a softening point between 35 °C and 80 °C	4
7.4 Procedure for materials with a softening point between 80 °C and 150 °C	4
7.5 Procedure for materials with a softening point above 150 °C	4
8 Manual ring-and-ball method (alternate method)	4
8.1 Apparatus	4
8.2 Calibration	7
8.3 Procedure	7
8.3.1 Procedure for materials with a softening point between 35 °C and 80 °C	7
8.3.2 Procedure for materials with a softening point between 80 °C and 150 °C	8
8.3.3 Procedure for materials with a softening point above 150 °C	8
8.3.4 Procedure for materials with a softening point below 35 °C	8
9 Expression of results	8
10 Precision and bias	8
10.1 Precision of the automated method	8
10.1.1 General	8
10.1.2 Precision data	8
10.2 Precision of the manual method	9
10.2.1 General	9
10.2.2 Precision data	9
10.3 Bias	9
11 Test report	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 4625-1:2004), which has been technically revised. The main changes compared to the previous edition are as follows:

- the automated method has been classified to be the reference method;
- an introduction with information on all three methods described in the three parts of ISO 4625 series has been added;
- CAS-numbers have been added to the chemicals used;
- the text has been editorially revised;
- the normative references have been updated.

A list of all parts in the ISO 4625 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The ISO 4625 series specifies three widely used procedures for the measurement of the softening point of rosin-based resins. This document presents the ring-and-ball method, which has been the accepted standard for many years. ISO 4625-2 presents the Mettler cup-and-ball method. A new method, called the Mettler method without the ball, is to be presented in a future document.

This document is still the only standard test method accepted in regulatory documents such as Title 21 of the Code of Federal Regulations (CFR) – Food and Drugs.

Other parts of the ISO 4625 series concern Mettler cup-and-ball methods. Although the recommended testing conditions differ, the only difference between the equipment required in such methods is that Mettler method without the ball does not use a ball. Surveys have shown that the Mettler cup-and-ball method specified in ISO 4625-2 is the most widely used in the USA, while the Mettler method without the ball is the most widely used in Europe. These methods are less time consuming than the ring-and-ball manual method and the equipment is less expensive than the ring-and-ball automated method.

As a consequence of the thermoplastic nature of the test resins, the softening points obtained using the recommended test conditions for all three methods are not generally the same. Consequently, the test method and the testing conditions used should be noted in the final report.

Binders for paints and varnishes — Determination of softening point —

Part 1: Ring-and-ball method

1 Scope

This document specifies the test methods for determining the softening point of resins (including rosin) and similar materials by means of ring-and-ball apparatus.

Both manual and automated methods are specified, the automated method being the reference method.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

IEC 60751, *Industrial platinum resistance thermometer and platinum temperature sensors*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

softening point

temperature at which a disc of sample held within a horizontal ring is forced downward a distance of 25 mm under the weight of a steel ball as the disc is heated at a prescribed rate in a water, glycerol, silicone oil, ethylene glycol/water or glycerol/water bath

4 Principle

In general, with materials of the types mentioned in [Clause 1](#), softening does not take place at a definite temperature. As the temperature rises, these materials gradually change from brittle or exceedingly thick and slow-flowing materials to softer and less viscous liquids. For this reason, the determination of the softening point shall be made by a fixed, closely defined method if the results obtained are to be comparable.

For the purpose of these test methods, the definition of softening point given in [Clause 3](#) applies.