INTERNATIONAL STANDARD

First edition 2020-08

Textiles — Tests for colour fastness —

Part X19: **Colour fastness to rubbing (Gakushin** test method)

Textiles — Essais de solidité des coloris —

sa. Partie X19: Solidité des coloris au frottement (Méthode d'essai Gakushin)



Reference number ISO 105-X19:2020(E)



© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

For	reword	iv
1	Scope	
2	Normative references	1
3	Terms and definitions	1
4	Principles	1
5	Apparatus	2
6	Test specimens	3
7	Procedure 7.1 Dry rubbing test 7.2 Wet rubbing test	
8	Evaluation	4
9	Test report	4
Anr	nex A (informative) Typical figure of rubbing meter with six rubbing fingers (Gakushin test method)	1 5
Anr	nex B (informative) Precision data	6
ر م اد	SO 2020 All rights reserved	;;;

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

A list of all parts in the ISO 105 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Textiles — Tests for colour fastness —

Part X19: Colour fastness to rubbing (Gakushin test method)

1 Scope

This document specifies the test method for determining the resistance of the colour of textiles of all kinds to rubbing off and staining other materials using convex specimen stage (Gakushin test method). Two test methods are specified, one with a dry rubbing cloth and one with a wet rubbing cloth.

This document is applicable to textiles made from all kinds of fibres in the form of yarn or fabric, including textile floor coverings and other pile fabrics, whether dyed or printed.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A01, Textiles — Tests for colour fastness — Part A01: General principles of testing

ISO 105-A03, Textiles — Tests for colour fastness — Part A03: Grey scale for assessing staining

ISO 105-A04, Textiles — Tests for colour fastness — Part A04: Method for the instrumental assessment of the degree of staining of adjacent fabrics

ISO 105-F09, Textiles — Tests for colour fastness — Part F09: Specification for cotton rubbing cloth

ISO 139, Textiles — Standard atmospheres for conditioning and testing

ISO 3696, Water for analytical laboratory use — Specification and test methods

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>
- IEC Electropedia: available at http://www.electropedia.org/

4 **Principles**

The test specimen on the convex specimen stage is rubbed by the cotton rubbing cloth fastened to the rubbing finger with a reciprocating motion. After the test is carried out, the cotton rubbing cloth is assessed by comparing with the grey scale for assessing staining or instrumentally.