
**Plastics — Impact-resistant
polystyrene (PS-I) moulding and
extrusion materials —**

**Part 2:
Preparation of test specimens and
determination of properties**

*Plastiques — Polystyrènes résistants au choc (PS-I) pour moulage et
extrusion —*

Partie 2: Préparation des éprouvettes et détermination des propriétés



This document is a preview generated by ELS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	3
4 Preparation of test specimens	3
4.1 General.....	3
4.2 Treatment of the material before moulding.....	3
4.3 Injection moulding.....	3
4.4 Compression moulding.....	3
5 Conditioning of test specimens	4
6 Determination of properties	4
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 19063-2 cancels and replaces ISO 2897-2:2003, which has been technically revised.

The main changes compared to the previous edition are as follows:

- the normative references have been updated;
- [Clause 3](#), Terms and definitions, has been added;
- the contents and structures of [Table 3](#) and [Table 4](#) have been revised according to the current version of ISO 10350-1.

A list of all parts in the ISO 19063 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Impact-resistant polystyrene (PS-I) moulding and extrusion materials —

Part 2: Preparation of test specimens and determination of properties

1 Scope

This document specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of PS-I moulding and extrusion materials. It establishes the requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing.

This document gives procedures and conditions for the preparation of test specimens and procedures for measuring properties of the materials from which these specimens are made. It lists properties and test methods which are suitable and necessary to characterize PS-I moulding and extrusion materials.

The properties have been selected from the general test methods in ISO 10350-1. Other test methods in wide use for, or of particular significance to, these moulding and extrusion materials are also included in this document, as are the designatory properties specified in ISO 19063-1.

The methods of specimen preparation and conditioning, the specimen dimensions and the test procedures specified herein are used to obtain reproducible and comparable test results. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 62, *Plastics — Determination of water absorption*

ISO 75-1, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 179-1, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*

ISO 179-2, *Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 19063-2:2020(E)

ISO 294-4, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 4: Determination of moulding shrinkage*

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-4, *Plastics — Determination of tensile properties — Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 899-1, *Plastics — Determination of creep behaviour — Part 1: Tensile creep*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2561, *Plastics — Determination of residual styrene monomer in polystyrene (PS) and impact-resistant polystyrene (PS-I) by gas chromatography*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 4589-2, *Plastics — Determination of burning behaviour by oxygen index — Part 2: Ambient-temperature test*

ISO 6603-2, *Plastics — Determination of puncture impact behaviour of rigid plastics — Part 2: Instrumented impact testing*

ISO 8256, *Plastics — Determination of tensile-impact strength*

ISO 10350-1, *Plastics — Acquisition and presentation of comparable single-point data — Part 1: Moulding materials*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and step height*

ISO 20753, *Plastics — Test specimens*

IEC 60112, *Method for the determination of the proof and the comparative tracking indices of solid insulating materials*

IEC 60243-1, *Electrical strength of insulating materials — Test methods — Part 1: Tests at power frequencies*

IEC 60296, *Fluids for electrotechnical applications — Unused mineral insulating oils for transformers and switchgear*

IEC 60695-11-10, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods*

IEC 60695-11-20, *Fire hazard testing — Part 11-20: Test flames — 500 W flame test methods*

IEC 62631-2-1, *Dielectric and resistive properties of solid insulating materials-Part 2-1:Relative permittivity and dissipation factor-Technical frequencies (0,1 Hz to 10 MHz)-AC Methods*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials — Part 3-1: Determination of resistive properties (DC methods) — Volume resistance and volume resistivity — General method*

IEC 62631-3-2, *Dielectric and resistive properties of solid insulating materials — Part 3-2: Determination of resistive properties (DC methods) — Surface resistance and surface resistivity*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Preparation of test specimens

4.1 General

It is essential that specimens always be prepared by the same procedure (either injection moulding or compression moulding), using the same processing conditions. The procedure to be used for each test method is indicated in [Tables 3](#) and [4](#).

The material shall be kept in moisture-proof containers until it is required for use. The moisture content of filled or reinforced materials shall be expressed as a percentage of the total mass of the compound.

4.2 Treatment of the material before moulding

No pretreatment of the material sample is normally necessary before processing.

4.3 Injection moulding

Injection-moulded specimens shall be prepared in accordance with ISO 294-1 or ISO 294-3, under the conditions specified in [Table 1](#). It has been found that bar test specimens prepared in accordance with ISO 20753 give better precision than those injection-moulded directly to their final dimensions, and so the use of this geometry is preferable. (see ISO 294-1 or ISO 294-3 for tolerances).

Table 1 — Conditions for injection moulding of test specimens

Material	Melt temperature °C	Mould temperature °C	Average injection velocity mm/s
All grades	220	45	200 ± 100
Flame-retardant grades can show discoloration if moulded at a melt temperature of 220 °C. In such cases, a melt temperature of 210 °C may be used.			

4.4 Compression moulding

Compression-moulded sheets shall be prepared in accordance with ISO 293, using the conditions specified in [Table 2](#), in which the moulding temperature given is a target value (see ISO 293 for tolerances).

The test specimens required for the determination of the properties shall be machined from the compression moulded sheets in accordance with ISO 2818 or stamped.