

MEETOD KIIRENDATUD KULUMISE JA KORROSIONI
SIMULEERIMISEKS NIKLI ERAVDUMISE AVASTAMISEKS
NIKELDATUD ESEMETELT

Method for the simulation of accelerated wear and
corrosion for the detection of nickel release from
coated items

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12472:2020 sisaldab Euroopa standardi EN 12472:2020 ingliskeelset teksti.	This Estonian standard EVS-EN 12472:2020 consists of the English text of the European standard EN 12472:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 16.09.2020.	Date of Availability of the European standard is 16.09.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 39.060

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 12472

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2020

ICS 39.060

Supersedes EN 12472:2005+A1:2009

English Version

Method for the simulation of accelerated wear and corrosion for the detection of nickel release from coated items

Méthode de simulation de l'usure et de la corrosion accélérées pour la détermination de la teneur en nickel libéré par les objets revêtus

Simulierte Abrieb- und Korrosionsprüfung zum beschleunigten Nachweis der Nickelabgabe von mit Auflagen versehenen Gegenständen

This European Standard was approved by CEN on 24 May 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Reagents and materials	6
5.1 General	6
5.2 Corrosion	6
5.2.1 Container	6
5.2.2 Corrosive medium	6
5.2.3 Degreasing solution	6
5.2.4 Deionized water	6
5.2.5 Laboratory oven	6
5.3 Wear	6
5.3.1 Tumbling barrel and retaining assembly	6
5.3.2 Wear test apparatus	7
5.3.3 Abrasive paste	7
5.3.4 Granules	8
5.3.5 Wear medium	8
6 Procedure	8
6.1 Article preparation	8
6.2 Corrosion procedure	8
6.3 Wear procedure	8
6.3.1 Preparation of wear medium	8
6.3.2 Attachment of test parts	9
6.3.3 Tumbling	9
6.4 Determination of nickel release	9
7 Test report	9
Annex A (informative) Detailed examples of how to attach different types of test parts	10
A.1 General	10
A.2 Attachment of test parts with only one side in contact with the skin	10
A.3 Spectacle frames and sunglasses	10
A.4 Chains, watches, bracelets, rings etc.	14
Bibliography	16

European foreword

This document (EN 12472:2020) has been prepared by Technical Committee CEN/TC 347 “Methods for analysis of allergens”, the secretariat of which is held by SNV.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2021, and conflicting national standards shall be withdrawn at the latest by March 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12472:2005+A1:2009.

This document includes the revised text of EN 12472:2005+A1:2009, as well as the changes proposed by CEN/TC 170 regarding spectacle frames and sunglasses.

The major changes are:

- reference to Regulation (EC) No 1907/2006 (REACH) instead of Directive 94/27/EC;
- use of the term article instead of items, in order to adopt the use of terms in the REACH Regulation;
- update of normative references;
- clarification of articles covered by the scope of this document;
- clarification of concentration of the lactic acid stock solution;
- requirements for granules have been changed;
- A.3 regarding spectacle frames has been updated;
- the document has been editorially updated.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The wear and corrosion of objects in contact with the skin depends very much on the composition, environment, and shape of the article and the activities of the person concerned. This procedure attempts to simulate the wear and corrosion on a coated article during two years of normal use. By its nature this is a pragmatic solution to the problems posed by the evaluation of coated articles in contact with the skin, which may be subject to several kinds and varying degrees of wear.

In order to show compliance with the Commission Regulation (EC) No 1907/2006 (REACH) of the European Parliament and the Council in the current version, articles should be tested in accordance with the appropriate European harmonized standard(s), the references of which have been published by the European Commission in the Official Journal of the European Communities. Currently, these are EN 1811, EN 16128 and this document.

1 Scope

This document specifies a method for the simulation of accelerated wear and corrosion, to be used prior to the detection of nickel release from coated articles that come into direct and prolonged contact with the skin. According to the Commission Regulation (EC) No 1907/2006 (REACH), articles with an outer coating containing nickel and those which are inserted into pierced ears and other parts of the human body are excluded from the scope of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1811, *Reference test method for release of nickel from all post assemblies which are inserted into pierced parts of the human body and articles intended to come into direct and prolonged contact with the skin*

EN 16128, *Ophthalmic optics — Reference method for the testing of spectacle frames and sunglasses for nickel release*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

article

object that is subjected to the nickel release requirements according to Entry 27 of Annex XVII of Commission Regulation (EC) No 1907/2006 (REACH)

3.2

test part

article or sub-part of a dismantled and/or cut article that has to be tested according to EN 1811 or EN 16128

4 Principle

The articles to be tested are exposed to a corrosive atmosphere before being placed into a tumbling barrel together with a wear medium of abrasive paste and granules. The barrel is rotated so as to subject the test parts to wear from the wear medium. The test parts are then tested for nickel release in accordance with the applicable European standard.

NOTE EN 1811 is applicable to all products except spectacle frames and sunglasses. EN 16128 is applicable to spectacle frames and sunglasses.

If only indicative information on the extent of nickel release or the presence of nickel is required, such information can be obtained by performing the tests specified in CR 12471.