
**Paints and varnishes — Natural
weathering of coatings — Exposure
and assessment**

*Peintures et vernis — Vieillissement naturel des revêtements —
Exposition et évaluation*



This document is a preview generated by EKO



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General	1
5 Exposure racks	2
6 Apparatus for measurement of climatic factors	3
6.1 Measurement of solar radiation	3
6.1.1 Pyranometers	3
6.1.2 Pyrhemometers	3
6.1.3 Total-ultraviolet radiometers	4
6.1.4 Narrow-band ultraviolet radiometers	4
6.2 Other climate-measuring instruments	4
7 Test specimens	4
8 Procedure	5
9 Supplementary test conditions	5
10 Evaluation of properties	6
11 Precision	6
12 Test report	6
Annex A (normative) Environment and climate	8
Annex B (informative) Classification of climates	10
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 2810:2004), which has been technically revised. The main changes compared to the previous edition are as follows:

- in [Clause 4](#), the list in b) has been amended by radiant exposure and temperature;
- the time of wetness has been deleted from the list of additional observations on climate in [A.2](#) and replaced by a note with the reference to ASTM Practice G84;
- the climate classification in [Annex B](#) has been updated to ISO 877-1:2009;
- the text has been editorially revised and the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paints and varnishes — Natural weathering of coatings — Exposure and assessment

1 Scope

This document specifies the conditions to take into consideration when selecting the type of natural weathering and the natural weathering procedure to determine the resistance of coatings or coating systems (direct weathering or weathering behind window glass).

Natural weathering is used to determine the resistance of coatings or coating systems (denoted in this document by coatings) to the sun's radiation and the atmosphere.

This document does not take into account special atmospheric influences, e.g. industrial pollution.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 4618, *Paints and varnishes — Terms and definitions*

WMO Publication No, 8, *Guide to meteorological instruments and methods of observation*, World Meteorological Organization, Geneva, 2012

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

durability

ability of a specimen to resist the deleterious effect of its environment

3.2

time of wetness

period during which an exposed coating has surface moisture present on it

4 General

The durability of a coating during natural weathering depends on how, where and when the coating is weathered. Therefore, these parameters and the intended use of the coating shall be taken into account when exposures are carried out.