
**Lubricants, industrial oils and
related products (class L) — Family C
(gears) —**

**Part 2:
Specifications of categories CKH, CKJ
and CKM (lubricants open and semi-
enclosed gear systems)**

*Lubrifiants, huiles industrielles et produits connexes (classe L) —
Famille C (engrenages) —*

*Partie 2: Spécifications des lubrifiants de catégories CKH, CKJ et CKM
pour engrenages nus et sous carter semi-fermé*



This document is a preview generated by EKO



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Sampling	2
5 Open gear lubricants	3
5.1 Open gears.....	3
5.2 Viscosity of open gear lubricants.....	3
6 Extended classification for open gear lubricants	3
7 Additional requirements for the environmentally acceptable lubricants	5
8 Specifications tables	6
8.1 General.....	6
8.2 Specifications for ISO-L-CKH gear lubricants.....	6
8.3 Specifications for ISO-L-CKJ gear lubricants.....	6
8.4 Specifications for ISO-L-CKJ-F gear lubricants.....	6
8.5 Specifications for ISO-L-CKM gear lubricants.....	6
8.6 Specifications for ISO-L-CKJTG.....	6
8.7 Specifications for ISO-L-CKJES.....	7
8.8 Specifications for ISO-L-CKJPG.....	7
8.9 Specifications for ISO-L-CKJPR.....	7
Annex A (normative)	8
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 28, *Petroleum and related products, fuels and lubricants from natural or synthetic sources*, Subcommittee SC 4, *Classifications and specifications*.

A list of all parts in the ISO 12925 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Lubricants for gear systems are used in diverse types of gear designs, ranging from simple parallel spur to gears to bevel gears (straight or helical), worm gears and hypoid gears. Industrial gear systems, which are either of open type or enclosed type, vary in size from small enclosed systems used in machine tools to very large systems used in mining, steel mills and cement plants.

Lubricants for these applications vary in composition from refined straight mineral oils to more complex blends, based on mineral oils, synthetic oils (e.g. poly α -olefins, esters, poly-glycols) and additives friction modifying and / or extreme-pressure. Depending on the type of application and range, viscosity grades, in accordance with ISO 3448, vary from the low viscosity ISO VG 32 to high viscosity ISO VG 1 500; even more for the very low velocities and very high loads. In exceptional cases, viscosity grades may be even higher. Temperature conditions to which the gear systems are exposed also vary considerably, not only due to the ambient conditions of operation, but also depending on the sliding between the gear teeth, on the size of the casings, on the presence on the circulating systems of heat exchangers, on the vicinity of sources of heat like in the cement industry or in the steel industry.

Greases can also be used for the splash lubrication of enclosed gears or for the application on open gear teeth.

Lubricants, industrial oils and related products (class L) — Family C (gears) —

Part 2:

Specifications of categories CKH, CKJ and CKM (lubricants open and semi-enclosed gear systems)

1 Scope

This document establishes an extended classification which includes sub-categories of environmentally acceptable lubricants and specifies the minimum requirements for mineral or synthetic based lubricants for the categories CKH, CKJ and CKM, according to ISO 6743-6, and their sub-categories of environmentally acceptable lubricants, intended for the lubrication of open and semi-enclosed gears.

This document covers the lubricants applied in the open and semi-enclosed gear systems most currently encountered in the industry. It does not cover the extreme cases of use with regards to temperature and extreme charges conditions.

NOTE 1 For use in exceptional conditions, suppliers and purchasers of lubricants can mutually agree on additional testing methods and acceptability criteria of the products.

NOTE 2 This document can be read in conjunction with ISO 6743-6.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2160, *Petroleum products — Corrosiveness to copper — Copper strip test*

ISO 2592, *Petroleum and related products — Determination of flash and fire points — Cleveland open cup method*

ISO 3104, *Petroleum products — Transparent and opaque liquids — Determination of kinematic viscosity and calculation of dynamic viscosity*

ISO 3016, *Petroleum and related products from natural or synthetic sources — Determination of pour point*

ISO 3170, *Petroleum liquids — Manual sampling*

ISO 3448, *Industrial liquid lubricants — ISO viscosity classification*

ISO 3675, *Crude petroleum and liquid petroleum products — Laboratory determination of density — Hydrometer method*

ISO 3838, *Crude petroleum and liquid or solid petroleum products — Determination of density or relative density — Capillary-stoppered pycnometer and graduated bicapillary pycnometer methods*

ISO 4259-2, *Petroleum and related products — Precision of measurement methods and results — Part 2: Interpretation and application of precision data in relation to methods of test*

ISO 6341, *Water quality — Determination of the inhibition of the mobility of Daphnia magna Straus (Cladocera, Crustacea) — Acute toxicity test*

ISO 7120, *Petroleum products and lubricants — Petroleum oils and other fluids — Determination of rust-preventing characteristics in the presence of water*

ISO 7346-1, *Water quality — Determination of the acute lethal toxicity of substances to a freshwater fish [Brachydanio rerio Hamilton-Buchanan (Teleostei, Cyprinidae)] — Part 1: Static method*

ISO 8692, *Water quality — Fresh water algal growth inhibition test with unicellular green algae*

ISO 9408, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium by determination of oxygen demand in a closed respirometer*

ISO 9439, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Carbon dioxide evolution test*

ISO 10253, *Water quality — Marine algal growth inhibition test with Skeletonema sp. and Phaeodactylum tricornutum*

ISO 12185, *Crude petroleum and petroleum products — Determination of density — Oscillating U-tube method*

ISO 14593, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Method by analysis of inorganic carbon in sealed vessels (CO₂ headspace test)*

ISO 14635-1, *Gears — FZG test procedures — Part 1: FZG test method A/8,3/90 for relative scuffing load-carrying capacity of oils*

ISO 14635-3, *Gears — FZG test procedures — Part 3: FZG test method A/2, 8/50 for relative scuffing load-carrying capacity and wear characteristics of semifluid gear greases*

ISO 14669, *Water quality — Determination of acute lethal toxicity to marine copepods (Copepoda, Crustacea)*

ISO 16221, *Water quality — Guidance for determination of biodegradability in the marine environment*

EN 16807, *Liquid petroleum products. Bio-lubricants. Criteria and requirements of bio-lubricants and bio-based lubricants*

ASTM D 6866, *Standard Test Method for Determining the Biobased Content of Solid, Liquid and Gaseous Samples using Radiocarbon Analysis*

CEN/TS 16640, *Bio-based products — Determination of the bio based carbon content of products using the radiocarbon method*

DIN 51819-3, *Testing of lubricants — Mechanical-dynamic testing in the roller bearing test apparatus FE8 — Part 3: Test method for lubricating oils, axial cylindrical roller bearing*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Sampling

Sampling of gear oils for the purpose of this document, unless otherwise specified, shall be carried out in accordance with the pertinent procedure described in ISO 3170. The sample shall be evaluated on a